



**NSAI**  
Standards

Irish Standard  
I.S. EN 1177:2018

# Impact attenuating playground surfacing - Methods of test for determination of impact attenuation

**I.S. EN 1177:2018**

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

*This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):*

*NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.*

*This document is based on:*

EN 1177:2018

*Published:*

2018-01-10

*This document was published under the authority of the NSAI and comes into effect on:*

2018-01-28

ICS number:

97.200.40

NOTE: If blank see CEN/CENELEC cover page

NSAI  
1 Swift Square,  
Northwood, Santry  
Dublin 9

T +353 1 807 3800  
F +353 1 807 3838  
E standards@nsai.ie  
W NSAI.ie

Sales:  
T +353 1 857 6730  
F +353 1 857 6729  
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

## National Foreword

I.S. EN 1177:2018 is the adopted Irish version of the European Document EN 1177:2018, Impact attenuating playground surfacing - Methods of test for determination of impact attenuation

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

**Compliance with this document does not of itself confer immunity from legal obligations.**

*In line with international standards practice the decimal point is shown as a comma (,) throughout this document.*

This page is intentionally left blank

EUROPEAN STANDARD

EN 1177

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2018

ICS 97.200.40

Supersedes EN 1177:2008

English Version

## Impact attenuating playground surfacing - Methods of test for determination of impact attenuation

Sols d'aires de jeux absorbant l'impact - Méthodes  
d'essai pour la détermination de l'atténuation de  
l'impact

Stoßdämpfende Spielplatzböden - Prüfverfahren zur  
Bestimmung der Stoßdämpfung

This European Standard was approved by CEN on 29 October 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## Contents

Page

European foreword.....	4
Introduction .....	6
1 Scope.....	8
2 Normative references.....	8
3 Terms and definitions .....	8
4 Test apparatus.....	9
4.1 Suitability.....	9
4.2 Components of the apparatus.....	10
4.3 Accuracy of apparatus .....	12
4.3.1 Calibration by a laboratory .....	12
4.3.2 Checks by operators.....	12
5 Testing procedure.....	13
5.1 Principle of impact measurement.....	13
5.2 Selection and definition of test positions .....	14
6 Test Method 1 – Determination of Critical Fall Height (CFH) .....	15
6.1 Principle .....	15
6.2 Testing in the laboratory.....	15
6.3 Testing on site .....	17
7 Test Method 2 – Determination of Impact Attenuation on site .....	18
7.1 Principle .....	18
7.2 Selection and recording of test positions .....	18
7.3 Carrying out the test.....	19
7.4 Results.....	19
8 Reports.....	19
8.1 General.....	19
8.2 Tests carried out in the laboratory with Method 1.....	19
8.3 Tests carried out on site in accordance with Method 1.....	20
8.4 Tests carried out on site in accordance with Method 2.....	21
Annex A (informative) Test rig for determination of impact attenuation.....	22
Annex B (informative) Typical examples of trace of acceleration against time and curve of HIC and $g_{max}$ values against drop height .....	23
Annex C (informative) Verification of computer algorithm used for the calculation of HIC (see 4.3.1.4) .....	25
Annex D (normative) Procedure for selection of test positions in playgrounds for Method 2 (see Clause 7).....	26
D.1 Principle .....	26
D.2 Criteria for selection of test zones (3.12).....	26

<b>Annex E (normative) Method for compaction of loose particulate impact attenuating material (see 6.2.4.5.1)</b> .....	<b>31</b>
<b>E.1 General</b> .....	<b>31</b>
<b>E.2 Measurement of layer thickness</b> .....	<b>31</b>
<b>E.3 Compaction procedure</b> .....	<b>31</b>
<b>Annex F (informative) Example of a regime for checking the function of an HIC test apparatus</b> .....	<b>33</b>

## EN 1177:2018 (E)

### European foreword

This document (EN 1177:2018) has been prepared by Technical Committee CEN/TC 136 “Sports, playground and other recreational facilities and equipment”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2018, and conflicting national standards shall be withdrawn at the latest by July 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1177:2008.

European standards for playground equipment and surfacing comprise this European Standard and the EN 1176 series, which consists of a number of parts as follows:

- *Part 1: General safety requirements and test methods*
- *Part 2: Additional specific safety requirements and test methods for swings*
- *Part 3: Additional specific safety requirements and test methods for slides*
- *Part 4: Additional specific safety requirements and test methods for cableways*
- *Part 5: Additional specific safety requirements and test methods for carousels*
- *Part 6: Additional specific safety requirements and test methods for rocking equipment*
- *Part 7: Guidance on installation, inspection, maintenance and operation*
- *Part 10: Additional specific safety requirements and test methods for fully enclosed play equipment*
- *Part 11: Additional specific safety requirements and test methods for spatial network*

This standard should also be read in conjunction with:

- EN 1176:2017 series
- CEN/TR 16467:2013, *Playground equipment accessible for all children*
- CEN/TR 16598:2014, *Collection of rationales for EN 1176 - Requirements*
- CEN/TR 16396:2012, *Playground equipment for children, replies to requests for interpretation of EN 1176:2008 and its parts*

For inflatable play equipment, see EN 14960, *Inflatable play equipment — Safety requirements and test methods*.



The principal changes from the previous edition of this European Standard are as follows:

- a) European foreword: References to CEN/TRs added.
- b) Introduction: Rationale for retaining HIC 1 000 and introducing  $g_{\max}$  200 as upper limits for surfacing when assessed in accordance with this standard has been added.
- c) Scope: Two methods of impact testing are now provided. Method 1 (as in the previous edition) – Test for determination of Critical Fall Height AND new Method 2 – Test for measurement of impact attenuation on site to enable, upon installation or at periods later in its life, confirmation as required of suitability of the product for that specific site location at the time of the test.
- d) Body of standard:
  - 1) change of the order and adding new clauses by implementation of Method 2;
  - 2) adaption of recent technology for requirements on test apparatus and measurements in order to improve accuracy of results (including checks by operators);
  - 3) adapting Annex B and adding new Annexes C, D, E and F.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## EN 1177:2018 (E)

### Introduction

This European Standard is based on the safety principles given in EN 1176-1 for playground equipment and provides a method for the assessment of impact attenuation of surfaces intended for use in the impact area as defined in EN 1176-1. This standard (EN 1177) aims to reduce consequences of experiencing risks that are desirable for child development according to the principles set in EN 1176-1.

Injuries arise during the use of playground equipment for a variety of reasons and the great majority are minor. Even the presence of protection features like impact attenuating surfacing is known to affect the behaviour of children, as well as carers and play providers, which in turn can affect the risk. The majority of more serious injuries are attributable to falls and there are many factors that influence injury mechanisms during a fall that are independent of the surfacing, e.g. body orientation, awkwardness of fall, bone density, etc.

The most severe injuries are likely to be injuries to the head. Recent research has indicated that arm and leg injuries are more frequent and could be influenced by the duration of the acceleration pulse. The committee responsible for this European Standard maintains a constant review of research in this area for possible use in a future revision of this standard. The committee recognizes that there is a relationship between the risk of arm and leg injuries and surface type but takes the view that such injuries are not usually in the most severe category. At present the available injury data can be taken into account by limitation of the maximum (peak) acceleration.

Consequently, the committee has chosen to make its priority the reduction of the likelihood of serious head injuries caused by a fall from playground equipment, because even though such injuries are relatively uncommon, they can have the most severe consequences. The severity of injury resulting from an impact to the head can be quantified in terms of Head Injury Criterion (HIC) and the level of  $HIC = 1\ 000$  together with the upper limit of the peak acceleration of  $g_{\max} = 200g$  ( $g$  for gravity) have been chosen as the upper limits for surfacing when assessed in accordance with this standard.

Limiting the HIC value at a maximum of 1 000 is equivalent to a 3 % chance of a critical head injury (MAIS<sup>1</sup> 5), an 18 % probability of a severe (MAIS 4) head injury, a 55 % probability of a serious (MAIS 3) head injury, a 89 % probability of a moderate head injury (MAIS 2), and a 99,5 % chance of a minor head injury (MAIS 1), to an average male adult.

Limiting  $g_{\max}$  to a maximum of 200g as well as limiting HIC to a maximum of 1 000 takes account of impacts of very short duration and follows the current research on arm injuries as a means of improvement to the Standard.

Two methods of impact tests are provided. The first method is for determination of the Critical Fall Height to enable full and detailed confirmation of a product's range of suitability. The second method describes an on-site drop test, without determination of critical fall height to enable, upon installation or at periods later in its life, confirmation as required of the performance of the surfacing in that specific site location at the time of the test.

The EN committee is aware of discussions within ASTM International since 2014 about a reduction in the HIC threshold to 700 in its corresponding standard. The current limiting value of  $HIC \leq 1\ 000$  has been used in Europe since 1998 and the EN committee considers that at present, there is insufficient evidence of net overall value to playground users to support a change. It has therefore chosen to retain the value  $HIC \leq 1\ 000$  and to provide a second threshold of 200g as the criteria of acceptability in this standard, whilst continuing to monitor research publications on this subject. The same has been decided by ASTM for the time being.

---

<sup>1</sup> Maximum Abbreviated Injury Scale, first developed by the Association for the Advancement of Automotive Medicine and used extensively in the automotive industry as an indicator of the severity of head-related injuries.

A variety of materials, both natural and synthetic, may be used as impact attenuating surfacing with different attributes and performance. These include grass growing in soil, sand, wood chips, bark, gravel, and various rubber-based products which may be in the form of tiles or continuous coatings or combinations of these materials. Whilst the methods described in this Standard can be used to assess the impact attenuation performance of any of these surfaces, attention of users is drawn that the behaviour of some materials can be highly variable and dependent on prevailing test conditions and that test results will likely vary over time or with climatic conditions.

## EN 1177:2018 (E)

### 1 Scope

This European Standard specifies the test apparatus and the impact test methods for determining the impact attenuation of surfacing by measuring the acceleration experienced during impact. Test apparatus in compliance with this standard are applicable to tests carried out in a laboratory or on site by either methods described.

NOTE The test methods described in this standard are also applicable for impact areas required in other standards than for playground equipment, e.g. for outdoor fitness equipment and parkour equipment.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 1176-1:2017, *Playground equipment and surfacing — Part 1: General safety requirements and test methods*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025)*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1176-1 and the following apply.

#### 3.1 impact attenuation

property of a surface, which dissipates the kinetic energy of an impact by localized deformation or displacement in such a way that the acceleration experienced by the impacting object is reduced

#### 3.2 impact attenuating surfacing

IAS  
surfacing intended to reduce the risk of injury when falling onto it

Note 1 to entry: product or material having the inherent ability to attenuate the impact of a user falling onto it

#### 3.3 critical fall height

CFH  
maximum Free Height of Fall (FHF), for which a surface will provide an adequate level of impact attenuation, determined by test Method 1 as described in Clause 6 of this standard

#### 3.4 head injury criterion

HIC  
measure of the severity of a head injury likely to arise from an impact, determined as described in Clause 5 of this standard

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-