



**NSAI**  
Standards

Irish Standard  
I.S. EN ISO 2819:2018

Metallic coatings on metallic substrates -  
Electrodeposited and chemically deposited  
coatings - Review of methods available for  
testing adhesion (ISO 2819:2017)

## I.S. EN ISO 2819:2018

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

*This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):*

*NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.*

*This document is based on:*

EN ISO 2819:2018

*Published:*

2018-03-07

*This document was published under the authority of the NSAI and comes into effect on:*

2018-03-26

ICS number:

25.220.40

NOTE: If blank see CEN/CENELEC cover page

NSAI  
1 Swift Square,  
Northwood, Santry  
Dublin 9

T +353 1 807 3800  
F +353 1 807 3838  
E standards@nsai.ie  
W NSAI.ie

Sales:  
T +353 1 857 6730  
F +353 1 857 6729  
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

## National Foreword

I.S. EN ISO 2819:2018 is the adopted Irish version of the European Document EN ISO 2819:2018, Metallic coatings on metallic substrates - Electrodeposited and chemically deposited coatings - Review of methods available for testing adhesion (ISO 2819:2017)

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

**Compliance with this document does not of itself confer immunity from legal obligations.**

*In line with international standards practice the decimal point is shown as a comma (,) throughout this document.*

This page is intentionally left blank

EUROPEAN STANDARD

EN ISO 2819

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2018

ICS 25.220.40

Supersedes EN ISO 2819:1994

English Version

## Metallic coatings on metallic substrates - Electrodeposited and chemically deposited coatings - Review of methods available for testing adhesion (ISO 2819:2017)

Revêtements métalliques sur bases métalliques -  
Dépôts électrolytiques et dépôts par voie chimique -  
Liste des différentes méthodes d'essai d'adhérence  
(ISO 2819:2017)

Metallische Überzüge auf metallischen  
Grundwerkstoffen - Galvanische und chemische  
Überzüge - Überblick über Methoden der  
Haftfestigkeitsprüfung (ISO 2819:2017)

This European Standard was approved by CEN on 1 December 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

**EN ISO 2819:2018 (E)**

<b>Contents</b>	<b>Page</b>
<b>European foreword.....</b>	<b>3</b>

## **European foreword**

This document (EN ISO 2819:2018) has been prepared by Technical Committee ISO/TC 107 “Metallic and other inorganic coatings” in collaboration with Technical Committee CEN/TC 262 “Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys” the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2018, and conflicting national standards shall be withdrawn at the latest by September 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2819:1994.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **Endorsement notice**

The text of ISO 2819:2017 has been approved by CEN as EN ISO 2819:2018 without any modification.

This page is intentionally left blank



# INTERNATIONAL STANDARD

**ISO  
2819**

Third edition  
2017-11

---

---

## **Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion**

*Revêtements métalliques sur bases métalliques — Dépôts  
électrolytiques et dépôts par voie chimique — Liste des différentes  
méthodes d'essai d'adhérence*



Reference number  
ISO 2819:2017(E)

© ISO 2017

**ISO 2819:2017(E)**



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Methods of test</b> .....	<b>1</b>
4.1 Burnishing test.....	1
4.2 Ball burnishing test.....	2
4.3 Shot peening test.....	2
4.4 Peel test.....	2
4.5 File test.....	2
4.6 Grinding and sawing tests.....	3
4.7 Chisel test.....	3
4.8 Scribe and grid test.....	3
4.9 Bending test.....	3
4.10 Twisting (winding) test.....	4
4.11 Tensile test.....	4
4.11.1 Tensile test as qualitative test as a measure of adhesion in terms of a classification.....	4
4.11.2 Tensile test as quantitative test for the determination of assembly strength in N/mm <sup>2</sup> .....	4
4.12 Thermal shock test.....	4
4.13 Drawing test.....	5
4.14 Cathodic test.....	5
4.15 Rockwell-C test.....	5
4.16 Scratch-test.....	6
4.17 Cavitation test.....	6
<b>5 Summary</b> .....	<b>6</b>
<b>Annex A (informative) Determination of adhesion of silver deposits (100 µm to 600 µm):     shot-peening method</b> .....	<b>8</b>
<b>Bibliography</b> .....	<b>11</b>

## ISO 2819:2017(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in collaboration with ISO Technical Committee TC 107, *Metallic and other inorganic coatings*, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 2819:1980), which has been technically revised.

The main changes compared to the previous edition are as follows:

- tensile test has been extended by centrifugal adhesion testing;
- Rockwell-C test has been added;
- scratch test has been added;
- cavitation test has been added;
- editorial changes and informative references to further existing standards have been made.

# Metallic coatings on metallic substrates — Electrodeposited and chemically deposited coatings — Review of methods available for testing adhesion

**WARNING** — When particular methods of adhesion testing are included in International Standards for individual coatings, they should be used in preference to the methods described in this document and should be agreed upon beforehand by the supplier and the purchaser.

## 1 Scope

This document specifies methods of checking the adhesion of electrodeposited and chemically deposited coatings. It is limited to tests of a qualitative nature.

This document does not describe certain tests that have been developed at various times to give a quantitative measure of adhesion of metallic coating to a substrate, since such tests require special apparatus and considerable skill in their performance which renders them unsuitable as quality control tests for production parts. Some of these quantitative tests can, however, be useful in research and development work.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Methods of test

### 4.1 Burnishing test

If plated parts are subjected to burnishing in a localized area, the deposit will tend to work-harden and absorb frictional heat. If the coating is thin, separation of the coating from the basis metal as blisters will occur under these conditions in areas of poor adhesion.

When the shape and size of the part permit, an area of not more than 6 cm<sup>2</sup> of the plated surface should be rubbed with a smooth implement for about 15 s. A suitable implement is a steel rod 6 mm in diameter with a smooth hemispherical end.

The pressure shall be sufficient to burnish the coating at every stroke but not so great as to cut the coating. Poor adhesion is indicated by the appearance of a blister which grows as the rubbing is continued.

If the mechanical properties of the coating are poor, the blister may crack and the coating will peel from the basis metal. This test shall be limited to relatively thin deposits.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-