

Irish Standard I.S. EN ISO 5398-4:2019

Leather - Chemical determination of chromic oxide content - Part 4: Quantification by inductively coupled plasma (ICP) (ISO 5398-4:2018)

 $\ensuremath{\mathbb C}$  CEN 2019  $\hfill No copying without NSAI permission except as permitted by copyright law.$ 

#### I.S. EN ISO 5398-4:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

*NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.* 

This document is based on: EN ISO 5398-4:2019 *Published:* 2019-02-06

This document was published under the authority of the NSAI and comes into effect on:

2019-02-24

ICS number:

59.140.30

NOTE: If blank see CEN/CENELEC cover page

NSAI	T +353 1 807 3800	Sales:
1 Swift Square,	F +353 1 807 3838	T +353 1 857 6730
Northwood, Santry	E standards@nsai.ie	F +353 1 857 6729
Dublin 9	W NSAI.ie	W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

#### **National Foreword**

I.S. EN ISO 5398-4:2019 is the adopted Irish version of the European Document EN ISO 5398-4:2019, Leather - Chemical determination of chromic oxide content - Part 4: Quantification by inductively coupled plasma (ICP) (ISO 5398-4:2018)

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

#### Compliance with this document does not of itself confer immunity from legal obligations.

*In line with international standards practice the decimal point is shown as a comma (,) throughout this document.* 

This is a free page sample. Access the full version online.

This page is intentionally left blank

## EUROPEAN STANDARD NORME EUROPÉENNE

## EN ISO 5398-4

## **EUROPÄISCHE NORM**

February 2019

ICS 59.140.30

Supersedes EN ISO 5398-4:2007

**English Version** 

## Leather - Chemical determination of chromic oxide content - Part 4: Quantification by inductively coupled plasma (ICP) (ISO 5398-4:2018)

Cuir - Dosage chimique de l'oxyde de chrome - Partie 4: Quantification par plasma à couplage inductif (ICP) (ISO 5398-4:2018) Leder - Chemische Bestimmung des Chromoxidgehalts - Teil 4: Quantitative Bestimmung durch induktiv gekoppeltes Plasma (ICP) (ISO 5398-4:2018)

This European Standard was approved by CEN on 16 December 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	

## **European foreword**

This document (EN ISO 5398-4:2019) has been prepared by Technical Committee ISO/IULTCS "International Union of Leather Technologists and Chemists Societies" in collaboration with Technical Committee CEN/TC 289 "Leather" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2019, and conflicting national standards shall be withdrawn at the latest by August 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 5398-4:2007.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **Endorsement notice**

The text of ISO 5398-4:2018 has been approved by CEN as EN ISO 5398-4:2019 without any modification.

This is a free page sample. Access the full version online.

This page is intentionally left blank

## INTERNATIONAL ISO STANDARD 5398-4 IULTCS/IUC 8-4

Second edition 2018-12

## Leather — Chemical determination of chromic oxide content —

Part 4: Quantification by inductively coupled plasma (ICP)

Cuir — Dosage chimique de l'oxyde de chrome — Partie 4: Quantification par plasma à couplage inductif (ICP)



Reference numbers ISO 5398-4:2018(E) IULTCS/IUC 8-4:2018(E)



## **COPYRIGHT PROTECTED DOCUMENT**

#### © ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

## Contents

Forew	ord			iv	
Introd	luctior	1		vi	
1	Scope	<u>.</u>			
2	Norm				
3	Terms and definitions				
4	Principle				
5	Sampling and sample preparation				
6	Reagents				
7	Apparatus				
8	Methods				
-	8.1	Prepar 8.1.1 8.1.2	ation of analytical solution Wet oxidation method Microwave digestion or other method of digestion		
	8.2	Measu 8.2.1 8.2.2 8.2.3	rement of the aqueous solution General Preparation of calibration graph Analysis of the test solution	3 3 3 3 3 3	
9	Calculation and expression of results				
10	Test report				
Annex	<b>A</b> (inf	ormative	e) Determination of water and other volatile matter	5	
Annex	<b>B</b> (inf	ormative	e) Suitable ICP equipment	6	

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <u>www.iso</u> .org/iso/foreword.html.

This document was prepared by the Chemical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

It is based on IUC 8, published in *J. Soc. Leather Tech. Chem.*, **49**, p. 17, 1965, and declared an official method of the IULTCS in 1965.

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 5398-4:2007), which has been technically revised. The main changes compared to the previous edition are as follows:

- the title has changed to "inductively coupled plasma (ICP)" to include more than just the "ICP-OES" type equipment;
- <u>Clause 5</u> now refers to ISO 4044 for preparing the sample rather than grinding the leather;
- the description of additional suitable ICP equipment (ICP-MS) has been included in a new subclause <u>7.3;</u>
- the previous subclause 8.2.1 describing suitable ICP equipment has been moved to a new informative <u>Annex B</u>;
- the text has been revised for editorial corrections.

A list of all parts in the ISO 5398 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

## Introduction

The ISO 5398 series comprises four parts, each describing methods suitable for the determination of the chromic oxide content in leather. The different techniques have been described to reflect the variations in industrial practice compared with the more sensitive analytical equipment available for test laboratories. Variations also exist in the range of chromic oxide that the methods are deemed suitable to quantify.

This document describes a technique that is suitable for determining chromium more precisely than those described in ISO 5398-1 and ISO 5398-2. It requires the use of sophisticated analytical equipment, such as inductively coupled plasma (ICP).

# Leather — Chemical determination of chromic oxide content —

## Part 4: Quantification by inductively coupled plasma (ICP)

## 1 Scope

This document describes a method for the determination of chromium in aqueous solution obtained from leather. This is an analysis for total chromium in leather; it is not compound specific or specific to its oxidation state.

This method describes the determination of chromium by inductively coupled plasma (ICP) and is applicable to leathers which are expected to have chromic oxide contents in excess of 1 mg/kg. Two techniques for the preparation of the solution to be analysed are included. In the event of dispute, the wet oxidation technique is intended to be used.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, Leather — Chemical, physical and mechanical and fastness tests — Sampling location

ISO 3696, Water for analytical laboratory use — Specification and test methods

ISO 4044, Leather — Chemical tests — Preparation of chemical test samples

ISO 4684, Leather — Chemical tests — Determination of volatile matter

ISO 11885, Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)

ISO 17294-2, Water quality — Application of inductively coupled plasma mass spectrometry (ICP-MS) — Part 2: Determination of selected elements including uranium isotopes

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

#### 3.1

#### chromic oxide content

amount of chromium in leather, determined by this method and reported as chromic oxide

Note 1 to entry: The chromic oxide content is expressed in milligrams per kilogram (mg/kg), based on dry matter.



This is a free preview. Purchase the entire publication at the link below:

**Product Page** 

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation