



NSAI
Standards

Irish Standard Recommendation
S.R. CEN ISO/TS 19590:2019

Nanotechnologies - Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry (ISO/TS 19590:2017)

S.R. CEN ISO/TS 19590:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

CEN ISO/TS 19590:2019

Published:

2019-02-27

*This document was published
under the authority of the NSAI
and comes into effect on:*

2019-03-17

ICS number:

07.120

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

S.R. CEN ISO/TS 19590:2019 is the adopted Irish version of the European Document CEN ISO/TS 19590:2019, Nanotechnologies - Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry (ISO/TS 19590:2017)

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

TECHNICAL SPECIFICATION

CEN ISO/TS 19590

SPÉCIFICATION TECHNIQUE

TECHNISCHE SPEZIFIKATION

February 2019

ICS 07.120

English Version

**Nanotechnologies - Size distribution and concentration of
inorganic nanoparticles in aqueous media via single
particle inductively coupled plasma mass spectrometry
(ISO/TS 19590:2017)**

Nanotechnologies - Distribution granulométrique et
concentration de nanoparticules inorganiques en
milieu aqueux par spectrométrie de masse à plasma
induit en mode particule unique (ISO/TS 19590:2017)

Nanotechnologien - Größenverteilung und
Konzentration anorganischer Nanopartikel in
wässrigen Medien durch Massenspektrometrie an
Einzelpartikeln mit induktiv gekoppeltem Plasma
(ISO/TS 19590:2017)

This Technical Specification (CEN/TS) was approved by CEN on 4 February 2019 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

CEN ISO/TS 19590:2019 (E)

Contents	Page
European foreword.....	3

European foreword

The text of ISO/TS 19590:2017 has been prepared by Technical Committee ISO/TC 229 "Nanotechnologies" of the International Organization for Standardization (ISO) and has been taken over as CEN ISO/TS 19590:2019 by Technical Committee CEN/TC 352 "Nanotechnologies" the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO/TS 19590:2017 has been approved by CEN as CEN ISO/TS 19590:2019 without any modification.

This page is intentionally left blank

TECHNICAL SPECIFICATION

**ISO/TS
19590**

First edition
2017-03

Nanotechnologies — Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry

*Nanotechnologies - Distribution de taille et concentration de
nanoparticules inorganiques en milieu aqueux par spectrométrie de
masse à plasma induit en mode particule unique*



Reference number
ISO/TS 19590:2017(E)

© ISO 2017

ISO/TS 19590:2017(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Abbreviated terms	2
5 Conformance	2
6 Procedure	3
6.1 Principle.....	3
6.2 Apparatus and equipment.....	3
6.3 Chemicals, reference materials and reagents.....	3
6.3.1 Chemicals.....	3
6.3.2 Reference materials.....	3
6.3.3 Reagents.....	4
6.4 Samples.....	4
6.4.1 Amount of sample.....	4
6.4.2 Sample dilution.....	5
6.5 Instrumental settings and performance check.....	5
6.5.1 Settings of the ICP-MS system.....	5
6.5.2 Checking the performance of the ICP-MS system.....	5
6.6 Determination of the transport efficiency.....	6
6.6.1 Determination of transport efficiency based on measured particle frequency.....	6
6.6.2 Determination of transport efficiency based on measured particle size.....	7
6.7 Determination of the linearity of response.....	8
6.8 Determination of the blank level.....	8
6.9 Analysis of aqueous suspension.....	8
6.10 Data conversion.....	9
7 Results	9
7.1 Calculations.....	9
7.1.1 Calculation of the transport efficiency.....	10
7.1.2 Calculation of the ICP-MS response.....	10
7.1.3 Calculation of particle concentration and size.....	10
7.1.4 Calculation of the particle concentration detection limit.....	11
7.1.5 Calculation of the particle size detection limit.....	12
7.1.6 Calculation of ionic concentration.....	13
7.2 Performance criteria.....	13
7.2.1 Transport efficiency.....	13
7.2.2 Linearity of the calibration curve.....	13
7.2.3 Blank samples.....	13
7.2.4 Number of detected particles.....	13
8 Test report	13
Annex A (informative) Calculation spreadsheet	15
Bibliography	19

ISO/TS 19590:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by ISO/TC 229, *Nanotechnologies*.

Introduction

This document was developed in response to the worldwide demand of suitable methods for the detection and characterization of nanoparticles in food and consumer products. Products based on nanotechnology or containing engineered nanoparticles are already in use and beginning to impact the food-associated industries and markets. As a consequence, direct and indirect consumer exposure to engineered nanoparticles (in addition to natural nanoparticles) becomes more likely. The detection of engineered nanoparticles in food, in samples from toxicology and in exposure studies therefore becomes an essential part in understanding the potential benefits, as well as the potential risks, of the application of nanoparticles.

Single particle inductively coupled plasma mass spectrometry (spICP-MS) is a method capable of detecting single nanoparticles at very low concentrations. The aqueous sample is introduced continuously into a standard ICP-MS system that is set to acquire data with a high time resolution (i.e. a short dwell time). Following nebulization, a fraction of the nanoparticles enters the plasma where they are atomized and the individual atoms ionized. For every particle atomized, a cloud of ions results. This cloud of ions is sampled by the mass spectrometer and since the ion density in this cloud is high, the signal pulse is high compared to the background (or baseline) signal if a high time resolution is used. A typical run time is 30 s to 200 s and is called a “time scan.” The mass spectrometer can be tuned to measure any specific element, but due to the high time resolution, typically only one m/z value will be monitored during a run (with the current instruments).

The number of pulses detected per second is directly proportional to the number of nanoparticles in the aqueous suspension that is being measured. To calculate concentrations, the transport efficiency has to be determined first using a reference nanoparticle. The intensity of the pulse and the pulse area are directly proportional to the mass of the measured element in a nanoparticle, and thereby to the nanoparticle’s diameter to the third power (i.e. assuming a spherical geometry for the nanoparticle). This means that for any increase of a particle’s diameter, the response will increase to the third power and therefore a proper validation of the response for each size range of each composition of nanoparticle is required. Calibration is best performed using a reference nanoparticle material; however, such materials are often not available. Therefore, calibration in this procedure is performed using ionic standard solutions of the measured element under the same analytical condition.

The data can be processed by commercially available software or it can be imported in a custom spreadsheet program to calculate the number and mass concentration, the size (the spherical equivalent diameter) and the corresponding number-based size distribution of the nanoparticles. In addition, mass concentrations of ions present in the same sample can be determined from the same data.

The interested reader can consult References [1] to [4] for further information.

Nanotechnologies — Size distribution and concentration of inorganic nanoparticles in aqueous media via single particle inductively coupled plasma mass spectrometry

1 Scope

This document specifies a method for the detection of nanoparticles in aqueous suspensions and characterization of the particle number and particle mass concentration and the number-based size distribution using ICP-MS in a time-resolved mode to determine the mass of individual nanoparticles and ionic concentrations.

The method is applicable for the determination of the size of inorganic nanoparticles (e.g. metal and metal oxides like Au, Ag, TiO₂, BVO₄, etc.), with size ranges of 10 nm to 100 nm (and larger particles up to 1 000 nm to 2 000 nm) in aqueous suspensions. Metal compounds other than oxides (e.g. sulfides, etc.), metal composites or coated particles with a metal core can be determined if the chemical composition and density are known. Particle number concentrations that can be determined in aqueous suspensions range from 10⁶ particles/L to 10⁹ particles/L which corresponds to mass concentrations in the range of approximately 1 ng/L to 1 000 ng/L (for 60 nm Au particles). Actual numbers depend on the type of mass spectrometer used and the type of nanoparticle analysed.

In addition to the particle concentrations, ionic concentrations in the suspension can also be determined. Limits of detection are comparable with standard ICP-MS measurements. Note that nanoparticles with sizes smaller than the particle size detection limit of the spICP-MS method may be quantified as ionic.

The method proposed in this document is not applicable for the detection and characterization of organic or carbon-based nanoparticles like encapsulates, fullerenes and carbon nanotubes (CNT). In addition, it is not applicable for elements other than carbon and that are difficult to determine with ICP-MS. Reference [5] gives an overview of elements that can be detected and the minimum particle sizes that can be determined with spICP-MS.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 80004-1, *Nanotechnologies — Vocabulary — Part 1: Core terms*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— IEC Electropedia: available at <http://www.electropedia.org/>

— ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

nanoparticle

nano-object with all three external dimensions in the nanoscale

[SOURCE: ISO/TS 80004-2:2015, modified]

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-