



NSAI
Standards

Irish Standard
I.S. EN 17199-5:2019

Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA or other respirable particles - Part 5: Vortex shaker method

I.S. EN 17199-5:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 17199-5:2019

Published:

2019-03-27

*This document was published
under the authority of the NSAI
and comes into effect on:*

2019-04-14

ICS number:

13.040.30

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 17199-5:2019 is the adopted Irish version of the European Document EN 17199-5:2019, Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA or other respirable particles - Part 5: Vortex shaker method

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

EUROPEAN STANDARD

EN 17199-5

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2019

ICS 13.040.30

English Version

Workplace exposure - Measurement of dustiness of bulk materials that contain or release respirable NOAA or other respirable particles - Part 5: Vortex shaker method

Exposition sur les lieux de travail - Mesurage du pouvoir de resuspension des matériaux en vrac contenant ou émettant des nano-objets et leurs agrégats et agglomérats (NOAA) ou autres particules en fraction alvéolaire - Partie 5: Méthode impliquant l'utilisation d'un agitateur vortex

Exposition am Arbeitsplatz - Messung des Staubungsverhaltens von Schüttgütern, die Nanoobjekte oder Submikrometerpartikel enthalten oder freisetzen - Teil 5: Verfahren mit Vortex-Schüttler

This European Standard was approved by CEN on 8 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	7
3 Terms and definitions	7
4 Symbols and abbreviations	8
5 Principle	8
6 Equipment	10
6.1 General.....	10
6.2 Test apparatus.....	12
6.2.1 Vortex shaker apparatus.....	12
6.2.2 Cylindrical container	12
6.2.3 Humidification system of incoming and dilution air.....	15
6.2.4 Sampling line for the measurement of the respirable dustiness mass fraction.....	15
6.2.5 Sampling line for other measurements.....	17
6.2.6 Conductive flexible tubing, carbon impregnated	19
6.2.7 Respirable cyclone, made of stainless steel.....	19
6.2.8 Air sampling cassette.....	19
6.2.9 Condensation particle counter (CPC), with alcohol as working fluid.....	20
6.2.10 Time- and size-resolving aerosol instrument.....	20
6.2.11 Aerosol sampler for analytical electron microscopy analysis.....	20
6.2.12 Analytical balance, capable of weighing to a resolution of 10 µg	21
6.2.13 Microbalance, capable of weighing to a resolution of 1 µg	21
6.2.14 Filters for gravimetric analysis.....	21
6.2.15 Micro-centrifuge tubes.....	21
7 Requirements	21
7.1 General.....	21
7.2 Engineering control measures	21
7.3 Conditioning of the test material.....	21
7.3.1 General.....	21
7.3.2 Specified conditions	22
7.3.3 As-received conditions.....	22
7.4 Conditioning of the test equipment.....	22
8 Preparation	22
8.1 Test sample	22
8.2 Moisture content of the test material	23
8.3 Bulk density of the test material	23
8.4 Preparation of test apparatus	23
8.5 Aerosol instruments and aerosol samplers.....	23
9 Test procedure	23
10 Evaluation of data	26
10.1 Respirable dustiness mass fraction.....	26

10.2	Number-based dustiness index, number-based emission rate and modal aerodynamic equivalent diameters of the particle size distribution	26
10.2.1	General	26
10.2.2	Number-based dustiness index	27
10.2.3	Number-based emission rate	27
10.2.4	Modal aerodynamic equivalent diameters of the number-based particle size distribution	27
10.3	Morphological and chemical characterization of the particles.....	28
11	Test report	29
Annex A (informative)	Pictures illustrating some of the equipment of the method	30
Annex B (informative)	Examples of TEM images obtained with the vortex shaker method.....	35
Annex C (informative)	Motivation for development of the vortex shaker method	36
Bibliography	37

EN 17199-5:2019 (E)

European foreword

This document (EN 17199-5:2019) has been prepared by Technical Committee CEN/TC 137 “Assessment of workplace exposure to chemical and biological agents”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2019 and conflicting national standards shall be withdrawn at the latest by September 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Dustiness measurement and characterization provide users (e.g. manufacturers, producers, occupational hygienists and workers) with information on the potential for dust emissions when bulk material is handled or processed in workplaces. They provide the manufactures of bulk materials containing NOAA with information that can help to improve their products and reduce their dustiness. It allows the users of the bulk materials containing NOAA to assess the controls and precautions required for handling and working with the material and the effects of pre-treatments (e.g. modify surface properties or chemistry). It also allows the users to select less dusty products, if available. The particle size distribution of the aerosol and the morphology and chemical composition of its particles can be used by occupational hygienists, scientists and regulators to further characterize the aerosol in terms of particle size distribution and chemical composition and to thus aid users to evaluate and control the health risk of airborne dust.

This document gives details on the design and operation of the vortex shaker test method that measures the dustiness of bulk materials that contain or release respirable NOAA or other respirable particles in terms of dustiness indices or emission rates. Dustiness indices as well as emission rates can be determined number- or mass-based. In addition the test method characterizes the released aerosol by measuring the particle size distribution using direct-reading aerosol instruments and collects samples for off-line analysis (as required) for their morphology and their chemical composition.

The vortex shaker method is useful for addressing the ability of bulk materials including nanomaterials (in powder form), to release airborne particles (aerosol) during agitation, the so-called dustiness.

The vortex shaker method provides a simulation of operation or processes where the agitation mechanism delivering energy to the powder to release airborne particles is the vibration or shaking mechanism. Vibration and shaking are mechanisms that are often found in industry, either voluntarily or involuntarily. Many surfaces receiving powders are vibrating or shaking, as for example during powder transportation by belt feeder or vibrating conveyor. Moreover, by providing an energetic aerosolization, the vortex shaker method provides even a simulation of the worst-case scenario in a workplace, as for example the (non-recommended) practice of cleaning contaminated worker coveralls and dry work surfaces with compressed air.

The vortex shaker method presented here differs from the rotating drum, the continuous drop and the small rotating drum methods presented in EN 17199-2 [1], EN 17199-3 [2] and EN 17199-4 [3] respectively. The rotating drum and small rotating drum methods perform, both, repeated agitation of the same sample nanomaterial while the continuous drop method simulates continuous feed of a nanomaterial. The method described in this document, in turn, provides an agitation to a small test sample of powder.

This document was developed based on the results of pre-normative research [4]. This project investigated the dustiness of ten bulk materials (including nine bulk nanomaterials) with the intention to test as wide a range of bulk materials as possible in terms of magnitude of dustiness, chemical composition and primary particle size distribution as indicated by a large range in specific surface area.

EN 17199-5:2019 (E)

1 Scope

This document describes the methodology for measuring and characterizing the dustiness of bulk materials that contain or release respirable NOAA or other respirable particles, under standard and reproducible conditions and specifies for that purpose the vortex shaker method.

This document specifies the selection of instruments and devices and the procedures for calculating and presenting the results. It also gives guidelines on the evaluation and reporting of the data.

The methodology described in this document enables

- a) the measurement of the respirable dustiness mass fraction,
- b) the measurement of the number-based dustiness index of respirable particles in the particle size range from about 10 nm to about 1 μm ,
- c) the measurement of the number-based emission rate of respirable particles in the particle size range from about 10 nm to about 1 μm ,
- d) the measurement of the number-based particle size distribution of the released respirable aerosol in the particle size range from about 10 nm to 10 μm ,
- e) the collection of released airborne particles in the respirable fraction for subsequent observations and analysis by electron microscopy.

This document is applicable to the testing of a wide range of bulk materials including nanomaterials in powder form.

NOTE 1 With slightly different configurations of the method specified in this document, dustiness of a series of carbon nanotubes has been investigated ([5] to [10]). On the basis of this published work, it can be assumed that the vortex shaker method is also applicable to nanofibres and nanoplates.

This document is not applicable to millimetre-sized granules or pellets containing nano-objects in either unbound, bound uncoated and coated forms.

NOTE 2 The restrictions with regard to the application of the vortex shaker method on different kinds of nanomaterials result from the configuration of the vortex shaker apparatus as well as from the small size of the test sample required. Eventually, if future work will be able to provide accurate and repeatable data demonstrating that an extension of the method applicability is possible, the intention is to revise this document and to introduce further cases of method application.

NOTE 3 As observed in the pre-normative research project [4], the vortex shaker method specified in this document provides a more energetic aerosolization than the rotating drum, the continuous drop and the small rotating drum methods specified in EN 17199-2 [1], EN 17199-3 [2] and EN 17199-4 [3], respectively. The vortex shaker method can better simulate high energy dust dispersion operations or processes where vibration or shaking is applied or even describe a worst case scenario in a workplace, including the (non-recommended) practice of cleaning contaminated worker coveralls and dry work surfaces with compressed air.

NOTE 4 Currently no classification scheme in terms of dustiness indices or emission rates has been established according to the vortex shaker method. Eventually, when a large number of measurement data has been obtained, the intention is to revise the document and to introduce such a classification scheme, if applicable.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-