

Irish Standard I.S. EN 1849-2:2019

Flexible sheets for waterproofing -Determination of thickness and mass per unit area - Part 2: Plastics and rubber sheets for roof waterproofing

 $\ensuremath{\mathbb C}$ CEN 2019 $\hfill No copying without NSAI permission except as permitted by copyright law.$

I.S. EN 1849-2:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on: EN 1849-2:2018

Published: 2019-07-10

This document was published under the authority of the NSAI and comes into effect on:

2019-07-28

ICS number:

91.100.50

NOTE: If blank see CEN/CENELEC cover page

NSAI	T +353 1 807 3800	Sales:
1 Swift Square,	F +353 1 807 3838	T +353 1 857 6730
Northwood, Santry	E standards@nsai.ie	F +353 1 857 6729
Dublin 9	W NSAI.ie	W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 1849-2:2019 is the adopted Irish version of the European Document EN 1849-2:2019, Flexible sheets for waterproofing - Determination of thickness and mass per unit area - Part 2: Plastics and rubber sheets for roof waterproofing

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This is a free page sample. Access the full version online.

This page is intentionally left blank

This is a free page sample. Access the full version online. I.S. EN 1849-2:2019

EUROPEAN STANDARD NORME EUROPÉENNE

EN 1849-2

EUROPÄISCHE NORM

July 2019

ICS 91.100.50

Supersedes EN 1849-2:2009

English Version

Flexible sheets for waterproofing - Determination of thickness and mass per unit area - Part 2: Plastics and rubber sheets for roof waterproofing

Feuilles souples d'étanchéité - Détermination de l'épaisseur et de la masse surfacique - Partie 2 : Feuilles d'étanchéité de toiture plastiques et élastomères Abdichtungsbahnen - Bestimmung der Dicke und der flächenbezogenen Masse - Teil 2: Kunststoff- und Elastomerbahnen für Dachabdichtungen

This European Standard was approved by CEN on 22 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

This is a free page sample. Access the full version online. $I.S.\ EN\ 1849-2:2019$

EN 1849-2:2019 (E)

Contents

Page

Europe	ean foreword	3
Introd	uction	4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Sampling	7
5	Determination of thickness	
5.1	Principle	8
5.2	Apparatus	8
5.2.1	Mechanical measuring device	8
5.2.2	Optical measuring device	8
5.3	Test specimens	8
5.4	Procedure	9
5.4.1	Mechanical measurement	9
5.4.2	Optical measurement	10
5.5	Expression of results	10
6	Determination of mass per unit area	10
6.1	Principle	10
6.2	Apparatus	10
6.3	Test specimens	10
6.4	Procedure	10
6.5	Expression of results	10
7	Test report	10
Annex	A (informative) Example of the cut cross-section of a fleece backed membrane	12

European foreword

This document (EN 1849-2:2019) has been prepared by Technical Committee CEN/TC 254 "Flexible sheets for waterproofing", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2020, and conflicting national standards shall be withdrawn at the latest by January 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1849-2:2009.

Compared with EN 1849-2:2009 the following changes have been made in EN 1849-2:2019:

- the "overall thickness" and "effective thickness" has been replaced by:
 - mechanical effective thickness (d_{effm});
 - optical effective thickness (d_{effo});
 - mechanical overall thickness (d_m) ;
 - optical overall thickness (d_0) ;
- Figure 1 and Figure 2 have been replaced by new Figure 1 a-d;
- Table 1 in 5.3 has been removed;
- Figure 3 has been updated;
- a new Figure 2 has been introduced in 5.2.1;
- Figure A.1 has been replaced by a new one.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This European Standard is intended for characterisation of plastic and rubber sheets as manufactured or supplied before use. This test method relates exclusively to products or to their components where appropriate, and not to waterproofing membrane systems composed of such products and installed in the works.

This test is intended to be used in conjunction with European Standard "Definition and Characteristics" for plastic and rubber sheets for roof waterproofing (EN 13956).

1 Scope

This document specifies methods for the determination of the thickness and mass per unit area of plastic and rubber sheets for roof waterproofing.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13416, Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Rules for sampling

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at <u>http://www.iso.org/obp</u>

3.1

surface texture

textured pattern on one or both surfaces of the sheet together creating a difference between the effective and overall thickness not exceeding 0,15 mm

Note 1 to entry: See Figure 1 a) key 8.

3.2

surface profile (surface structure)

raised area on the surface of the sheet creating a difference between the effective and overall thickness exceeding $0,15~\mathrm{mm}$

Note 1 to entry: See Figure 1 c) key 9.

3.3

mechanical effective thickness (d_{effm})

thickness of the sheet providing the waterproofing measured with a mechanical measuring device

3.4

backing

layer of woven or non-woven fabric of synthetic or mineral fibres or other materials, fixed to the bottom of the sheet

Note 1 to entry: See Figure 1 b) key 7.

3.5

optical effective thickness (d_{effo})

thickness of the sheet providing the waterproofing measured with an optical measuring device



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation