



NSAI
Standards

Irish Standard
I.S. EN 13523-19:2019

Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing

I.S. EN 13523-19:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 13523-19:2019

Published:

2019-09-18

*This document was published
under the authority of the NSAI
and comes into effect on:*

2019-10-07

ICS number:

25.220.60

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 13523-19:2019 is the adopted Irish version of the European Document EN 13523-19:2019, Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

EUROPEAN STANDARD

EN 13523-19

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2019

ICS 25.220.60

Supersedes EN 13523-19:2011

English Version

Coil coated metals - Test methods - Part 19: Panel design and method of atmospheric exposure testing

Tôles prélaquées - Méthodes d'essai - Partie 19 :
Modèles de panneaux et méthode d'essai pour les
essais d'exposition à l'extérieur

Bandbeschichtete Metalle - Prüfverfahren - Teil 19:
Probenplatten und Verfahren zur Freibewitterung

This European Standard was approved by CEN on 1 July 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Apparatus.....	6
5 Sampling.....	7
6 Test panels.....	7
6.1 General.....	7
6.2 Panel preparation	7
6.3 Panel design	7
7 Procedure.....	9
8 Expression of results.....	9
Annex A (informative) Parameters that can influence exposure results.....	14
Annex B (informative) European outdoor exposure sites recommended by ECCA	16
Bibliography.....	17

European foreword

This document (EN 13523-19:2019) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2020, and conflicting national standards shall be withdrawn at the latest by March 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13523-19:2011.

The main changes compared to EN 13523-19:2011 are:

- a) in 4.1 some additional information has been added for the rack design;
- b) in 6.3.4 some information on how to use panels 1, 2 and 3 has been added;
- c) the test site for continental industrial climate has been deleted from Annex B;
- d) the text has been editorially revised and the normative references have been updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*

EN 13523-19:2019 (E)

- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*
- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasma test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

In the past, it has been common practice in the northern hemisphere to expose test panels at 45° facing South.

Whilst this orientation is appropriate for degradation of the organic coating, investigations have shown that it has little bearing on the overall corrosion performance of the product when used in building applications.

For example, the 45° facing South exposure takes no account of

- overhangs which produce unwashed areas;
- sheet overlaps;
- low pitched roofing, etc.

The Outdoor Exposure Committee of European Coil Coating Association (ECCA) designed an exposure system which aligns more closely with “real life” situations and which is the basis of this part of EN 13523.

Three panel orientations are specified:

- a) PANEL 1: 45° to horizontal facing South. The traditional orientation for evaluation of organic coatings: colour change, gloss change, chalking, etc.;
- b) PANEL 2: 90° to horizontal facing North, with an overhang for evaluating general corrosion on side cladding particularly in unwashed areas;
- c) PANEL 3: 5° to horizontal facing South. This panel which includes an overlap is principally for evaluating general corrosion in roofing applications.

The selection of one or more panel designs and their corresponding orientations will be chosen according to the exposure data required.

The multiplicity of panel types and exposure conditions can be somehow confusing when trying to compare results from systems that were characterized in different conditions. The normative recommendation is to use PANEL 1: 45° to horizontal facing South for characterizing UV resistance. PANEL 2 and PANEL 3 are more suitable for evaluation of corrosion resistance.

EN 13523-19:2019 (E)

1 Scope

This part of EN 13523 specifies the panel design and describes the procedure for determining the resistance to outdoor exposure of an organic coating on a metallic substrate.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0, *Coil coated metals — Test methods — Part 0: General introduction*

EN 13523-2, *Coil coated metals — Test methods — Part 2: Gloss*

EN 13523-3, *Coil coated metals — Test methods — Part 3: Colour difference — Instrumental comparison*

EN 13523-7:2014, *Coil coated metals — Test methods — Part 7: Resistance to cracking on bending (T-bend test)*

EN 13523-14, *Coil coated metals — Test methods — Part 14: Chalking (Helmen method)*

EN 13523-21, *Coil coated metals — Test methods — Part 21: Evaluation of outdoor exposed panels*

EN ISO 17872, *Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing (ISO 17872)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Apparatus

4.1 Rack design

The typical rack configuration accommodating the three elevations is shown in Figures 4 a), 4 b) and 5. The actual design and material of manufacture is at the discretion of the individual taking into consideration the corrosivity on the exposure site. Similarly the method of fixing the panels to the rack is up to the individual, but they shall be fixed in such a way as to avoid bimetallic corrosion. The material to provide the overhang on the North-facing panel shall be manufactured from an inert rigid material such as polymethyl methacrylate¹ and shall give an overhang on the panel of approximately 65 mm (see 2 in Figure 4 a)).

¹ e.g. Perspex. Perspex is the trade name of a product supplied by Perspecs Distribution Ltd. This information is given for the convenience of users of this document and does not constitute an endorsement of the product named. Equivalent products may be used if they can be shown to lead to the same results.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-