



NSAI
Standards

Irish Standard
I.S. EN IEC 61788-4:2020

Superconductivity - Part 4: Residual resistance ratio measurement - Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

I.S. EN IEC 61788-4:2020

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN IEC 61788-4:2020

Published:

2020-05-15

*This document was published
under the authority of the NSAI
and comes into effect on:*

2020-06-03

ICS number:

17.220.20

29.050

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN IEC 61788-4:2020 is the adopted Irish version of the European Document EN IEC 61788-4:2020, Superconductivity - Part 4: Residual resistance ratio measurement - Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

EUROPEAN STANDARD

EN IEC 61788-4

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2020

ICS 17.220.20; 29.050

Supersedes EN 61788-4:2016 and all of its amendments
and corrigenda (if any)

English Version

**Superconductivity - Part 4: Residual resistance ratio
measurement - Residual resistance ratio of Nb-Ti and Nb₃Sn
composite superconductors
(IEC 61788-4:2020)**

Supraconductivité - Partie 4: Mesurage du rapport de
résistance résiduelle - Rapport de résistance résiduelle des
composites supraconducteurs de Nb-Ti et de Nb₃Sn
(IEC 61788-4:2020)

Supraleitfähigkeit - Teil 4: Messung des
Restwiderstandsverhältnisses - Restwiderstandsverhältnis
von Nb-Ti und Nb₃Sn Verbundsupraleitern
(IEC 61788-4:2020)

This European Standard was approved by CENELEC on 2020-04-24. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN IEC 61788-4:2020 (E)

European foreword

The text of document 90/448/FDIS, future edition 5 of IEC 61788-4, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 61788-4:2020.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2021-01-24
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2023-04-24

This document supersedes EN 61788-4:2016 and all of its amendments and corrigenda (if any).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 61788-4:2020 was approved by CENELEC as a European Standard without any modification.

Annex ZA

(normative)

Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050-815	-	International Electrotechnical Vocabulary - Part 815: Superconductivity	-	-

This page is intentionally left blank



IEC 61788-4

Edition 5.0 2020-03

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Superconductivity –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

Supraconductivité –

Partie 4: Mesurage du rapport de résistance résiduelle – Rapport de résistance résiduelle des composites supraconducteurs de Nb-Ti et de Nb₃Sn



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.



IEC 61788-4

Edition 5.0 2020-03

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Superconductivity –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

Supraconductivité –

Partie 4: Mesurage du rapport de résistance résiduelle – Rapport de résistance résiduelle des composites supraconducteurs de Nb-Ti et de Nb₃Sn

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 17.220.20; 29.050

ISBN 978-2-8322-7916-8

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Principle	8
5 Apparatus	8
5.1 Material of measurement mandrel or of measurement base plate	8
5.2 Diameter of the measurement mandrel and length of the measurement base plate	9
5.3 Cryostat for the resistance (R_2) measurement	9
6 Specimen preparation	9
7 Data acquisition and analysis	9
7.1 Resistance (R_1) at room temperature	9
7.2 Resistance (R_2 or R_2^*) just above the superconducting transition	10
7.2.1 Correction of strain effect	10
7.2.2 Data acquisition of cryogenic resistance	10
7.2.3 Optional acquisition methods	12
7.3 Correction on measured R_2^* of Nb-Ti composite superconductor for bending strain	12
7.4 Residual resistance ratio (RRR)	12
8 Uncertainty and stability of the test method	13
8.1 Temperature	13
8.2 Voltage	13
8.3 Current	13
8.4 Dimension	13
9 Test report	13
9.1 RRR value	13
9.2 Specimen	14
9.3 Test conditions	14
9.3.1 Measurements of R_1 and R_2	14
9.3.2 Measurement of R_1	15
9.3.3 Measurement of R_2	15
Annex A (informative) Additional information relating to the measurement of RRR	16
A.1 Recommendation on specimen mounting orientation	16
A.2 Alternative methods for increasing temperature of specimen above superconducting transition temperature	16
A.3 Alternative measurement methods of R_2 or R_2^*	16
A.4 Bending strain dependency of RRR for Nb-Ti composite superconductor	19
A.5 Procedure of correction of bending strain effect	22
Annex B (informative) Uncertainty considerations	24
B.1 Overview	24
B.2 Definitions	24

B.3	Consideration of the uncertainty concept	24
B.4	Uncertainty evaluation example for IEC TC 90 standards	26
Annex C (informative)	Uncertainty evaluation in test method of RRR for Nb-Ti and Nb ₃ Sn composite superconductors	28
C.1	Evaluation of uncertainty	28
C.2	Summary of round robin test of RRR of a Nb-Ti composite superconductor	31
C.3	Reason for large COV value in the intercomparison test on Nb ₃ Sn composite superconductor	32
Bibliography	34
Figure 1	– Relationship between temperature and resistance	8
Figure 2	– Voltage versus temperature curves and definitions of each voltage	11
Figure A.1	– Definition of voltages	18
Figure A.2	– Bending strain dependency of RRR value for pure Cu matrix of Nb-Ti composite superconductors (comparison between measured values and calculated values)	20
Figure A.3	– Bending strain dependency of RRR value for round Cu wires	20
Figure A.4	– Bending strain dependency of normalized RRR value for round Cu wires	21
Figure A.5	– Bending strain dependency of RRR value for rectangular Cu wires	21
Figure A.6	– Bending strain dependency of normalized RRR value for rectangular Cu wires	22
Figure C.1	– Distribution of observed r_{RRR} of Cu/Nb-Ti composite superconductor	32
Table A.1	– Minimum diameter of the measurement mandrel for round wires	22
Table A.2	– Minimum diameter of the measurement mandrel for rectangular wires	22
Table B.1	– Output signals from two nominally identical extensometers	25
Table B.2	– Mean values of two output signals	25
Table B.3	– Experimental standard deviations of two output signals	25
Table B.4	– Standard uncertainties of two output signals	26
Table B.5	– COV values of two output signals	26
Table C.1	– Uncertainty of each measurement	31
Table C.2	– Obtained values of RRR for six Nb ₃ Sn specimens	32
Table C.3	– Average, standard deviation and coefficient of variation for six specimens	33

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-4 has been prepared by IEC technical committee 90: Superconductivity.

This fifth edition cancels and replaces the fourth edition published in 2016. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) change in the suitable distance of voltage taps on the specimen for reliable measurement,
- b) new report on the result of the round robin test of the residual resistance ratio of Nb₃Sn superconductors that proves the validity of the measurement method in this standard,
- c) revision of the confusing definitions of the copper ratio and copper fraction.

The text of this standard is based on the following documents:

FDIS	Report on voting
90/448/FDIS	90/451/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

Copper, Cu/Cu-Ni or aluminium is used as matrix material in Ni-Ti and Nb₃Sn composite superconductors and works as an electrical shunt when the superconductivity is interrupted. It also contributes to recovery of the superconductivity by conducting heat generated in the superconductor to the surrounding coolant. The cryogenic-temperature resistivity of copper is an important quantity, which influences the stability and AC losses of the superconductor. The residual resistance ratio is defined as a ratio of the resistance of the superconductor at room temperature to that just above the superconducting transition.

This document specifies the test method for residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors. The curve method is employed for the measurement of the resistance just above the superconducting transition. Other methods are described in Clause A.3.

SUPERCONDUCTIVITY –

Part 4: Residual resistance ratio measurement – Residual resistance ratio of Nb-Ti and Nb₃Sn composite superconductors

1 Scope

This part of IEC 61788 specifies a test method for the determination of the residual resistance ratio (RRR) of Nb-Ti and Nb₃Sn composite superconductors with Cu, Cu-Ni, Cu/Cu-Ni and Al matrix in a strain-free condition and zero external magnetic field. This method is intended for use with superconductor specimens that have a monolithic structure with rectangular or round cross-section, RRR value less than 350, and cross-sectional area less than 3 mm². In the case of Nb₃Sn, the specimens have received a reaction heat-treatment.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary (IEV) – Part 815: Superconductivity* (available at: www.electropedia.org)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-815 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

residual resistance ratio

RRR

ratio of resistance at room temperature to the resistance just above the superconducting transition

Note 1 to entry: This note applies to the French language only.

Note 2 to entry: In this document for Nb-Ti and Nb₃Sn composite superconductors, the room temperature is defined as 293 K (20 °C), and the residual resistance ratio is obtained in Formula (1), where the resistance (R_1) at 293 K is divided by the resistance (R_2) just above the superconducting transition.

$$r_{\text{RRR}} = \frac{R_1}{R_2} \quad (1)$$

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-