



**NSAI**  
Standards

Irish Standard  
I.S. EN 73:2020

Durability of wood and wood-based products - Accelerated ageing of treated wood prior to biological testing - Evaporative ageing procedure

**I.S. EN 73:2020**

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

*This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):*

*NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.*

*This document is based on:*

EN 73:2020

*Published:*

2020-08-12

*This document was published under the authority of the NSAI and comes into effect on:*

2020-08-30

ICS number:

71.100.50

NOTE: If blank see CEN/CENELEC cover page

NSAI  
1 Swift Square,  
Northwood, Santry  
Dublin 9

T +353 1 807 3800  
F +353 1 807 3838  
E standards@nsai.ie  
W NSAI.ie

Sales:  
T +353 1 857 6730  
F +353 1 857 6729  
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

## National Foreword

I.S. EN 73:2020 is the adopted Irish version of the European Document EN 73:2020, Durability of wood and wood-based products - Accelerated ageing of treated wood prior to biological testing - Evaporative ageing procedure

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

**Compliance with this document does not of itself confer immunity from legal obligations.**

*In line with international standards practice the decimal point is shown as a comma (,) throughout this document.*

This page is intentionally left blank

EUROPEAN STANDARD

EN 73

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2020

ICS 71.100.50

Supersedes EN 73:2014

English Version

## Durability of wood and wood-based products - Accelerated ageing of treated wood prior to biological testing - Evaporative ageing procedure

Durabilité du bois et des produits dérivés - Épreuves de vieillissement accéléré des bois traités avant essais biologiques - Épreuve d'évaporation

Dauerhaftigkeit von Holz und Holzprodukten - Beschleunigte Alterung von behandeltem Holz vor biologischen Prüfungen - Verdunstungsbeanspruchung

This European Standard was approved by CEN on 24 February 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>		<b>Page</b>
<b>European foreword</b> .....		<b>3</b>
<b>Introduction</b> .....		<b>4</b>
<b>1</b>	<b>Scope</b> .....	<b>5</b>
<b>2</b>	<b>Normative references</b> .....	<b>5</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>5</b>
<b>4</b>	<b>Principle</b> .....	<b>5</b>
<b>5</b>	<b>Equipment</b> .....	<b>5</b>
<b>6</b>	<b>Test specimens</b> .....	<b>6</b>
<b>6.1</b>	<b>Definition and origin</b> .....	<b>6</b>
<b>6.2</b>	<b>Number of test specimens</b> .....	<b>6</b>
<b>7</b>	<b>Procedure</b> .....	<b>6</b>
<b>7.1</b>	<b>Arrangement of the test specimens</b> .....	<b>6</b>
<b>7.2</b>	<b>Starting and adjustment of the apparatus</b> .....	<b>7</b>
<b>7.3</b>	<b>Ageing procedure</b> .....	<b>7</b>
<b>7.4</b>	<b>Exposure period in the tunnel</b> .....	<b>9</b>
<b>8</b>	<b>Destination of the test specimens after the evaporative ageing procedure</b> .....	<b>9</b>
<b>9</b>	<b>Reference to this document in biological test reports</b> .....	<b>9</b>
<b>Bibliography</b> .....		<b>10</b>

## **European foreword**

This document (EN 73:2020) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2021, and conflicting national standards shall be withdrawn at the latest by February 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 73:2014. Data using this version of EN 73 may still be used.

Compared to EN 73:2014 the following modifications have been made:

- change of title;
- inclusion of untreated wood, modified wood and wood-based panel products in the Scope;
- inclusion of a statement regarding the maximum period of time permitted between the completion of the ageing procedure and the start of the biological test procedure;
- inclusion of a requirement that this period of time be stated in the biological test report.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **EN 73:2020 (E)**

### **Introduction**

During its service life, preservative-treated wood can be exposed to conditions which may cause the volatilization and removal of the wood preservative thereby reducing its effectiveness.

This document provides a laboratory based method for ageing test specimens which are to be subject to biological testing.



## 1 Scope

This document specifies an evaporative ageing procedure, applicable to test specimens of wood and wood-based products which are subsequently subjected to biological tests.

NOTE The method can also be used for pre-conditioning of untreated wood, modified wood and wood-based panel products, whether they received preservative treatment or not.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

Test specimens are prepared for biological testing against either fungi or insects using the appropriate standards methods. Test specimens are exposed, for a specified period, in a dust-free current of air of a defined velocity and temperature.

## 5 Equipment

**5.1** A wind tunnel which is compartmented and fitted with devices for heating and distributing air.

The air shall be dust-free and shall not be polluted by chemical products which could have an effect on the results of biological testing.

The heating and distribution devices shall be such that the temperature and air velocity are maintained constant and uniform in each compartment.

The air leaving the tunnel shall be led away in such a manner that it cannot re-enter the tunnel.

**5.2** A device which:

- a) controls the temperature within the defined limits stated in 7.2;
- b) measures and records the air temperature within the defined limits as stated in 7.2.

**5.3** An anemometer capable to measuring air velocity of  $(1 \pm 0,3)$  m/s.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-