

AS/NZS 4456.11:2003(Reconfirmed)2023-10-03

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

RECONFIRMATION

OF

AS/NZS 4456.11:2003

**Masonry units, segmental pavers and flags—Methods of test
Method 11: Determining coefficients of expansion**

RECONFIRMATION NOTICE

Major stakeholders of this publication have reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 23 August 2023.

Approved for reconfirmation in New Zealand on behalf of the New Zealand Standards Approval Board on 01 November 2022.

Australian/New Zealand StandardTM**Masonry units, segmental pavers and flags—
Methods of test****Method 11: Determining coefficients of
expansion**

This Standard incorporates Amendment No. 1 (August 2004). The changes required by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.

1 SCOPE

This Standard sets out the methods for determining the coefficients of expansion of masonry units, segmental pavers and flags. The coefficients of expansion estimated by these tests represent the total 15 year expansion of either kiln-fresh or non-kiln-fresh fired clay units. Provision is also included for the estimation of past expansion and of residual expansion to 15 years, of units of any age.

2 REFERENCED DOCUMENTS

The following document is referred to in this Standard:

AS/NZS

4456	Masonry units, segmental pavers and flags—Methods of test
4456.0	Part 0: General introduction and list of methods
4456.1	Method 1: Sampling for testing
4456.2	Method 2: Assessment of mean and standard deviation

3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS/NZS 4456.0 apply.

4 NOTATION

The following symbols are used in this Standard:

L	= overall length of unit, in millimetres
Z_i	= initial gauge reading of reference bar (average of two readings), in millimetres = $(Z_1 + Z_2)/2$
Z_f	= final gauge reading of reference bar (average of two readings), in millimetres = $(Z_3 + Z_4)/2$
Y_i	= initial gauge reading of unit before steaming or refiring, in millimetres
Y_f	= final gauge reading of unit after steaming or refiring, in millimetres
dL	= change in length of the specimen due to steaming or refiring, in millimetres
dZ	= differences between final and initial gauge reading ($Z_i - Z_f$) of the reference bar, in millimetres
ΔL	= percentage change in length of each unit due to steaming or refiring

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-