

**IRISH STANDARD SPECIFICATION**

**SHEETING, SHEETS AND PILLOW  
SLIPS MADE OF MATERIALS OTHER  
THAN COTTON**

I.S. 2: Part 2: 1982

*Price Code C*

**INSTITUTE FOR INDUSTRIAL RESEARCH AND STANDARDS**

Ballymun Road, Dublin 9

Telegrams: Research, Dublin    Telex: 25449    Telephone: (01) 370101

## **DECLARATION**

OF

SPECIFICATION

ENTITLED

**SHEETING, SHEETS AND PILLOW SLIPS MADE OF MATERIALS  
OTHER THAN COTTON**

AS

**THE IRISH STANDARD SPECIFICATION FOR**

**SHEETING, SHEETS AND PILLOW SLIPS MADE OF MATERIALS  
OTHER THAN COTTON**

---

The Institute for Industrial Research and Standards in exercise of the power conferred by section 20 of the Industrial Research and Standards Act, 1961 (No. 20 of 1961), and with the consent of the Minister for Industry and Energy, hereby declares as follows:

1. This instrument may be cited as the Standard Specification (Sheeting, Sheets and Pillow Slips made of Materials other than Cotton) Declaration, 1982.

2. (1) The Specification set forth in the Schedule to this declaration is hereby declared to be the standard specification for Sheeting, Sheets and Pillow Slips made of Materials other than Cotton.

(2) The said standard specification may be cited as Irish Standard 2 : Part 2 : 1982 or as I.S. 2 : Part 2 : 1982.

## SCHEDULE

# Sheeting, Sheets and Pillow Slips made of Materials other than Cotton

## 1. SCOPE

Section 1 covers the requirements for four types of sheeting fabric (see Table 1) made of polyester/cotton, Irish linen and Irish linen/cotton. Section 2 covers the requirements for sheets, draw sheets and pillow slips made from sheeting complying with Section 1.

## SECTION ONE : SHEETING

### 2. GENERAL REQUIREMENTS FOR SHEETING FABRIC

Sheeting fabrics conforming to this specification shall be free from imperfections or blemishes which affect their appearance or serviceability. The yarns from which they are woven shall be composed entirely of chemically sound, thoroughly cleaned material free from waste. Sheeting manufactured from the fabrics shall be of uniform length, width and weave and may be bleached, unbleached or dyed. It shall be available in the unbleached, bleached or dyed state, either in plain weave or loomstate twill. The selvages shall be firm and straight.

### 3. DETAIL REQUIREMENTS

**3.1 Weave.** The weave shall be plain weave or 2×2 twill or 3×1 herring-bone twill.

**3.2 Length.** Each piece shall be one continuous length and unless otherwise specified, this length shall be not less than 60 m. Length of sheeting shall be determined in accordance with ISO 3933:1976 “Textiles – Woven fabrics – Measurement of length of pieces”, issued by the International Organization for Standardization, 1 rue de Varembe, 1211 Geneva 20, Switzerland.

**3.3 Width.** Sheeting width may be 230 cm, 180 cm, 155 cm, or 114 cm and shall be determined in accordance with ISO 3932:1976 “Textiles – Woven fabrics – Measurement of width of pieces”.

**3.4 Mass.** The mass of the fabric shall be in accordance with Table 1. It shall be determined in accordance with ISO 3801:1977 “Textiles – Woven fabrics – Determination of mass per unit length and mass per unit area”.

**3.5 Minimum number of yarns per cm in warp and weft.** This property shall meet the requirements set out in Table 1. It shall be determined in accordance with Method 4/88, Determination of threads per centimetre in woven fabrics, of British Standards Handbook 11:1974, “Methods of test for textiles” published by the British Standards Institution, 2 Park Street, London W1A 2BS.

**3.6 Breaking load.** The breaking load in warp and weft shall be as given in Table 1 and shall be determined in accordance with ISO 5081:1977 “Textiles – Woven fabrics – Determination of breaking strength and elongation (Strip method)”.

**3.7 Filling.** The maximum filling percentage shall be as set out in Table 1.

### **3.8 Colour of fabrics.**

**3.8.1 White fabrics.** Unless otherwise specified in the purchase documents, sheeting and sheets conforming to this specification shall be white, i.e. the fabric shall be given a full commercial bleach.

**3.8.2 Dyed fabrics.** The colour shall be as specified in the purchase documents. When so required by the purchaser, the sheeting shall have woven coloured stripes.

**3.9 Maximum dimensional change, each direction, laundering (10 cycles).** The above property shall conform to Table 1 and shall be determined by the method prescribed in ISO 675:1979 “Textiles – Woven fabrics – Determination of dimensional change on commercial laundering near the boiling point”.

**3.10 Colour fastness of dyed sheeting.** The minimum values for colour fastness (to light, laundering, dry cleaning, dry rubbing, wet rubbing, perspiration) shall accord with Table 2. The test method used shall be as specified in ISO 105:1978 “Textiles – Tests for colour fastness”. Dyed sheeting shall show no visible evidence of change in colour either through loss of depth or change in hue outside the limits specified in Table 2.

## **4. MARKING**

Sheeting shall be clearly and indelibly marked at each end of each piece with the following information:

- (a) the inscription “I.S. 2:Part 2:1982”,
- (b) the manufacturer’s name or mark,
- (c) the words “polyester/cotton” or “Irish linen” or “Irish linen/cotton” as appropriate,
- (d) the length of the piece in metres.

Alternatively, a label secured to one end of the piece shall give the same information.

## **5. SAMPLES FOR TEST**

Samples of sheeting required for the tests prescribed in this specification shall be cut (not torn) from the piece at a position not less than 3 metres from the end of the piece. They shall be the full width of the sheeting and shall be not less than 2 m in length.

## **6. SEWING THREAD**

Except otherwise specified a suitable core spun polyester thread or cotton thread conforming to I.S. 113:1964 “Domestic Sewing Threads (Cotton and Linen)” shall be used.

TABLE 1. MINIMUM PERFORMANCE REQUIREMENTS FOR VARIOUS NON-COTTON SHEETING  
(PLAIN AND TWILL)

Type	Weave	Materials	Filling content %	Mass g/m <sup>2</sup>	Fabric count, yarns/cm		Breaking load, newtons		Dimensional change after laundering %	
					warp	weft	warp	weft	in warp	in weft
1	Plain	White or coloured, unresinated 50% Polyester, 50% Cotton	≥ 2	145	28	25	650	600	≥ 5	≥ 5
2	Twill	Irish Linen, Fully Bleached and Finished Piece Bleached and of Fluidity 12 reciprocal poises	≥ 5	175	20	19	1100	900	≥ 5	≥ 5
3	Plain	Bleached Union Plain Sheeting 52% Linen Weft, 48% Cotton Warp by weight	≥ 5	160	25	22	630	1090	≥ 5	≥ 5
4	Twill	Bleached Union Twill Sheeting 63% Linen Weft, 37% Cotton Warp by weight	≥ 5	235	20	16	690	980	≥ 5	≥ 5

**Note:** The resistance to pilling of sheeting Type 1 shall be not less than Rating 4 on the ICI Pilling Standard.

The linen yarns employed in the manufacture of sheeting Types 2, 3 and 4 shall be spun wholly from retted flax. The fluidity of all bleached linen fabrics shall not exceed 12 reciprocal poises when determined in accordance with B.S. 3090:1978 "Method of test for the determination of the cuprammonium fluidity of linen materials".

TABLE 2 – COLOUR FASTNESS REQUIREMENTS FOR DYED SHEETINGS

<i>Colour fastness to</i>	<i>No more change in colour than</i>
Light	Blue scale 4
Laundering	Grey scale 4 or to staining than grey scale 3
Dry cleaning	Grey scale 4
Dry rubbing	Grey scale 4
Wet rubbing	Grey scale 3–4
Perspiration	Grey scale 4 or to staining than grey scale 3–4

TABLE 3 – FINISHED DIMENSIONS OF SHEETS, DRAW SHEETS AND PILLOW SLIPS  
(All materials as specified in Table 1)

Item	Width x Length (cm)
Sheets	152 x 203 178 x 274, 178 x 252, 178 x 229 89 x 70
Draw sheets	114 x 183
Pillow slips	51 x 76 59 x 76

## SECTION 2 : SHEETS AND PILLOW SLIPS

### 7. MATERIALS

Sheets and pillow slips shall be manufactured from a grade of sheeting conforming to the requirements specified in Section 1 of this specification. Each sheet or pillow slip shall be made from a single full width of material. The material shall be carefully cut on the warp.

### 8. HEMMING

Each sheet shall be hemmed at each non-selvedge edge. Hems of a size specified in the purchase documents and ideally of equal width and sewn with thread conforming to Clause 6 of this specification shall be used. The turn-in shall be not less than 6 mm. The sewing shall be lockstitch with a minimum of 4 stitches per cm. The ends of the sewings, also breaks in the threads during sewing shall be securely backstitched.

The hem at the open end of pillow slips shall be  $25 \pm 3$  mm wide, turned to the inside unless otherwise specified by the purchaser and with the raw edge folded in 6 mm. The hem on the flap shall be at least 6 mm wide with the raw edge folded in 3 mm. A selvedge may be used on the flap without hemming.

### 9. DIMENSIONS

The finished dimensions for sheets and pillow slips are given in Table 3.

### 10. PILLOW SLIPS, PLAIN WEAVE, MANUFACTURE

The pillow slip shall be made to the Housewife pattern with a 20 cm flap and shall have the selvages at the end of the flap and the opening. The flap edges shall be inserted between the long side seams. No cut edges shall be exposed. The sewing shall be of even tension throughout and shall be finished off securely and neatly. The number of stitches shall be not less than 5 per cm. Figure 1 shows the Housewife pattern pillow slip.

### 11. MARKING OF SHEETS AND PILLOW SLIPS

Sheets and pillow slips shall be clearly and indelibly marked, the former at one corner, the latter on the inside of the flap, with the following information:

- (a) the inscription "I.S. 2:Part 2:1982",
- (b) the manufacturer's name or mark,
- (c) the words "polyester cotton" or "Irish linen" or "Irish linen/cotton" as appropriate,
- (d) the dimensions,
- (e) the type, see Table 1.

### 12. SAMPLES FOR TEST

Samples for the purpose of testing for conformity with this specification shall be taken from a single sheet or pillow slip selected at random.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- Looking for additional Standards? Visit Intertek Inform Infostore
  - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-