



National Standards Authority of Ireland

IRISH STANDARD

I.S. EN 12502-3:2005

ICS 77.060
23.040.99
91.140.60

**PROTECTION OF METALLIC MATERIALS
AGAINST CORROSION - GUIDANCE ON THE
ASSESSMENT OF CORROSION LIKELIHOOD
IN WATER DISTRIBUTION AND STORAGE
SYSTEMS - PART 3: INFLUENCING FACTORS
FOR HOT DIP GALVANISED FERROUS
MATERIALS**

National Standards
Authority of Ireland
Glasnevin, Dublin 9
Ireland

Tel: +353 1 807 3800
Fax: +353 1 807 3838
<http://www.nsai.ie>

Sales
<http://www.standards.ie>

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland
and comes into effect on:
March 24, 2005*

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2005

Price Code F

Údarás um Chaighdeán Náisiúnta na hÉireann

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12502-3

December 2004

ICS 77.060; 23.040.99; 91.140.60

English version

**Protection of metallic materials against corrosion - Guidance on
the assessment of corrosion likelihood in water distribution and
storage systems - Part 3: Influencing factors for hot dip
galvanised ferrous materials**

Protection des matériaux métalliques contre la corrosion -
Recommandations pour l'évaluation du risque de corrosion
dans les installations de distribution et stockage d'eau -
Partie 3 : Facteurs à considérer pour les métaux ferreux
galvanisés à chaud

Korrosionsschutz metallischer Werkstoffe - Hinweise zur
Abschätzung der Korrosionswahrscheinlichkeit in
Wasserverteilungs- und speichersystemen - Teil 3:
Einflussfaktoren für schmelztauchverzinkte Eisenwerkstoffe

This European Standard was approved by CEN on 22 November 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms, definitions, and symbols	5
3.1 Terms and definitions	5
3.2 Symbols	5
4 Types of corrosion.....	6
4.1 General.....	6
4.2 Uniform corrosion.....	7
4.3 Pitting corrosion	8
4.4 Selective corrosion.....	11
4.5 Bimetallic corrosion	12
5 Assessment of corrosion likelihood.....	13
Bibliography	14

Foreword

This document (EN 12502-3:2004) has been prepared by Technical Committee CEN/TC 262 "Metallic and other inorganic coatings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

This standard is in five parts:

Part 1: General;

Part 2: Influencing factors for copper and copper alloys;

Part 3: Influencing factors for hot dip galvanized ferrous material;

Part 4: Influencing factors for stainless steels;

Part 5: Influencing factors for cast iron, unalloyed and low alloyed steels.

Together these five parts constitute a package of interrelated European Standards with a common date of withdrawal (dow) of 2005-06.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

This document results mainly from investigations into and experience gained of the corrosion of hot dip galvanized ferrous materials, used as steel tubes and cast iron fittings (galvanized products), in drinking water distribution systems in buildings. However, it can be applied analogously to other water systems.

The corrosion likelihood of galvanized products depends on the formation of a corrosion product layer, which begins to form as soon as the galvanized surface comes in contact with water. The more this layer prevents ionic and electronic exchanges between the metal and water, the more protective it will be and the higher the durability of the galvanized products.

Drinking water systems with galvanized products, although showing visible corrosion effects, are, in general, resistant to corrosion damage in normal use. However, there are conditions under which they will sustain corrosion damage.

As a result of the complex interactions between the various influencing factors, the extent of corrosion can only be expressed in terms of likelihood. This document is a guidance document and does not set explicit rules for the use of hot dip galvanized ferrous materials in water systems. It can be used to minimize the likelihood of corrosion damages occurring by:

- assisting in designing, installing and operating systems from an anti-corrosion point of view;
- evaluating the need for additional corrosion protection methods for a new or existing system;
- assisting in failure analysis, when failures occur in order to prevent repeat failures occurring.

However, a corrosion expert, or at least a person with technical training and experience in the corrosion field is required to give an accurate assessment of corrosion likelihood or failure analysis.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-