

IRISH STANDARD

I.S. CEN/TS 13130-10:2005

ICS 67.250

MATERIALS AND ARTICLES IN CONTACT
WITH FOODSTUFFS - PLASTICS
SUBSTANCES SUBJECT TO LIMITATION PART 10: DETERMINATION OF ACRYLAMIDE
IN FOOD SIMULANTS

National Standards Authority of Ireland Glasnevin, Dublin 9 Ireland

Tel: +353 1 807 3800 Fax: +353 1 807 3838 http://www.nsai.ie

Sales

http://www.standards.ie

This Irish Standard was published under the authority of the National Standards Authority of Ireland and comes into effect on: May 5, 2005

NO COPYING WITHOUT NSAI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

© NSAI 2005 Price Code G

Údarás um Chaighdeáin Náisiúnta na hÉireann

This is a free page sample. Access the full version online.

TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN/TS 13130-10

February 2005

ICS 67.250

English version

Materials and articles in contact with foodstuffs - Plastics substances subject to limitation - Part 10: Determination of acrylamide in food simulants

Matériaux et objets en contact avec les denrées alimentaires - Substances dans les matières plastiques soumises à des limitations - Partie 10 : Détermination de l'acrylamide dans les simulants d'aliments Werkstoffe und Gegenstände in Kontakt mit Lebensmitteln
- Substanzen in Kunststoffen, die Beschränkungen
unterliegen - Teil 10: Bestimmung von Acrylamid in
Prüflebensmitteln

This Technical Specification (CEN/TS) was approved by CEN on 16 December 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

CEN/TS 13130-10:2005 (E)

Contents

		page
Fore	word	3
Intro	duction	
1	Scope	6
2	Normative references	6
3	Principle	
4	Reagents	6
5	Apparatus	7
6	Samples	
7	Procedure	9
8	Expression of results	11
9	Confirmation	
10	Test report	14
Biblio	ography	15

CEN/TS 13130-10: 2005 (E)

Foreword

This document (CEN/TS 13130-10:2005) has been prepared by Technical Committee CEN/TC 194 "Utensils in contact with food", the secretariat of which is held by BSI.

This part of EN 13130 has been prepared within the Standards, Measurement and Testing project, MAT1-CT92-0006, "Development of Methods of Analysis for Monomers" and has been prepared by Subcommittee (SC 1) of TC 194 "Utensils in contact with food" as one of a series of test methods for plastics materials and articles in contact with foodstuffs.

This standard is intended to support Directives 2002/72/EC [1], 89/109/EEC [2], 82/711/EEC [3] and its amendments 93/8/EEC [4] and 97/48/EC [5], and 85/572/EEC [6].

At the time of preparation and publication of this part of EN 13130 the European Union legislation relating to plastics materials and articles intended to come into contact with foodstuffs is incomplete. Further Directives and amendments to existing Directives are expected which could change the legislative requirements which this standard supports. It is therefore strongly recommended that users of this standard refer to the latest relevant published Directive(s) before commencement of a test or tests described in this standard.

This part of EN 13130 should be read in conjunction with EN 13130-1.

Further parts of EN 13130, under the general title *Materials and articles in contact with foodstuffs - Plastics substances subject to limitation*, have been prepared, and others are in preparation, concerned with the determination of specific migration from plastics materials into foodstuffs and food simulants and the determination of specific monomers and additives in plastics. The parts of EN 13130 are as follows.

- Part 1: Guide to test methods for the specific migration of substances from plastics to foods and food simulants and the determination of substances in plastics and the selection of conditions of exposure to food simulants
- Part 2: Determination of terephthalic acid in food simulants
- Part 3: Determination of acrylonitrile in food and food simulants
- Part 4: Determination of 1,3-butadiene in plastics
- Part 5: Determination of vinylidene chloride in food simulants
- Part 6: Determination of vinylidene chloride in plastics
- Part 7: Determination of monoethylene glycol and diethylene glycol in food simulants
- Part 8: Determination of isocyanates in plastics
- Part 9: Determination of acetic acid, vinyl ester in food simulants
- Part 10: Determination of acrylamide in food simulants
- Part 11: Determination of 11-aminoundecanoic acid in food simulants
- Part 12: Determination of 1,3-benzenedimethanamine in food simulants
- Part 13: Determination of 2,2-bis(4-hydroxyphenyl)propane (Bisphenol A) in food simulants

CEN/TS 13130-10:2005 (E)

- Part 14: Determination of 3,3-bis(3-methyl-4-hydroxyphenyl)-2-indoline in food simulants
- Part 15: Determination of 1.3-butadiene in food simulants
- Part 16: Determination of caprolactam and caprolactam salt in food simulants
- Part 17: Determination of carbonyl chloride in plastics
- Part 18: Determination of 1,2-dihydroxybenzene, 1,3-dihydroxybenzene, 1,4-dihydroxybenzene, 4,4'-dihydroxybenzophenone and 4,4'dihydroxybiphenyl in food simulants
- Part 19: Determination of dimethylaminoethanol in food simulants
- Part 20: Determination of epichlorohydrin in plastics
- Part 21: Determination of ethylenediamine and hexamethylenediamine in food simulants
- Part 22: Determination of ethylene oxide and propylene oxide in plastics
- Part 23: Determination of formaldehyde and hexamethylenetetramine in food simulants
- Part 24: Determination of maleic acid and maleic anhydride in food simulants
- Part 25: Determination of 4-methyl-pentene in food simulants
- Part 26: Determination of 1-octene and tetrahydrofuran in food simulants
- Part 27: Determination of 2,4,6-triamino-1,3,5-triazine in food simulants
- Part 28: Determination of 1,1,1-trimethylolpropane in food simulants
- Parts 1 to 8 are European Standards. Parts 9 to 28 are Technical Specifications.

WARNING All chemicals are hazardous to health to a greater or lesser extent. It is beyond the scope of this Technical Specification to give instructions for the safe handling of all chemicals, that meet, in full, the legal obligations in all countries in which this Technical Specification may be followed. Therefore, specific warnings are not given and users of this Technical Specification should ensure that they meet all the necessary safety requirements in their own country.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this CEN Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



	This is a free preview.	Purchase the e	entire publication	at the link below:
--	-------------------------	----------------	--------------------	--------------------

Product Page

- Dooking for additional Standards? Visit Intertek Inform Infostore
- Dearn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation