

IRISH STANDARD

I.S. EN 14617-5:2005

THAW RESISTANCE

ICS 91.100.15

National Standards Authority of Ireland Glasnevin, Dublin 9 Ireland

Tel: +353 1 807 3800 Fax: +353 1 807 3838 http://www.nsai.ie

Sales http://www.standards.ie

This Irish Standard was published under the authority of the National Standards Authority of Ireland and comes into effect on: June 3, 2005

NO COPYING WITHOUT NSAI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

© NSAI 2005

Price Code E

Údarás um Chaighdeáin Náisiúnta na hÉireann

AGGLOMERATED STONE - TEST METHODS -

PART 5: DETERMINATION OF FREEZE AND

This is a free page sample. Access the full version online.

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 14617-5

March 2005

ICS 91.100.15

English version

Agglomerated stone - Test methods - Part 5: Determination of freeze and thaw resistance

Pierre agglomérée - Méthodes d'essai - Partie 5: Détermination de la résistance au gel et au dégel Künstlich hergestellter Stein - Prüfverfahren - Teil 5: Bestimmung der Frost-Tau-Wechselbeständigkeit

This European Standard was approved by CEN on 3 February 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2005 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members. Ref. No. EN 14617-5:2005: E

EN 14617-5:2005 (E)

Contents

Page

Foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Terms, definitions and symbols	4
5	Apparatus	4
6	Preparation of the specimens	5
7	Test procedure	5
8	Expression of results	5
9	Test report	5
Bibliog	Bibliography	

Foreword

This document (EN 14617-5:2005) has been prepared by Technical Committee CEN/TC 246 "Natural stones", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2005, and conflicting national standards shall be withdrawn at the latest by September 2005.

Test methods for agglomerated stones consist of the following:

EN 14617-1, Agglomerated stone - Test methods – Part 1: Determination of apparent density and water absorption

EN 14617-2, Agglomerated stone – Test methods – Part 2: Determination of flexural strength (bending)

prEN 14617-3, Agglomerated stone - Test methods - Part 3: Determination of slipperiness

EN 14617-4, Agglomerated stone - Test methods – Part 4: Determination of the abrasion resistance

EN 14617-5, Agglomerated stone - Test methods – Part 5: Determination of freeze and thaw resistance

EN 14617-6, Agglomerated stone - Test methods – Part 6: Determination of thermal shock resistance

prEN 14617-7, Agglomerated stone – Test methods – Part 7: Determination of ageing

prEN 14617-8, Agglomerated stone – Test methods – Part 8: Determination of resistance to fixing (dowel hole)

EN 14617-9, Agglomerated stone - Test methods - Part 9: Determination of impact resistance

EN 14617-10, Agglomerated stone – Test methods – Part 10: Determination of chemical resistance

EN 14617-11, Agglomerated stone - Test methods - Part 11: Determination of linear thermal expansion coefficient

EN 14617-12, Agglomerated stone – Test methods – Part 12: Determination of dimensional stability

EN 14617-13, Agglomerated stone – Test methods – Part 13: Determination of electrical resistivity

prEN 14617-14, Agglomerated stone – Test methods – Part 14: Determination of surface hardness

EN 14617-15, Agglomerated stone – Test methods – Part 15: Determination of compressive strength

EN 14617-16, Agglomerated stone – Test methods – Part 16: Determination of dimensions, geometric characteristics and surface quality of modular tiles

prEN 14617-17, Agglomerated stone – Test methods – Part 17: Determination of biological resistance

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

The document specifies a method to assess the effect of freeze/thaw cycles on agglomerated stones. The standard contains provision for technological test to assess the effect of freeze/thaw cycles on the flexural strength characteristic.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14617-2:2004, Agglomerated stone – Test Methods – Part 2:Determination of flexural strength (bending)

3 Principle

The principle of this test method is the determination of the ratio between the flexural strength of specimens after 25 freeze/thaw cycles and that of unfrosted specimens. One freeze/thaw cycle includes freezing part, when water saturated specimen is loaded into freezer (temperature -20 °C ± 5 °C) and thaw part, when frosted specimen is immersed in tap water (temperature 20 °C ± 5 °C).

4 Terms, definitions and symbols

4.1 Terms and definitions

For the purposes of this document, the following term and definition applies.

4.1.1

freeze/thaw resistance

ability of the agglomerated stone product saturated by water to resist the effect of freeze/thaw cycling.

4.2 Symbols

*KM*_{f 25} coefficient of freeze/thaw resistance in flexural strength (after 25 freeze/thaw cycles);

- *R*_f flexural strength average value (MPa) of dried, unfrosted specimens;
- *RM*_f flexural strength average value (MPa) of specimens after 25 freeze/thaw cycles.

5 Apparatus

5.1 A freezing chamber of sufficient capacity to hold the required number of specimens, possibly with an automatic control system to programme the freezing and thawing cycles within the chamber, capable of maintaining the temperature at $(-20 \pm 5)^{\circ}$ C.

- **5.2** A temperature recording system or thermometer capable of measuring temperature to $\pm 0,1$ °C.
- 5.3 A linear measuring device with an accuracy of 0,5 mm (for the flexural measurement).
- 5.4 A desiccator.
- **5.5** A ventilated oven capable of maintaining a temperature of (70 ± 5) °C.
- 4



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation