



National Standards Authority of Ireland

STANDARD

**I.S. EN ISO 15875-3:2004**

ICS 23.040.45

91.140.60

**PLASTICS PIPING SYSTEMS FOR HOT AND  
COLD WATER INSTALLATIONS -  
CROSSLINKED POLYETHYLENE (PE-X) -  
PART 3: FITTINGS (ISO 15875-3:2003)**

National Standards  
Authority of Ireland  
Dublin 9  
Ireland

Tel: (01) 807 3800

Tel: (01) 807 3838

*This Irish Standard was  
published under the  
authority of the National  
Standards Authority of  
Ireland  
and comes into effect on:  
April 21, 2004*

**NO COPYING WITHOUT NSAI  
PERMISSION EXCEPT AS  
PERMITTED BY COPYRIGHT  
LAW**

© NSAI 2004

**Price Code F**

Údarás um Chaighdeáin Náisiúnta na hÉireann



EUROPEAN STANDARD

**EN ISO 15875-3**

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2003

---

ICS 23.040.45; 91.140.60

English version

**Plastics piping systems for hot and cold water installations -  
Crosslinked polyethylene (PE-X) - Part 3: Fittings (ISO 15875-  
3:2003)**

Systèmes de canalisations en plastique pour les  
installations d'eau chaude et froide - Polyéthylène réticulé  
(PE-X) - Partie 3: Raccords (ISO 15875-3:2003)

Kunststoff-Rohrleitungssysteme für die Warm- und  
Kaltwasserinstallation - Vernetztes Polyethylen (PE-X) -  
Teil 3: Formstücke (ISO 15875-3:2003)

This European Standard was approved by CEN on 14 March 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**EN ISO 15875-3:2003 (E)**

**Contents**

**Contents**..... **2**

**Introduction** ..... **4**

**1 Scope**..... **4**

**2 Normative references**..... **4**

**3 Terms and definitions, symbols and abbreviated terms**..... **5**

**4 Material characteristics** ..... **6**

4.1 Plastics fitting material ..... 6

4.1.1 Fitting material identical to PE-X pipe material ..... 6

4.1.2 PE-X fitting material not identical to PE-X pipe material ..... 7

4.1.3 Plastics fitting material other than PE-X..... 7

4.2 Metallic fitting material..... 7

4.3 Influence on water intended for human consumption ..... 7

**5 General characteristics**..... **8**

5.1 Appearance ..... 8

5.2 Opacity ..... 8

**6 Geometrical characteristics** ..... **8**

6.1 General..... 8

6.1.1 Nominal diameter(s)..... 8

6.1.2 Angles ..... 8

6.1.3 Threads ..... 8

6.2 Dimensions of sockets for electrofusion fittings ..... 8

6.3 Dimensions of metallic fittings..... 9

**7 Mechanical characteristics of plastics fittings**..... **10**

7.1 General..... 10

7.2 Fittings made from PE-X material identical to the PE-X pipe material..... 10

7.3 Fittings made from PE-X not identical to the PE-X pipe material ..... 11

7.4 Fittings made from plastics other than PE-X..... 11

**8 Physical and chemical characteristics of plastics fittings** ..... **11**

**9 Sealing elements** ..... **12**

**10 Performance requirements** ..... **12**

**11 Marking**..... **12**

11.1 General requirements ..... 12

11.2 Minimum required marking..... 12

**Bibliography** ..... **14**

## Foreword

This document (EN ISO 15875-3:2003) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN, in collaboration with Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2004, and conflicting national standards shall be withdrawn at the latest by December 2005.

NOTE This draft was submitted for CEN enquiry as prEN 12318-3:1996.

This standard is part of a System Standard for plastics piping systems of a particular material for a specified application. There are a number of such System Standards.

System Standards are based on the results of the work being undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organisation for Standardization (ISO).

They are supported by separate Standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and recommended practices for installation.

EN ISO 15875 consists of the following Parts <sup>1)</sup>, under the general title: *Plastics piping systems for hot and cold water installations — Crosslinked polyethylene (PE-X)*

- Part 1: *General*
- Part 2: *Pipes*
- Part 3: *Fittings* (the present standard)
- Part 5: *Fitness for purpose of the system*
- Part 7: *Guidance for the assessment of conformity* (published as CEN ISO/TS 15875-7).

This Part of EN ISO 15875 includes a Bibliography

At the date of publication of this standard, System Standards for piping systems of other plastics materials used for the same application include the following:

EN ISO 15874, *Plastics piping systems for hot and cold water installations — Polypropylene (PP)* (ISO 15874:2003)

EN ISO 15876, *Plastics piping systems for hot and cold water installations — Polybutylene (PB)* (ISO 15876:2003)

EN ISO 15877, *Plastics piping systems for hot and cold water installations — Chlorinated poly(vinyl chloride) (PVC-C)* (ISO 15877:2003)

For pipes and fittings which have conformed to the relevant national standard before 1<sup>st</sup> November 2003, as shown by the manufacturer or by a certification body, the national standard may continue to apply until 30<sup>th</sup> November 2005.

---

<sup>1)</sup> This System Standard does not incorporate a Part 4 *Ancillary equipment* or a Part 6 *Guidance for installation*. For ancillary equipment separate standards can apply. Guidance on installation of plastics piping systems made from different materials intended to be used for hot and cold water installations is given by ENV 12108 <sup>[1]</sup>.

## EN ISO 15875-3:2003 (E)

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

### Introduction

The System Standard of which this is Part 3, specifies the requirements for a piping system when made from polypropylene (PE-X). The piping system is intended to be used for hot and cold water installations.

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this standard:

- This standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- It should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

Requirements and test methods for materials and components, other than fittings, are specified in Part 1 and Part 2 of EN ISO 15875:2003. Characteristics for fitness for purpose (mainly for joints) are covered in Part 5. Part 7 (CEN ISO/TS 15875-7) gives guidance for the assessment of conformity.

This Part of EN ISO 15875 specifies the characteristics of the fittings.

### 1 Scope

This Part of EN ISO 15875 specifies the characteristics of fittings for crosslinked polyethylene (PE-X) piping systems intended to be used for hot and cold water installations within buildings for the conveyance of water, whether or not intended for human consumption, (domestic systems) and for heating systems, under design pressures and temperatures appropriate to the class of application (see Table 1 of EN ISO 15875-1:2003).

This standard covers a range of service conditions (application classes) and design pressure classes. For values of  $T_D$ ,  $T_{max}$  and  $T_{mal}$  in excess of those in Table 1 of Part 1, this standard does not apply.

NOTE It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with the other Parts of EN ISO 15875:2003 (see Foreword) it is applicable to fittings made from crosslinked polyethylene (PE-X) and to fittings made from other materials which are intended to be fitted to pipes conforming to EN ISO 15875-2:2003 for hot and cold water installations and whereby the joints conform to the requirements of EN ISO 15875-5.

This standard is applicable to fittings of the following types:

- mechanical fittings;
- electrofusion fittings;
- fittings with incorporated inserts.

### 2 Normative references

This Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 578, *Plastics piping systems — Plastics pipes and fittings — Determination of the opacity*

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-