



National Standards Authority of Ireland

IRISH STANDARD

I.S. CEN/TS 14938-2:2006

ICS 77.120.30

**COPPER AND COPPER ALLOYS -  
DETERMINATION OF BISMUTH CONTENT -  
PART 2: FAAS METHOD**

National Standards  
Authority of Ireland  
Glasnevin, Dublin 9  
Ireland

Tel: +353 1 807 3800  
Fax: +353 1 807 3838  
<http://www.nsai.ie>

**Sales**  
<http://www.standards.ie>

*This Irish Standard was  
published under the  
authority of the National  
Standards Authority of  
Ireland and comes into  
effect on:  
17 October 2006*

**NO COPYING WITHOUT NSAI  
PERMISSION EXCEPT AS  
PERMITTED BY COPYRIGHT  
LAW**

© NSAI 2006

**Price Code E**

Údarás um Chaighdeán Náisiúnta na hÉireann



TECHNICAL SPECIFICATION  
SPÉCIFICATION TECHNIQUE  
TECHNISCHE SPEZIFIKATION

**CEN/TS 14938-2**

September 2006

ICS 77.120.30

English Version

**Copper and copper alloys - Determination of bismuth content -  
Part 2: FAAS method**

Cuivre et alliages de cuivre - Dosage du bismuth - Partie 2 :  
Méthode par spectrométrie d'absorption atomique dans la  
flamme (SAAF)

Kupfer und Kupferlegierungen - Bestimmung des  
Bismutgehaltes - Teil 2:  
Flammenatomabsorptionsspektrometrisches Verfahren  
(FAAS)

This Technical Specification (CEN/TS) was approved by CEN on 23 July 2006 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## CEN/TS 14938-2:2006 (E)

<b>Contents</b>		<b>Page</b>
<b>Foreword</b> .....		<b>3</b>
<b>1</b>	<b>Scope</b> .....	<b>4</b>
<b>2</b>	<b>Normative references</b> .....	<b>4</b>
<b>3</b>	<b>Principle</b> .....	<b>4</b>
<b>4</b>	<b>Reagents and materials</b> .....	<b>4</b>
<b>5</b>	<b>Apparatus</b> .....	<b>5</b>
<b>6</b>	<b>Sampling</b> .....	<b>5</b>
<b>7</b>	<b>Procedure</b> .....	<b>5</b>
<b>8</b>	<b>Expression of results</b> .....	<b>8</b>
<b>9</b>	<b>Precision</b> .....	<b>9</b>
<b>10</b>	<b>Test report</b> .....	<b>9</b>
<b>Bibliography</b> .....		<b>10</b>

## **Foreword**

This document (CEN/TS 14938-2:2006) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 "Methods of analysis" to prepare the following Technical Specification:

*CEN/TS 14938-2, Copper and copper alloys — Determination of bismuth content — Part 2: FAAS method*

This is one of two parts of the standard/technical specification for the determination of bismuth content in copper and copper alloys. The other part is under preparation:

*..., Copper and copper alloys — Determination of bismuth content — Part 1: Spectrophotometric method*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## CEN/TS 14938-2:2006 (E)

### 1 Scope

This European Technical Specification specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the bismuth content of copper and copper alloys in the form of unwrought, wrought and cast products.

The method is applicable to products having bismuth mass fractions between 0,01 % and 0,25 %.

### 2 Normative references

The following referenced documents are indispensable for the application of this European Technical Specification. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

NOTE Informative references to documents used in the preparation of this standard, and cited at the appropriate places in the text, are listed in the bibliography.

### 3 Principle

Dissolution of a test portion in a mixture of hydrochloric acid/hydrogen peroxide and nitric acid solutions followed, after suitable dilution, by aspiration into an air/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 223,1 nm line emitted by a bismuth hollow-cathode or electrodeless discharge lamp.

### 4 Reagents and materials

#### 4.1 General

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

**4.2 Hydrochloric acid**,  $\text{HCl}$  ( $\rho = 1,19 \text{ g/ml}$ ).

**4.3 Nitric acid**,  $\text{HNO}_3$  ( $\rho = 1,40 \text{ g/ml}$ ).

**4.4 Hydrogen peroxide**,  $\text{H}_2\text{O}_2$  30 % (mass fraction) solution.

**4.5 Bismuth stock solution**, 1,000 g/l Bi

Weigh  $(0,25 \pm 0,001)$  g of bismuth ( $\text{Bi} \geq 99,9999 \%$ ) and transfer it into a 250 ml conical flask. Add 50 ml of nitric acid (4.3). Heat gently until the bismuth is dissolved and then bring to the boiling point until the nitrous fumes have been expelled. Cool to room temperature, transfer the solution quantitatively into a 250 ml one-mark volumetric flask, dilute to the mark with water and mix well.

1 ml of this solution contains 1,000 mg of Bi.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- Looking for additional Standards? Visit Intertek Inform Infostore
  - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-