



National Standards Authority of Ireland

IRISH STANDARD

I.S. EN 725-11:2006

ICS 81.060.99

**ADVANCED TECHNICAL CERAMICS -
METHODS OF TEST FOR CERAMIC
POWDERS - PART 11: DETERMINATION OF
DENSIFICATION ON NATURAL SINTERING**

National Standards
Authority of Ireland
Glasnevin, Dublin 9
Ireland

Tel: +353 1 807 3800
Fax: +353 1 807 3838
<http://www.nsai.ie>

Sales
<http://www.standards.ie>

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland and comes into
effect on:
22 August 2006*

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2006

Price Code E

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 725-11

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2006

ICS 81.060.99

Supersedes ENV 725-11:1993

English Version

Advanced technical ceramics - Methods of test for ceramic powders - Part 11: Determination of densification on natural sintering

Céramiques techniques avancées - Méthodes d'essai pour poudres céramiques - Partie 11: Détermination de la densification lors du frittage naturel

Hochleistungskeramik - Prüfverfahren für keramische Pulver - Teil 11: Bestimmung der Verdichtungsverhaltens bei natürlichem Sinterbrand

This European Standard was approved by CEN on 25 May 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Terms, symbols and units	5
5	Apparatus	5
6	Test pieces	6
7	Heating conditions	6
8	Procedure	6
9	Expression of results	6
10	Test report	7

Foreword

This document (EN 725-11:2006) has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2006, and conflicting national standards shall be withdrawn at the latest by December 2006.

This document supersedes ENV 725-11:1993.

EN 725 *Advanced technical ceramics — Methods of test for ceramic powders* was prepared in Parts as follows:

- Part 1: *Determination of impurities in alumina*
- Part 2: *Determination of impurities in barium titanate*
- Part 3: *Determination of oxygen content of non-oxides by thermal extraction*
- Part 4: *Determination of oxygen content in aluminium nitride by XRF analysis*
- Part 5: *Determination of particle size distribution*
- Part 6: *Determination of specific surface area (withdrawn)*
- Part 7: *Determination of absolute density (withdrawn)*
- Part 8: *Determination of tapped bulk density*
- Part 9: *Determination of un-tapped bulk density*
- Part 10: *Determination of compaction properties*
- Part 11: *Determination of densification on natural sintering*
- Part 12: *Chemical analysis of zirconia*

Parts 6 and 7 of the series were superseded in 2005 by EN ISO 18757 and EN ISO 18753 respectively

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 725-11:2006 (E)

1 Scope

This Part of EN 725 describes a method for determining the densification of ceramic powders on natural sintering, without the application of any external pressure. The method is applicable to pure oxides, mixtures of oxides and solid solutions. Inorganic sintering additives may be used where their presence is reported.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 623-2:1993, *Advanced technical ceramics — Monolithic ceramics — General and textural properties — Part 2: Determination of density and porosity*

EN 725-10, *Advanced technical ceramics — Methods of test for ceramic powders — Part 10: Determination of compaction properties*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)*

ISO 3611, *Micrometer callipers for external measurement*

3 Principle

Measurements are made of the mass, dimensions and density of a compacted piece of ceramic powder, before and after sintering through thermal treatment. The results depend on the maximum temperature and the density after compaction, and are expressed as a function of these two main parameters.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-