



National Standards Authority of Ireland

IRISH STANDARD

I.S. CEN/TS 15022-4:2006

ICS 77.120.30

**COPPER AND COPPER ALLOYS -
DETERMINATION OF TIN CONTENT - PART 4:
MEDIUM TIN CONTENT - FLAME ATOMIC
ABSORPTION SPECTROMETRY METHOD
(FAAS)**

National Standards
Authority of Ireland
Glasnevin, Dublin 9
Ireland

Tel: +353 1 807 3800
Fax: +353 1 807 3838
<http://www.nsai.ie>

Sales
<http://www.standards.ie>

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland and comes into
effect on:
22 January 2007*

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2006

Price Code E

Údarás um Chaighdeáin Náisiúnta na hÉireann

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 15022-4

November 2006

ICS 77.120.30

English Version

**Copper and copper alloys - Determination of tin content - Part 4:
Medium tin content - Flame atomic absorption spectrometry
method (FAAS)**

Cuivre et alliages de cuivre - Dosage de l'étain - Partie 4 :
Etain en moyenne teneur - Méthode par spectrométrie
d'absorption atomique dans la flamme (SAAF)

Kupfer und Kupferlegierungen - Bestimmung des
Zinngehaltes - Teil 4: Mittlerer Zinngehalt -
Flammenatomabsorptionsspektrometrisches Verfahren
(FAAS)

This Technical Specification (CEN/TS) was approved by CEN on 12 September 2006 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

CEN/TS 15022-4:2006 (E)

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Reagents and materials	4
5	Apparatus	5
6	Sampling	5
7	Procedure	5
8	Expression of results	7
9	Precision	8
10	Test report	9
Bibliography		10

Foreword

This document (CEN/TS 15022-4:2006) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 "Methods of analysis" to prepare the following Technical Specification:

CEN/TS 15022-4, Copper and copper alloys — Determination of tin content — Part 4: Medium tin content — Flame atomic absorption spectrometry method (FAAS)

This is one of four parts of the standard/technical specification for the determination of tin content in copper and copper alloys. The other parts are:

prEN 15022-1, Copper and copper alloys — Determination of tin content — Part 1: Titrimetric method

prEN 15022-2, Copper and copper alloys — Determination of tin content — Part 2: Spectrometric method

EN 15022-3, Copper and copper alloys — Determination of tin content — Part 3: Low tin content — Flame atomic absorption spectrometry method (FAAS)

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CEN/TS 15022-4:2006 (E)

1 Scope

This Technical Specification specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the tin content of copper and copper alloys in the form of unwrought, wrought and cast products.

The method is applicable to products having medium tin mass fractions between 0,2 % and 3 %.

2 Normative references

The following referenced documents are indispensable for the application of this European Technical Specification. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

3 Principle

Dissolution of a test portion in hydrochloric acid and hydrogen peroxide followed, after suitable dilution, by aspiration into a nitrous oxide/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 286,3 nm line emitted by a tin hollow-cathode discharge lamp.

4 Reagents and materials

4.1 General

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.2 Hydrochloric acid, HCl ($\rho = 1,19$ g/ml)

4.3 Hydrochloric acid solution, 7 + 3

Dilute 700 ml of hydrochloric acid (4.2) in 300 ml of water.

4.4 Hydrogen peroxide, H₂O₂ 30 % (mass fraction) solution, free from tin base stabilizers

Hydrogen peroxide may be stabilized by products containing some tin. It is therefore necessary to use exactly the same volume of hydrogen peroxide for the dissolution of the test sample as for the preparation of the calibration solution.

4.5 Tin stock solution, 1 g/l Sn

Weigh ($1 \pm 0,001$) g of tin ($\text{Sn} \geq 99$ %) and transfer it into a 250 ml beaker. Dissolve it in 100 ml hydrochloric acid (4.2) and several drops of hydrogen peroxide (4.4) and cover with a watch glass. Heat gently until the metal is dissolved. Cool to room temperature and transfer the solution quantitatively into a 1 000 ml one-mark volumetric flask. Dilute to the mark with water and mix well.

1 ml of this solution contains 1 mg of Sn.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-