



National Standards Authority of Ireland

IRISH STANDARD

I.S. CEN/TS 15023-3:2006

ICS 77.120.30

**COPPER AND COPPER ALLOYS -
DETERMINATION OF NICKEL CONTENT -
PART 3: FLAME ATOMIC ABSORPTION
SPECTROMETRY METHOD (FAAS)**

National Standards
Authority of Ireland
Glasnevin, Dublin 9
Ireland

Tel: +353 1 807 3800
Fax: +353 1 807 3838
<http://www.nsai.ie>

Sales
<http://www.standards.ie>

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland and comes into
effect on:*

22 January 2007

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2006

Price Code F

Údarás um Chaighdeáin Náisiúnta na hÉireann

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 15023-3

November 2006

ICS 77.120.30

English Version

**Copper and copper alloys - Determination of nickel content -
Part 3: Flame atomic absorption spectrometry method (FAAS)**

Cuivre et alliages de cuivre - Dosage du nickel - Partie 3:
Méthode par spectrométrie d'absorption atomique dans la
flamme (SAAF)

Kupfer und Kupferlegierungen - Bestimmung des
Nickelgehaltes - Teil 3:
Flammenatomabsorptionsspektrometrisches Verfahren
(FAAS)

This Technical Specification (CEN/TS) was approved by CEN on 12 September 2006 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

CEN/TS 15023-3:2006 (E)

Contents	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Reagents and materials	4
5 Apparatus	5
6 Sampling	6
7 Procedure	6
8 Expression of results	10
9 Precision	11
10 Test report	12
Bibliography	13

Foreword

This document (CEN/TS 15023-3:2006) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 "Methods of analysis" to prepare the following Technical Specification:

CEN/TS 15023-3, Copper and copper alloys — Determination of nickel content — Part 3: Flame atomic absorption spectrometry method (FAAS)

This is one of three parts of the standard/technical specification for the determination of nickel content in copper and copper alloys. The other parts are:

prEN 15023-1, Copper and copper alloys — Determination of nickel content — Part 1: Spectrometric method

prEN 15023-2, Copper and copper alloys — Determination of nickel content — Part 2: Titrimetric method

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CEN/TS 15023-3:2006 (E)

1 Scope

This Technical Specification specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the nickel content of copper and copper alloys in the form of unwrought, wrought and cast products.

The method is applicable to products having a nickel mass fractions between 0,001 % and 6,0 %.

2 Normative references

The following referenced documents are indispensable for the application of this European Technical Specification. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

3 Principle

Dissolution of a test portion in hydrochloric and nitric acid solution followed, after suitable dilution and the addition of lanthanum chloride to mask the effect of interfering ions, by aspiration into an air/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 232,0 nm or the 352,4 nm line emitted by a nickel hollow-cathode lamp.

4 Reagents and materials

4.1 General

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.2 Hydrochloric acid, HCl ($\rho = 1,19$ g/ml)

4.3 Nitric acid, HNO₃ ($\rho = 1,40$ g/ml)

4.4 Nitric acid solution, 1 + 1

Dilute 500 ml of nitric acid (4.3) in 500 ml of water.

4.5 Lanthanum (III) chloride solution, 100 g/l

Dissolve 100 g of lanthanum (III) chloride (LaCl₃ · 7H₂O) in a 600 ml beaker with water and transfer the solution into a 1 000 ml one-mark volumetric flask. Dilute to the mark with water and mix.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-