



National Standards Authority of Ireland

IRISH STANDARD

I.S. EN 13817:2004

ICS 97.150
97.220.10

National Standards
Authority of Ireland
Dublin 9
Ireland

Tel: (01) 807 3800
Fax: (01) 807 3838

**SURFACES FOR SPORTS AREAS -
PROCEDURE FOR ACCELERATED AGEING
BY
EXPOSURE TO HOT AIR**

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland
and comes into effect on:
November 26, 2004*

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2004

Price Code D

Údarás um Chaighdeán Náisiúnta na hÉireann

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13817

October 2004

ICS 97.150; 97.220.10

English version

**Surfaces for sports areas - Procedure for accelerated ageing by
exposure to hot air**

Sols sportifs - Méthode de vieillissement accéléré par
exposition à l'air chaud

Sportböden - Verfahren der beschleunigten Alterung durch
Beanspruchung mit heißer Luft

This European Standard was approved by CEN on 29 July 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Principle.....	4
4 Apparatus	4
5 Test pieces	4
6 Procedure	4
7 Comparison tests.....	5
8 Calculation and expression of results.....	5
9 Test report	5

Foreword

This document (EN 13817:2004) has been prepared by Technical Committee CEN/TC 217 “Surfaces for sports areas”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2005, and conflicting national standards shall be withdrawn at the latest by April 2005.

It is one of two standards for procedures for ageing surfaces for sports areas. The other standard in this series has the following title:

EN 13744, *Surfaces for sports areas — Procedures for accelerated ageing by immersion in hot water*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 13817:2004 (E)

1 Scope

This document describes a procedure for subjecting test pieces taken from surfaces for sports areas to accelerated ageing by exposure to hot air in the laboratory. Test pieces are aged to permit a comparison of their physical characteristics before and after ageing in accordance with European Standard test methods for surfaces for sports areas.

This method is suitable for ageing all types of sports surfaces, except for wooden surfaces, using test pieces in the laboratory, but is primarily intended for ageing polymeric surfaces. The procedure allows a measure of the effect on the physical characteristics of the sports surface due to exposure to hot air to be made.

NOTE Results on materials which exhibit temporary changes in properties due to drying should be interpreted with caution.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 188:1998, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

3 Principle

Test pieces are exposed to air at an elevated temperature to permit selected physical characteristics of the surface to be assessed before and after test.

4 Apparatus

4.1 Air circulating oven, as described in ISO 188:1998, 3.2.2.

5 Test pieces

Select, prepare and condition the test piece(s) in accordance with the appropriate method of test.

Test pieces shall be such that no mechanical, chemical or heat treatment will be required after their removal from the oven.

Any material used for marking test pieces shall not be applied in any critical area of the test piece and shall not damage the surface or be destroyed during ageing.

NOTE Wherever possible, marking should be carried out after ageing of the test piece.

6 Procedure

Place the test pieces in the oven (4.1) after it has been pre-heated to a temperature of $(70 \pm 2) ^\circ\text{C}$. The test pieces shall be stationary, free from strain and freely exposed to air on all sides and not exposed to light.

Leave the test pieces in the oven for (336 ± 2) h.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-