

Irish Standard I.S. EN 15690-2:2009

Copper and copper alloys -Determination of iron content - Part 2: Flame atomic absorption spectrometric method (FAAS)

© NSAI 2009 No copying without NSAI permission except as permitted by copyright law.

Incorporating amendments/corrigenda issued since publication:

This document replaces:	<i>This document is based on:</i> EN 15690-2:2009	<i>Publish</i> 11 Feb	<i>ed:</i> ruary, 2009	
This document was published under the authority of the NSAI and comes into effect on: 9 April, 2009			ICS number: 77.040.30 77.120.30	
NSAI 1 Swift Square, T +3 Northwood, Santry F +3 Dublin 9 E st W N	Sales: 53 1 807 3800 T +353 1 8 53 1 807 3838 F +353 1 8 andards@nsai.ie W standar SAl.ie	57 6730 57 6729 ds.ie	Price Code: F	
Údarás um Chaighdeáin Náisiúnta na hÉireann				

EUROPEAN STANDARD NORME EUROPÉENNE

EN 15690-2

EUROPÄISCHE NORM

February 2009

ICS 77.040.30; 77.120.30

English Version

Copper and copper alloys - Determination of iron content - Part 2: Flame atomic absorption spectrometric method (FAAS)

Cuivre et alliages de cuivre - Dosage du fer - Partie 2 : Méthode par spectrométrie d'absorption atomique dans la flamme (SAAF) Kupfer und Kupferlegierungen - Bestimmung des Eisengehaltes - Teil 2: Flammenatomabsorptionsspektrometrisches Verfahren (FAAS)

This European Standard was approved by CEN on 26 December 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

© 2009 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN 15690-2:2009: E

Contents

Page

Forewo	rd	3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Reagents and materials	4
5	Apparatus	6
6	Sampling	6
7	Procedure	6
8	Expression of results	10
9	Precision	11
10	Test report	12
Bibliog	raphy	13

Foreword

This document (EN 15690-2:2009) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2009, and conflicting national standards shall be withdrawn at the latest by August 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 "Methods of analysis" to prepare the following standard:

EN 15690-2, Copper and copper alloys — Determination of iron content — Part 2: Flame atomic absorption spectrometric method (FAAS)

This is one of two Parts of the standard for the determination of iron content in copper and copper alloys. The other Part is:

EN 15690-1, Copper and copper alloys — Determination of iron content — Part 1: Titrimetric method

Part 1 will be the subject of future work.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This Part of this European Standard specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the iron content of copper and copper alloys in the form of castings or unwrought or wrought products.

The method is applicable to products having iron mass fractions between 0,005 % and 5,0 %.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products

ISO 1811-2, Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings

NOTE Informative references to documents used in the preparation of this standard, and cited at the appropriate places in the text, are listed in the Bibliography.

3 Principle

Dissolution of a test portion in a hydrochloric and nitric acid mixture followed, after suitable dilution and the addition of lanthanum chloride to mask the effect of interfering ions, by aspiration of the test solution into an air/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 248,3 nm or the 372,0 nm line emitted by an iron hollow-cathode lamp.

4 Reagents and materials

4.1 General

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

Avoid any contamination with iron during the mechanical preparation steps.

4.2 Hydrochloric acid, HCl (ρ = 1,19 g/ml)

4.3 Nitric acid, HNO₃ (*ρ* = 1,40 g/ml)

4.4 Nitric acid, (1 + 1)

Add 500 ml of nitric acid (4.3) into 500 ml of water.

4.5 Hydrofluoric acid, HF (ρ = 1,13 g/ml)

WARNING — Hydrofluoric acid is a hazardous substance. Care shall be taken and it shall be used under an efficient fume hood.



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation