



National Standards Authority of Ireland

STANDARD

I.S. EN 820-3:2004

ICS 81.060.30

**ADVANCED TECHNICAL CERAMICS -
METHODS OF TESTING MONOLITHIC
CERAMICS - THERMOMECHANICAL
PROPERTIES - PART 3: DETERMINATION OF
RESISTANCE TO THERMAL SHOCK BY
WATER QUENCHING**

National Standards
Authority of Ireland
Dublin 9
Ireland

Tel: (01) 807 3800
Fax: (01) 807 3838

*This Irish Standard was
published under the
authority of the National
Standards Authority of
Ireland
and comes into effect on:
November 12, 2004*

**NO COPYING WITHOUT NSAI
PERMISSION EXCEPT AS
PERMITTED BY COPYRIGHT
LAW**

© NSAI 2004

Price Code F

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 820-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2004

ICS 81.060.30

Supersedes ENV 820-3:1993

English version

**Advanced technical ceramics - Methods of testing monolithic
ceramics - Thermomechanical properties - Part 3: Determination
of resistance to thermal shock by water quenching**

Céramiques techniques avancées - Céramiques
monolithiques - Propriétés thermomécaniques - Partie 3:
Détermination de la résistance au choc thermique par la
méthode de trempe à l'eau

Hochleistungskeramik - Prüfverfahren für monolithische
Keramik - Thermomechanische Eigenschaften - Teil 3:
Bestimmung der Thermoschockbeständigkeit mit dem
Wasserabschreckversuch

This European Standard was approved by CEN on 24 June 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Apparatus	5
5 Test pieces	5
6 Procedure	6
7 Test report	7
Annex A (informative) Introduction to thermal shock behaviour	9
Bibliography	12

Foreword

This document (EN 820-3:2004) has been prepared by Technical Committee CEN/TC 184 “Advanced technical ceramics”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2005, and conflicting national standards shall be withdrawn at the latest by February 2005.

This document supersedes ENV 820-3:1993.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

EN 820 *Advanced technical ceramics — Methods of testing monolithic ceramics — Thermomechanical properties* consists of five Parts:

- Part 1: *Determination of flexural strength at elevated temperatures*
- Part 2: *Determination of self-loaded deformation*
- Part 3: *Determination of resistance to thermal shock by water quenching*
- Part 4: *Determination of flexural creep deformation at elevated temperatures*
- Part 5: *Determination of elastic moduli at elevated temperatures*

Part 4 is a European Prestandard (ENV) and Part 5 is a Technical Specification (CEN/TS).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 820-3:2004 (E)

1 Scope

This Part of EN 820 specifies the principles of thermal shock testing, and provides a general method for conducting thermal shock tests by quenching into water for both test pieces and components by quenching into water.

NOTE This document does not cover thermal stress developed as a result of steady inhomogeneous temperature within a ceramic body or of thermal expansion mismatch between joined bodies.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 623-1, *Advanced technical ceramics — Monolithic ceramics — General and textural properties — Part 1: Determination of the presence of defects by dye penetration tests*

EN 843-1, *Advanced technical ceramics — Monolithic ceramics — Mechanical properties at room temperatures — Part 1: Determination of flexural strength*

EN 60584-1, *Thermocouples — Part 1: Reference tables (IEC 60584-1:1995)*

EN 60584-2, *Thermocouples — Part 2: Tolerances (IEC 60584-2:1982)*

EN 60672-2, *Ceramic and glass insulating materials — Part 2: Methods of test (IEC 60672-2:1999)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:1999)*

3 Principle

A set of test pieces is heated to a given temperature, and then quickly and smoothly transferred to a water bath. The test pieces or components are then inspected for cracks or other damage, either by an appropriate mechanical test to establish whether weakening has occurred, or by using a dye penetrant to detect the presence of cracks (see EN 623-1).

NOTE 1 Dye penetration tests are unsatisfactory for porous or highly microcracked materials.

This thermal shock test determines whether a material or component has a capability of withstanding a water quench through a large temperature difference from high temperature without failure, under the conditions of heat transfer prevailing in such a quenching environment, and for the given geometry and section thickness.

NOTE 2 By agreement between parties an alternative quenching medium may be employed. Details of the medium employed should be incorporated in the report.

If the test pieces for the quench test are available as regular bar shapes, then the inspection after quenching with the mechanical test, such as a flexural test, may be preferred, as it enables the onset of loss of strength with increasing initial temperature to be determined. Sets of at least five test pieces are heated to a series of temperatures above that of the quenching bath, quenched, dried and subjected to a short-term strength test. The temperature drop corresponding to that at which a sudden loss of strength occurs is termed the critical temperature difference, ΔT_c . This temperature difference can be estimated using the first kind of thermal shock parameter, R (see A.3.2), to which it is numerically equal at an infinite rate of heat transfer.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-