This is a free page sample. Access the full version online.



Irish Standard I.S. EN 12390-5:2009

Testing hardened concrete - Part 5: Flexural strength of test specimens

© NSAI 2009 No copying without NSAI permission except as permitted by copyright law.

Incorporating amendments/corrigenda issued since publication:

<i>This document replaces:</i> I.S. EN 12390-5:2000	<i>This document is b</i> EN 12390-5:2009 EN 12390-5:2000	ased on:	<i>Publish</i> 11 Feb 2 Febru	<i>ed:</i> ruary, 2009 Jary, 2001	
This document was published under the authority of the NSA and comes into effect on: 20 March, 2009	I			ICS number: 91.100.30	
NSAI 1 Swift Square, T Northwood, Santry F Dublin 9 E V	+353 1 807 3800 +353 1 807 3838 standards@nsai.ie / NSAI.ie	Sales: 53 1 807 3800 T +353 1 857 6730 53 1 807 3838 F +353 1 857 6729 Indards@nsai.ie W standards.ie SAl.ie		Price Code: F	
Údarás um Chaighdeáin Náisiúnta na hÉireann					

EUROPEAN STANDARD

EN 12390-5

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2009

ICS 91.100.30

Supersedes EN 12390-5:2000

English Version

Testing hardened concrete - Part 5: Flexural strength of test specimens

Essai pour béton durci - Partie 5: Résistance à la flexion sur éprouvettes Prüfung von Festbeton - Teil 5: Biegezugfestigkeit von Probekörpern

This European Standard was approved by CEN on 27 December 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. EN 12390-5:2009: E

EN 12390-5:2009 (E)

Contents

Page

Forewo	ord	.3
1	Scope	.5
2	Normative references	.5
3	Principle	.5
4	Apparatus	.5
5	Test specimens	.6
6	Procedures	.6
7	Expression of results	.7
8	Test report	.7
9	Precision	.8
Annex	A (normative) Loading by a centre-point load	10

Foreword

This document (EN 12390-5:2009) has been prepared by Technical Committee CEN/TC 104 "Concrete and related products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2009, and conflicting national standards shall be withdrawn at the latest by August 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12390-5:2000.

It is recognized good practice to include measurement of density prior to the determination of flexural strength, as a check on compaction of the concrete.

The two-point method of loading has been taken as the reference method, but the use of centre-point loading has been included as a normative annex. An inter-comparison of the two-point and the centre-point methods has been made as part of a test programme, part-funded by the EC under the Measurement and Testing Programme, contract MAT I-CT-94-CO43. The centre-point method gave results which were consistently 13 % higher than those from the two-point method.

This standard is one of a series concerned with testing concrete.

The series EN 12390 includes the following parts:

EN 12390 Testing hardened concrete –

- Part 1: Shape, dimensions and other requirements for specimens and moulds;
- Part 2: Making and curing specimens for strength tests;
- Part 3: Compressive strength of test specimens;
- Part 4: Compressive strength Specification for testing machines;
- Part 5: Flexural strength of test specimens;
- Part 6: Tensile splitting strength of test specimens;
- Part 7: Density of hardened concrete;
- Part 8: Depth of penetration of water under pressure.

The following amendments have been made to the 2000-10 edition of this standard:

editorial revision

selected loading rate to be applied after the initial (not exceeding approx 20% of the anticipated failure load)

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia,

Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a method for the determination of the flexural strength of specimens of hardened concrete.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12350-1, Testing fresh concrete – Part 1: Sampling

EN 12390-1:2000, Testing hardened concrete – Part 1: Shape, dimensions and other requirements for test specimens and moulds

EN 12390-2, Testing hardened concrete - Part 2: Making and curing specimens for strength tests

EN 12390-4, Testing hardened concrete – Part 4: Compressive strength – Specification for testing machines

3 Principle

Prismatic specimens are subject to a bending moment by the application of load through upper and lower rollers. The maximum load sustained is recorded and the flexural strength is calculated.

4 Apparatus

4.1 Testing machine

The test shall be carried out using a testing machine conforming to EN 12390-4.

4.2 Force application

The device for applying loads (see Figure 1) shall consist of:

- 1) two supporting rollers;
- 2) two upper rollers carried by an articulated cross member, which divides the load applied by the machine equally between the two rollers.

All rollers shall be manufactured from steel and shall have a circular cross-section with a diameter of 20 mm to 40 mm. They shall be at least 10 mm longer than the width of the test specimen.

Three rollers, including the two upper ones, shall be capable of rotating freely around their axis and of being inclined in a plane normal to the longitudinal axis of the test specimen.

The distance, I, between the outer rollers (i.e. the span) shall be equal to 3d, where d is the width of the specimen. The distance between the inner rollers shall be equal to d. The inner rollers shall be equally spaced between the outer rollers as shown in Figure 1. All rollers shall be adjusted to the positions illustrated in Figure 1 to an accuracy of \pm 2,0 mm.



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation