



NSAI
Standards

Irish Standard
I.S. EN ISO 8249:2000

Welding – Determination of Ferrite Number (FN) in austenitic and duplex ferritic-austenitic Cr-Ni stainless steel weld metals (ISO 8249:200)

I.S. EN ISO 8249:2000

Incorporating amendments/corrigenda issued since publication:

<i>This document replaces:</i>	<i>This document is based on:</i> EN ISO 8249:2000	<i>Published:</i>
This document was published under the authority of the NSAI and comes into effect on: 18 August, 2000		ICS number: 25.160
NSAI 1 Swift Square, Northwood, Santry Dublin 9	T +353 1 807 3800 F +353 1 807 3838 E standards@nsai.ie W NSAI.ie	Sales: T +353 1 857 6730 F +353 1 857 6729 W standards.ie
Údarás um Chaighdeáin Náisiúnta na hÉireann		

ICS 25.160

English version

Welding - Determination of Ferrite Number (FN) in austenitic and duplex ferritic-austenitic Cr-Ni stainless steel weld metals (ISO 8249:2000)

Soudage - Détermination de l'Indice de Ferrite (FN) dans le métal fondu en acier inoxydable austénitique et duplex ferritique-austénitique au chrome-nickel (ISO 8249:2000)

Bestimmung der Ferrit-Nummer (FN) in austenitischem und ferritisch-austenitischem (Duplex-) Schweißgut von Cr-Ni-Stählen (ISO 8249:2000)

This European Standard was approved by CEN on 13 April 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

I.S. EN ISO 8249:2000

Page 2
EN ISO 8249:2000

Foreword

The text of the International Standard ISO 8249:2000 has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2000, and conflicting national standards shall be withdrawn at the latest by November 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

NOTE FROM CEN/CS: The foreword is susceptible to be amended on reception of the German language version. The confirmed or amended foreword, and when appropriate, the normative annex ZA for the references to international publications with their relevant European publications will be circulated with the German version.

Endorsement notice

The text of the International Standard ISO 8249:2000 was approved by CEN as a European Standard without any modification.

I.S. EN ISO 8249:2000

INTERNATIONAL STANDARD

ISO 8249

Second edition
2000-05-01

Welding — Determination of Ferrite Number (FN) in austenitic and duplex ferritic-austenitic Cr-Ni stainless steel weld metals

Soudage — Détermination de l'Indice de Ferrite (FN) dans le métal fondu en acier inoxydable austénitique et duplex ferritique-austénitique au chrome-nickel



Reference number
ISO 8249:2000(E)

© ISO 2000

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative reference	1
3 Principle	1
4 Calibration	2
5 Standard method for covered electrode test pads	4
6 Standard methods for test pads of other processes and for production welds	6
7 Other methods	7
8 Procedures used to prepare secondary standards for delta ferrite in austenitic stainless steel weld metal	8
Annex A (informative) Manufacture of secondary standards by strip cladding	9
Annex B (informative) Manufacture of secondary standards by centrifugal chill casting	18
Bibliography	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 8249 was prepared in collaboration with the International Institute of Welding which has been approved by the ISO Council as an international standardizing body in the field of welding.

This second edition cancels and replaces the first edition (ISO 8249:1985), which has been technically revised.

Annexes A and B of this International Standard are for information only.

Introduction

At present, there is no universal opinion concerning the best experimental method that gives an absolute measurement of the amount of ferrite in a weld metal, either destructively or non-destructively. This situation has led to the development and use, internationally, of the concept of a "Ferrite Number" or FN. A Ferrite Number is a description of the ferrite content of a weld metal determined using a standardized procedure. Such procedures are laid down in this International Standard. The Ferrite Number of a weld metal has been considered approximately equivalent to the percentage ferrite content, particularly at low FN values. More recent information suggests that the FN may overstate the volume percent ferrite at higher FN by a factor in the order of 1,3 to 1,5, which depends to a certain extent upon the actual composition of the alloy in question.

Although other methods are available for determining the Ferrite Number, the standardized measuring procedure, laid down in this International Standard, is based on assessing the tear-off force needed to pull the weld metal sample from a magnet of defined strength and size. The relationship between tear-off force and FN is obtained using primary standards consisting of a non-magnetic coating of specified thickness on a magnetic base. Each non-magnetic coating thickness is assigned an FN value.

The ferrite content determined by this method is arbitrary and is not necessarily the true or absolute ferrite content. In recognition of this fact, the term "Ferrite Number" (FN) shall be used instead of "ferrite per cent" when quoting a ferrite content determined by this method. To help convey the message that this standardized calibration procedure has been used, the terms "Ferrite Number" and "FN" are capitalized as proper nouns.

Welding — Determination of Ferrite Number (FN) in austenitic and duplex ferritic-austenitic Cr-Ni stainless steel weld metals

1 Scope

This International Standard specifies the method and apparatus for

- the measurement of the delta ferrite content, expressed as Ferrite Number (FN), in largely austenitic and duplex ferritic-austenitic stainless steel¹⁾ weld metal through the attractive force between a weld metal sample and a standard permanent magnet;
- the preparation and measurement of standard pads for manual metal arc covered electrodes. The general method is also recommended for the ferrite measurement of production welds and for weld metal from other processes, such as gas tungsten arc welding, gas shielded metal arc welding and submerged arc welding (in these cases, the way of producing the pad should be defined);
- the calibration of other instruments to measure FN.

The method laid down in this International Standard is intended for use on weld metals in the as-welded state and on weld metals after thermal treatments causing complete or partial transformation of ferrite to any non-magnetic phase. Austenitizing thermal treatments which alter the size and shape of the ferrite will change the magnetic response of the ferrite.

The method is not intended for measurement of the ferrite content of cast, forged or wrought austenitic or duplex ferritic-austenitic steel samples.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, this publication do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO/TR 15510:1997, *Stainless steels — Chemical composition*.

3 Principle

The measurement of the ferrite content of largely austenitic stainless steel weld metal through the attractive force between a weld metal sample and a permanent magnet is based upon the fact that the attractive force between a two-phase (or multiphase) sample containing one ferromagnetic phase and one (or more) non-ferromagnetic phase(s) increases as the content of the ferromagnetic phase increases. In largely austenitic and duplex ferritic-austenitic stainless steel weld metal, ferrite is magnetic, whereas austenite, carbides, sigma phase and inclusions are non-ferromagnetic.

1) The term "austenitic-ferritic (duplex) stainless steel" is sometimes applied in place of "duplex ferritic-austenitic stainless steel".

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-