



NSAI
Standards

Irish Standard
I.S. EN ISO 439:2010

Steel and iron - Determination of total silicon content - Gravimetric method (ISO 439:1994)

I.S. EN ISO 439:2010

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

| | | |
|---|--|---|
| <i>This document replaces:</i> | <i>This document is based on:</i> EN ISO 439:2010 | <i>Published:</i> 21 April, 2010 |
| This document was published under the authority of the NSAI and comes into effect on: 13 May, 2010 | | ICS number: 77.080.01 |
| NSAI 1 Swift Square, Northwood, Santry Dublin 9 | T +353 1 807 3800 F +353 1 807 3838 E standards@nsai.ie W NSAI.ie | Sales: T +353 1 857 6730 F +353 1 857 6729 W standards.ie |
| Údarás um Chaighdeáin Náisiúnta na hÉireann | | |

ICS 77.080.01

English Version

**Steel and iron - Determination of total silicon content -
Gravimetric method (ISO 439:1994)**

Aciers et fontes - Dosage du silicium total - Méthode
gravimétrique (ISO 439:1994)

Stahl und Eisen - Bestimmung des Gesamtsiliziumgehaltes
- Gravimetrisches Verfahren (ISO 439:1994)

This European Standard was approved by CEN on 18 March 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

| | |
|----------------------|----------|
| Foreword..... | 3 |
|----------------------|----------|

Foreword

The text of ISO 439:1994 has been prepared by Technical Committee ISO/TC 17 “Steel” of the International Organization for Standardization (ISO) and has been taken over as EN ISO 439:2010 by Technical Committee ECISS/TC 102 “Methods of chemical analysis for iron and steel” the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2010, and conflicting national standards shall be withdrawn at the latest by October 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 439:1994 has been approved by CEN as a EN ISO 439:2010 without any modification.

This page is intentionally left BLANK.

INTERNATIONAL STANDARD

ISO
439

Second edition
1994-04-01

Steel and iron — Determination of total silicon content — Gravimetric method

Aciers et fontes — Dosage du silicium total — Méthode gravimétrique



Reference number
ISO 439:1994(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 439 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*.

This second edition cancels and replaces the first edition (ISO 439:1982), which has been technically revised.

Annexes A and B of this International Standard are for information only.

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Steel and iron — Determination of total silicon content — Gravimetric method

1 Scope

This International Standard specifies a gravimetric method for the determination of the total silicon content in steel and iron.

The method is applicable to silicon contents between 0,10 % (*m/m*) and 5,0 % (*m/m*) (see note 1).

NOTE 1 For samples containing molybdenum, niobium, tantalum, titanium, tungsten, zirconium or high levels of chromium, the results are less precise than for unalloyed steels (see annex A).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 377-2:1989, *Selection and preparation of samples and test pieces of wrought steels — Part 2: Samples for the determination of the chemical composition*.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 1042:1983, *Laboratory glassware — One-mark volumetric flasks*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 5725:1986, *Precision of test methods — Determination of repeatability and reproducibility for a standard test method by inter-laboratory tests*.

3 Principle

Attack of a test portion by hydrochloric and nitric acids.

Conversion of acid-soluble silicon compounds to hydrated silicon dioxide by evaporation with perchloric acid until white fumes appear. Filtration of the hydrated silicon dioxide and acid-insoluble silicon compounds, ignition to form impure silicon dioxide and then weighing.

Treatment of the ignited residue with hydrofluoric and sulfuric acids, followed by ignition and weighing.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and grade 2 water as specified in ISO 3696.

4.1 Hydrochloric acid, ρ about 1,19 g/ml.

4.2 Hydrochloric acid, ρ about 1,19 g/ml, diluted 1 + 1.

4.3 Hydrochloric acid, ρ about 1,19 g/ml, diluted 1 + 19.

4.4 Nitric acid, ρ about 1,40 g/ml, diluted 3 + 1.

4.5 Hydrofluoric acid, ρ about 1,14 g/ml.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-