



**NSAI**  
Standards

Irish Standard  
I.S. EN ISO 13680:2010

Petroleum and natural gas industries -  
Corrosion-resistant alloy seamless tubes  
for use as casing, tubing and coupling  
stock - Technical delivery conditions (ISO  
13680:2010)

## I.S. EN ISO 13680:2010

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

### The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

<i>This document replaces:</i> EN ISO 13680:2008	<i>This document is based on:</i> EN ISO 13680:2010 EN ISO 13680:2008	<i>Published:</i> 1 September, 2010 15 October, 2008
This document was published under the authority of the NSAI and comes into effect on: 21 September, 2010		ICS number: 75.180.10 77.140.75
<b>NSAI</b> 1 Swift Square, Northwood, Santry Dublin 9	T +353 1 807 3800 F +353 1 807 3838 E standards@nsai.ie W NSAI.ie	<b>Sales:</b> T +353 1 857 6730 F +353 1 857 6729 W standards.ie
Údarás um Chaighdeáin Náisiúnta na hÉireann		

English Version

**Petroleum and natural gas industries - Corrosion-resistant alloy  
seamless tubes for use as casing, tubing and coupling stock -  
Technical delivery conditions (ISO 13680:2010)**

Industries du pétrole et du gaz naturel - Tubes sans  
soudure en acier allié résistant à la corrosion utilisés  
comme tubes de cuvelage, tubes de production et tubes-  
ébauches pour manchons - Conditions techniques de  
livraison (ISO 13680:2010)

Erdöl- und Erdgasindustrie - Nahtlose Rohre aus  
korrosionsbeständigen Legierungen zur Verwendung als  
Futter- oder Steigrohre sowie Muffenvorrohre - Technische  
Lieferbedingungen (ISO 13680:2010)

This European Standard was approved by CEN on 30 August 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

**Contents**

Page

**Foreword.....3**

## **Foreword**

This document (EN ISO 13680:2010) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011, and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 13680:2008.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### **Endorsement notice**

The text of ISO 13680:2010 has been approved by CEN as a EN ISO 13680:2010 without any modification.

*This page is intentionally left BLANK.*

I.S. EN ISO 13680:2010  
**INTERNATIONAL  
STANDARD**

**ISO  
13680**

Third edition  
2010-09-01

---

---

**Petroleum and natural gas industries —  
Corrosion-resistant alloy seamless tubes  
for use as casing, tubing and coupling  
stock — Technical delivery conditions**

*Industries du pétrole et du gaz naturel — Tubes sans soudure en acier allié résistant à la corrosion utilisés comme tubes de cuvelage, tubes de production et tubes-ébauches pour manchons — Conditions techniques de livraison*



Reference number  
ISO 13680:2010(E)

© ISO 2010

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland



# Contents

Page

Foreword .....	v
Introduction.....	vi
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Conformance</b> .....	<b>2</b>
2.1 <b>Dual normative references</b> .....	<b>2</b>
2.2 <b>Units of measurement</b> .....	<b>2</b>
<b>3</b> <b>Normative references</b> .....	<b>2</b>
<b>4</b> <b>Terms, abbreviated terms, symbols and definitions</b> .....	<b>4</b>
4.1 <b>Terms and definitions</b> .....	<b>4</b>
4.2 <b>Symbols</b> .....	<b>7</b>
4.3 <b>Abbreviated terms</b> .....	<b>7</b>
<b>5</b> <b>Information to be supplied by the purchaser</b> .....	<b>8</b>
<b>6</b> <b>Manufacturing process</b> .....	<b>9</b>
6.1 <b>Manufacturing of corrosion-resistant alloys</b> .....	<b>9</b>
6.2 <b>Product manufacturing process</b> .....	<b>9</b>
6.3 <b>Pipe end sizing</b> .....	<b>10</b>
6.4 <b>Straightening</b> .....	<b>10</b>
6.5 <b>Process requiring validation</b> .....	<b>10</b>
6.6 <b>Traceability</b> .....	<b>10</b>
<b>7</b> <b>Material requirements</b> .....	<b>11</b>
7.1 <b>Chemical composition</b> .....	<b>11</b>
7.2 <b>Tensile properties</b> .....	<b>11</b>
7.3 <b>Hardness properties</b> .....	<b>11</b>
7.4 <b>Charpy V-notch test properties — General requirements</b> .....	<b>11</b>
7.5 <b>Charpy V-notch — Absorbed energy requirements for coupling stock — All grades</b> .....	<b>12</b>
7.6 <b>Charpy V-notch — Absorbed energy requirements for pipe — All grades</b> .....	<b>13</b>
7.7 <b>Flattening requirements</b> .....	<b>14</b>
7.8 <b>Corrosion properties</b> .....	<b>15</b>
7.9 <b>Microstructure properties</b> .....	<b>15</b>
7.10 <b>Surface condition</b> .....	<b>15</b>
7.11 <b>Defects</b> .....	<b>15</b>
7.12 <b>Hydrostatic test</b> .....	<b>16</b>
<b>8</b> <b>Dimensions, masses and tolerances</b> .....	<b>16</b>
8.1 <b>Outside diameter, wall thickness and mass</b> .....	<b>16</b>
8.2 <b>Length</b> .....	<b>17</b>
8.3 <b>Tolerances</b> .....	<b>17</b>
8.4 <b>Product ends</b> .....	<b>17</b>
<b>9</b> <b>Inspection and testing</b> .....	<b>17</b>
9.1 <b>Test equipment</b> .....	<b>17</b>
9.2 <b>Type and frequency of tests</b> .....	<b>18</b>
9.3 <b>Testing of chemical composition</b> .....	<b>18</b>
9.4 <b>Testing of mechanical characteristics</b> .....	<b>19</b>
9.5 <b>Tensile test</b> .....	<b>19</b>
9.6 <b>Hardness test</b> .....	<b>20</b>
9.7 <b>Impact or flattening test</b> .....	<b>20</b>
9.8 <b>Microstructural examination</b> .....	<b>23</b>
9.9 <b>Dimensional testing</b> .....	<b>23</b>

9.10	Drift test .....	24
9.11	Length .....	24
9.12	Straightness .....	24
9.13	Mass determination .....	24
9.14	Hydrostatic test.....	25
9.15	Visual inspection .....	25
9.16	Non-destructive examination .....	26
10	Surface treatment .....	31
10.1	Group 1 .....	31
10.2	Groups 2, 3 and 4.....	31
11	Marking .....	31
11.1	General.....	31
11.2	Marking on the product.....	32
11.3	Date of manufacture .....	33
12	Surface protection — Group 1.....	33
13	Documents .....	33
13.1	Electronic media .....	33
13.2	Retention of records.....	34
13.3	Test certificates.....	34
14	Handling, packaging and storage .....	35
14.1	General.....	35
14.2	Handling.....	35
14.3	Packaging .....	35
14.4	Storage.....	35
Annex A	(normative) Tables in SI units .....	36
Annex B	(normative) Figures in SI (USC) Units .....	56
Annex C	(normative) Tables in USC units .....	61
Annex D	(normative) Purchaser inspection .....	81
Annex E	(normative) Cleanliness requirements .....	82
Annex F	(informative) Use of the API Monogram by Licensees .....	84
Annex G	(normative) Product specification level 2 (PSL-2) .....	87
Bibliography	.....	89

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13680 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

This third edition cancels and replaces the second edition (ISO 13680:2008), of which it constitutes a minor revision, with changes to 4.1.2; 4.1.14; 4.1.16; 4.1.19; 5.2 p) and 5.2 q); 6.1; 6.5; 6.6; 7.2; 7.7; 7.11.1 and 7.11.2; 9.3.3; 9.8.2; 9.8.3; 9.16.7; 9.16.13; 9.16.14; 11.2.4; 13.3; and Tables A.1, A.27, A.28, C.2, C.15, C.18, C.27 and C.28.

It is the intent of ISO/TC 67 that the second and third edition of ISO 13680 both be applicable, at the option of the purchaser, for a period of six months from the first day of the calendar quarter immediately following the date of publication of this third edition, after which period the second edition will no longer be applicable.

## **Introduction**

It is necessary that users of this International Standard be aware that further or differing requirements can be needed for individual applications. This International Standard is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is offered, it is the responsibility of the vendor to identify any variations from this International Standard and provide details.

This International Standard includes provisions of various nature. These are identified by the use of certain verbal forms:

SHALL is used to indicate that a provision is **MANDATORY**;

SHOULD is used to indicate that a provision is not mandatory, but **RECOMMENDED** as good practice;

MAY is used to indicate that a provision is **OPTIONAL**.

# Petroleum and natural gas industries — Corrosion-resistant alloy seamless tubes for use as casing, tubing and coupling stock — Technical delivery conditions

**WARNING** — It is the purchaser's responsibility to specify the product specification level (PSL), corrosion-resistant alloy (CRA) group, category, grade, delivery conditions and any other requirements in addition to those specified herewith to ensure that the product is adequate for the intended service environment. ISO 15156 (all parts) or NACE MR0175/ISO 15156 should be considered when making specific requirements for H<sub>2</sub>S-containing environment; see Annex G.

## 1 Scope

This International Standard specifies the technical delivery conditions for corrosion-resistant alloy seamless tubulars for casing, tubing and coupling stock for two product specification levels:

- PSL-1, which is the basis of this International Standard;
- PSL-2, which provides additional requirements for a product that is intended to be both corrosion resistant and cracking resistant for the environments and qualification method specified in ISO 15156-3 and Annex G of this International Standard.

At the option of the manufacturer, PSL-2 products can be provided in lieu of PSL-1.

NOTE 1 The corrosion-resistant alloys included in this International Standard are special alloys in accordance with ISO 4948-1 and ISO 4948-2.

This International Standard is applicable to the following four groups of product:

- a) group 1, which is composed of stainless alloys with a martensitic or martensitic/ferritic structure;
- b) group 2, which is composed of stainless alloys with a ferritic-austenitic structure, such as duplex and super-duplex stainless alloy;
- c) group 3, which is composed of stainless alloys with an austenitic structure (iron base);
- d) group 4, which is composed of nickel-based alloys with an austenitic structure (nickel base).

This International Standard contains no provisions relating to the connection of individual lengths of pipe.

NOTE 2 The connection or joining method can influence the corrosion performance of the materials specified in this International Standard.

NOTE 3 It is necessary to recognize that not all PSL-1 categories and grades can be made cracking resistant in accordance with ISO 15156-3 and are, therefore, not included in PSL-2.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-