



NSAI
Standards

Irish Standard
I.S. EN ISO 7783:2011

Paints and varnishes - Determination of water-vapour transmission properties - Cup method (ISO 7783:2011)

I.S. EN ISO 7783:2011

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:

EN ISO 7783-2:1999

EN ISO 7783-1:1999

This document is based on:

EN ISO 7783:2011

EN ISO 7783-2:1999

Published:

17 November, 2011

15 March, 1999

This document was published under the authority of the NSAI and comes into effect on:

17 November, 2011

ICS number:

87.040

NSAI

1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800

F +353 1 807 3838

E standards@nsai.ie

W NSAI.ie

Sales:

T +353 1 857 6730

F +353 1 857 6729

W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

Paints and varnishes - Determination of water-vapour transmission properties - Cup method (ISO 7783:2011)

Peintures et vernis - Détermination des propriétés de transmission de la vapeur d'eau - Méthode de la coupelle (ISO 7783:2011)

Beschichtungsstoffe - Bestimmung der Wasserdampfdurchlässigkeit - Schalenverfahren (ISO 7783:2011)

This European Standard was approved by CEN on 21 November 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

Foreword

This document (EN ISO 7783:2011) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2012, and conflicting national standards shall be withdrawn at the latest by May 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 7783-1:1999, EN ISO 7783-2:1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 7783:2011 has been approved by CEN as a EN ISO 7783:2011 without any modification.

This page is intentionally left BLANK.

I.S. EN ISO 7783:2011
**INTERNATIONAL
STANDARD**

**ISO
7783**

First edition
2011-11-01

**Paints and varnishes — Determination of
water-vapour transmission properties —
Cup method**

*Peintures et vernis — Détermination des propriétés de transmission de
la vapeur d'eau — Méthode de la coupelle*



Reference number
ISO 7783:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Apparatus and materials	3
5.1 Substrate for non-self-supporting coatings	3
5.2 Test cup	3
5.3 Ammonium dihydrogen phosphate (NH ₄ H ₂ PO ₄) solution for wet-cup method	3
5.4 Desiccant for dry-cup method	3
5.5 Sealing material	4
5.6 Test enclosure	4
5.7 Balance	4
6 Preparation for the test	4
6.1 Sampling of coating material	4
6.2 Preparation of test pieces	4
6.3 Determination of the thickness of the coating	5
6.4 Preparation of the test assemblies	6
7 Procedure	6
8 Expression of results	7
8.1 Water-vapour transmission rate, V , of self-supporting coatings	7
8.2 Water-vapour transmission rate, V , of non-self-supporting coatings	7
8.3 Water-vapour diffusion-equivalent air layer thickness, s_d	9
8.4 Water-vapour resistance factor, μ	9
9 Precision	10
9.1 Repeatability, (r)	10
9.2 Reproducibility, (R)	10
10 Test report	10
Annex A (informative) Derivation of Equation (8) in Subclause 8.3 for the calculation of the water-vapour diffusion-equivalent air layer thickness, s_d	12
Annex B (normative) Use of molten wax for sealing the test assembly	14
Bibliography	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7783 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This first edition of ISO 7783 cancels and replaces ISO 7783-1:1996 and ISO 7783-2:1999, which have been merged and technically revised. It also incorporates the Technical Corrigendum ISO 7783-1:1996/Cor.1:1998.

Introduction

ISO 7783 is one of a series of standards dealing with the sampling and testing of paints, varnishes and related products. It describes a method for determining the water-vapour transmission rate of self-supporting and non-self-supporting coatings.

The water-vapour transmission rate is not necessarily a linear function of film thickness, temperature or relative-humidity difference. A determination carried out under one set of conditions will not necessarily be comparable with one carried out under other conditions. Therefore, it is essential that the conditions of test are chosen to be as close as possible to the conditions of use.

Water-vapour transmission is of greatest interest under conditions of high humidity. For this reason, the wet-cup method has been adopted as the reference method. By agreement, other procedures and conditions, like the dry-cup method, may be used.

Paints and varnishes — Determination of water-vapour transmission properties — Cup method

1 Scope

This International Standard specifies a method for determining the water-vapour transmission properties of coatings of paints, varnishes and related products.

It supplements ISO 12572. As far as possible, the procedure, the definitions and the calculations have been taken over from ISO 12572. It is recommended that ISO 12572 be consulted, if necessary, to obtain a better understanding of the procedure specified in this International Standard.

Water-vapour transmission rates of more than 680 g/(m²·d) (i.e. water-vapour diffusion-equivalent air layer thicknesses, s_d , of less than 0,03 m) will not be accurately quantified by the test method described in this International Standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 3233, *Paints and varnishes — Determination of percentage volume of non-volatile matter by measuring the density of a dried coating*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

water-vapour transmission rate

V

mass of water vapour that is transmitted over a given period through a given surface area of a test piece under specified constant conditions of relative humidity at each face of the test piece

NOTE 1 It is measured in grams per square metre per day [g/(m²·d)].

NOTE 2 A water-vapour transmission rate measured at atmospheric pressure, p , can be converted to the equivalent value at standard atmospheric pressure, p_0 , by multiplying by p/p_0 . This allows a linear correlation with the water-vapour diffusion-equivalent air layer thickness (s_d) value (see 3.3) by the factor 20,4.

NOTE 3 The term “water-vapour transmission” is often incorrectly used for water-vapour transmission rate.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-