



NSAI
Standards

Irish Standard
I.S. EN ISO 4498:2010

Sintered metal materials, excluding hardmetals - Determination of apparent hardness and microhardness (ISO 4498:2010)

I.S. EN ISO 4498:2010

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

<i>This document replaces:</i> EN ISO 4498:2007	<i>This document is based on:</i> EN ISO 4498:2010 EN ISO 4498:2007	<i>Published:</i> 15 June, 2010 14 February, 2007
This document was published under the authority of the NSAI and comes into effect on: 22 June, 2010		ICS number: 77.160 77.040.10
<div> <div> NSAI 1 Swift Square, Northwood, Santry Dublin 9 </div> <div> T +353 1 807 3800 F +353 1 807 3838 E standards@nsai.ie W NSAI.ie </div> <div> Sales: T +353 1 857 6730 F +353 1 857 6729 W standards.ie </div> </div>		
Údarás um Chaighdeáin Náisiúnta na hÉireann		

English Version

**Sintered metal materials, excluding hardmetals - Determination
of apparent hardness and microhardness (ISO 4498:2010)**

Matériaux métalliques frittés, à l'exclusion des métaux-durs
- Détermination de la dureté apparente et de la microdureté
(ISO 4498:2010)

Sintermetalle, ausgenommen Hartmetalle - Bestimmung
der Sinterhärte und der Mikrohärte (ISO 4498:2010)

This European Standard was approved by CEN on 26 May 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
----------------------	----------

Foreword

This document (EN ISO 4498:2010) has been prepared by Technical Committee ISO/TC 119 "Powder metallurgy".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2010, and conflicting national standards shall be withdrawn at the latest by December 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4498:2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 4498:2010 has been approved by CEN as a EN ISO 4498:2010 without any modification.

This page is intentionally left BLANK.

I.S. EN ISO 4498:2010
**INTERNATIONAL
STANDARD**

**ISO
4498**

Second edition
2010-06-15

**Sintered metal materials, excluding
hardmetals — Determination of apparent
hardness and microhardness**

*Matériaux métalliques frittés, à l'exclusion des métaux-durs —
Détermination de la dureté apparente et de la microdureté*



Reference number
ISO 4498:2010(E)

© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	2
3 Apparatus	2
4 Sampling and preparation of test pieces	2
5 Test procedures.....	3
5.1 Procedure 1 — Determination of apparent hardness	3
5.2 Procedure 2 — Determination of microhardness	4
6 Expression of results	6
6.1 Apparent hardness	6
6.2 Microhardness	6
7 Repeatability and reproducibility.....	6
7.1 Vickers apparent hardness	6
7.2 Rockwell apparent hardness.....	6
7.3 Vickers microhardness	6
7.4 Precision statement	6
8 Test report.....	7
Annex A (normative) Test conditions and test loads as well as symbols and designations for microhardness values.....	8
Annex B (informative) Repeatability and reproducibility.....	10
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4498 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 3, *Sampling and testing methods for sintered metal materials (excluding hardmetals)*.

This second edition cancels and replaces the first edition (ISO 4498:2005), of which it constitutes a minor revision.

Introduction

Sintered metal materials generally have a porous structure. Therefore, they can be understood as composite metal/pore materials. That is why this International Standard describes two procedures to determine their hardness:

- Procedure 1 for the macrohardness (this is the apparent hardness);
- Procedure 2 for the microhardness (this is the hardness of the metallic phase only).

Tests in Procedure 1 determine Vickers, Brinell and/or Rockwell macrohardnesses; their acronyms are: HV, HBW and HR. These tests determine the apparent hardness (macrohardness) of the materials because indentations generally include both the solid phase and a number of pores. The usual test forces applied to an indenter are from 10 N to 2 000 N.

The apparent hardness value is often used as an expression of the mechanical strength of the material as a whole; it is usually lower than that of a solid material of the same composition and metallurgical condition. However, this does not imply that the functional characteristics (for example wear resistance) are necessarily inferior to those of an equivalent full-density material.

The apparent hardness is a macrostructural property. It characterizes the material taken as a whole.

Tests in Procedure 2 determine the Vickers and/or Knoop microhardnesses of the material; their acronyms are: HV_a and $HK_a^{1)}$. The usual test forces applied to an indenter are from 0,147 N to 1,960 N for Vickers, and 0,981 N for Knoop.

The microhardness is a microstructural property used to control chemical composition, heat treatment or surface treatment. For these purposes, it is necessary to ensure that hardness test indentations are small enough not to include any visible pores, but only the solid phase.

1) Where a is the test load, in kilograms.

Sintered metal materials, excluding hardmetals — Determination of apparent hardness and microhardness

1 Scope

1.1 This International Standard specifies methods of hardness testing of sintered metal materials, excluding hardmetals.

1.2 Procedure 1 determines the apparent hardness of the whole material.

Procedure 1

- applies to sintered metal materials which have either not been subjected to any heat treatment, or which have been heat treated in such a way that the hardness is essentially uniform to a depth of at least 5 mm below the surface,
- applies to the surfaces of sintered metal materials which have been treated in such a way that the hardness is not uniform in the section to a depth of 5 mm below the surface,
- therefore applies to materials in which the hardness is obtained essentially by surface enrichment by carbon, or by carbon and nitrogen (for example by carburizing, carbonitriding, nitrocarburizing or sulfidizing), and
- applies to materials which have been induction hardened.

1.3 Procedure 2 determines the microhardness of the metal phase.

Procedure 2

- applies to all types of sintered metal materials,
- is used, in particular, to determine the hardness profile of case-hardened or carbonitrided materials in accordance with the method described in ISO 4507, and
- also applies to any sintered metallic materials which have been subjected to surface treatments such as electrodeposited plating, chemical coating, chemical vapour deposition (CVD), physical vapour deposition (PVD), laser, ion bombardment, etc. To determine the microhardness of treated surfaces, Procedure 2 applies.

NOTE However, an international agreement has not yet been reached on a number of factors involved in microhardness testing. Nevertheless, the parameters defined in Procedure 2 are important enough to enable a considerable measure of standardization of extensively used practices.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-