

Irish Standard I.S. EN 61747-5-3:2010

Liquid crystal display devices -- Part 5-3: Environmental, endurance and mechanical test methods - Glass strength and reliability (IEC 61747-5 -3:2009 (MOD))

 $\ensuremath{\mathbb C}$ NSAI 2010 $\hfill No copying without NSAI permission except as permitted by copyright law.$

Incorporating amendments/corrigenda issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:	<i>This document is base</i> EN 61747-5-3:2010	ed on:	<i>Publish</i> 14 May	ned: 7, 2010
This document was published under the authority of the NSAI and comes into effect on: 14 June, 2010				ICS number: 31.120
NSAI T +353 1 807 3800 Sales: 1 Swift Square, F +353 1 807 3838 T +353 1 857 6730 Northwood, Santry E standards@nsai.ie F +353 1 857 6729 Dublin 9 W NSAI.ie W standards.ie				
Údarás um Chaighdeáin Náisiúnta na hÉireann				

EUROPEAN STANDARD

EN 61747-5-3

NORME EUROPÉENNE EUROPÄISCHE NORM

May 2010

ICS 31.120

English version

Liquid crystal display devices -Part 5-3: Environmental, endurance and mechanical test methods -Glass strength and reliability

(IEC 61747-5-3:2009, modified)

Dispositifs d'affichage à cristaux liquides -Part 5-3: Méthodes d'essais d'environnement, d'endurance et mécaniques -Résistance et fiabilité du verre (CEI 61747-5-3:2009, modifiée) Flüssigkristall-Anzeige-Bauelemente -Teil 5-3: Verfahren zur Messung von Glasfestigkeit und Zuverlässigkeit (IEC 61747-5-3:2009, modifiziert)

This European Standard was approved by CENELEC on 2010-05-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

© 2010 CENELEC - All rights of exploitation in any form and by any means reserved worldwide for CENELEC members.

EN 61747-5-3:2010

I.S. EN 61747-5-3:2010 - 2 -

Foreword

The text of the International Standard IEC 61747-5-3:2009, prepared by IEC TC 110, Flat panel display devices, together with the common modifications prepared by the CENELEC Reporting Secretariat 110 (NL), was submitted to the CENELEC formal vote and was approved by CENELEC as EN 61747-5-3 on 2010-05-01.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN and CENELEC shall not be held responsible for identifying any or all such patent rights.

The following dates were fixed:

_	latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement	(dop)	2011-05-01
_	latest date by which the national standards conflicting with the EN have to be withdrawn	(dow)	2013-05-01

Annex ZA has been added by CENELEC.

I.S. EN 61747-5-3:2010 - 3 -

EN 61747-5-3:2010

Endorsement notice

The text of the International Standard IEC 61747-5-3:2009 was approved by CENELEC as a European Standard with the following common modifications.

COMMON MODIFICATIONS

4 Abbreviated terms

Delete:

MCmirror constantMRmirror radiusSCSCstress corrosion susceptibility constant

8.2 Quasistatic biaxial strength (parent glass)

Replace the title by:

8.2 Quasistatic biaxial failure stress (parent glass)

8.3 Quasistatic edge strength (parent glass)

Replace the title by:

8.3 Quasistatic edge failure stress (parent glass)

Under equation 2, replace the following definition:

 $\sigma_{\rm e}$ is the edge failure stress.

9 Fatigue and reliability calculations

9.1 General

Replace Equation 3 by:

$$\int_{0}^{t_{F}} \sigma^{n}(t) dt \approx BS^{n-2}$$

Under Equation 3 replace the following definitions:

- $\sigma(t)$ is the applied stress over time,
- $t_{\rm F}$ is the time to failure,

9.2 Fatigue constant calculation

Replace the title by:

9.2 Dynamic fatigue calculation

9.3 Weibull parameter calculation from dynamic failure stress data

Replace the last sentence of the 1st paragraph by:

For each, the effective strength, $\mathsf{Seff}_{{\mbox{\tiny K}}}$ is calculated as

Under Equation 7 add the following definition:

Seff₀ is the Weibull scaling factor for Seff

EN 61747-5-3:2010

9.4 Fatigue constant calculation

Replace the title by:

9.4 Extrapolated static fatigue and Weibull distribution calculation

Replace Equation 8 by:

$$\ln(\text{Seff}) = \frac{n}{n-2}\ln(\sigma_a) + \frac{1}{n-2}\ln(t_F)$$

Replace Equation 9 by:

$$\ln(-\ln(1-F)) + m\ln(S_{\text{eff}_0}) = \frac{mn}{n-2}\ln(\sigma_a) + \frac{m}{n-2}\ln(t_F)$$

Annex A (informative) Worked test example

Replace the sentence under table A.1 by:

The failure stress value can also be estimated by measuring the mirror radius, R_m of the specimen's fracture surface, as shown in Figures A.2 and A.3, and using Equation (A.1).

Add the following note to Equation A.1:

 σ_f is the failure stress for a given sample.

I.S. EN 61747-5-3:2010 - 5 -

EN 61747-5-3:2010

Annex ZA

(normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

Publication	<u>Year</u>	Title	<u>EN/HD</u>	Year
IEC 61747-1	-	Liquid crystal and solid-state display devices - Part 1: Generic specification	EN 61747-1	-
IEC 61747-5	1998	Liquid crystal and solid-state display devices - Part 5: Environmental, endurance and mechanical test methods	EN 61747-5	1998

This is a free page sample. Access the full version online.

I.S. EN 61747-5-3:2010

This page is intentionally left BLANK.

61747-5-3 © IEC:2009

CONTENTS

- 2 -

FO	REWO	DRD	.3
INT	RODI	JCTION	.5
1	Scop	e	.6
2	Normative references		
3	Term	s and definitions	6
4	Abbre	eviated terms	7
5	Арра	ratus	.7
	5.1	General	7
	5.2	Method A: Quasistatic biaxial strength	.8
	5.3	Method B: Quasistatic edge strength (parent glass)	.8
	5.4	Method C: Quasistatic strength (module)	.9
	5.5	Method D: Fatigue constant	10
6	Test	sample	10
	6.1	General	10
	6.2	Parent glass	11
	6.3	Full size module	11
7	Proce	edure: Quasistatic loading	11
8	Stres	s calculations	11
	8.1	General	11
	8.2	Quasistatic biaxial strength (parent glass)	11
	8.3	Quasistatic edge strength (parent glass)	12
	8.4	Quasistatic failure load (LCD module)	12
9	Fatig	ue and reliability calculations	12
	9.1	General	12
	9.2	Fatigue constant calculation	13
	9.3	Weibull parameter calculation from dynamic failure stress data	13
	9.4	Fatigue constant calculation	13
10	Repo	rting requirements	14
Anr	Annex A (informative) Worked test example		
Bib	liogra	ohy	18

Figure 1 – Schematic of ROR test fixture for measuring biaxial strength of parent glass	8
Figure 2 – Vertical bend test fixture for measuring the edge strength of parent glass	9
Figure 3 – Schematic of strength measurement for full-size LCD module	10
Figure A.1 – Weibull plot of biaxial strength of abraded glass with different thicknesses	15
Figure A.2 – Fracture surface of parent glass with 0,089 mm mirror radius	16
Figure A.3 – Plot of calculated strength versus 1/square root of mirror radius	16
Figure A.4 – Weibull distribution of the strength of 17" module	17

Table A.1 – Example of strength data before and after abrasion	15
Table A.2 – Example of strength data for all modules and low strength modules	17

61747-5-3 © IEC:2009

- 3 -

INTERNATIONAL ELECTROTECHNICAL COMMISSION

LIQUID CRYSTAL DISPLAY DEVICES -

Part 5-3: Environmental, endurance and mechanical test methods – Glass strength and reliability

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committee; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61747-5-3 has been prepared by IEC technical committee 110: Flat panel display devices.

This International Standard replaces the IEC/PAS 61747-5-3, published in 2007.

There have been no significant revisions since the publication of the PAS version.

This part of IEC 61747 is a sectional specification for liquid crystal display cells. It is to be read in conjunction with the IEC 61747-1 to which it refers.

- 4 -

61747-5-3 © IEC:2009

The text of this standard is based on the following documents:

FDIS	Report on voting
110/169/FDIS	110/177/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

Future standards in this series will carry the new general title as cited above. Titles of existing standards in this series will be updated at the time of the next edition.

A list of all parts of the IEC 61747 series, under the general title *Liquid crystal display devices*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

61747-5-3 © IEC:2009

- 5 -

INTRODUCTION

IEC 61747-5-3 facilitates the characterization of mechanical strength properties of LCD modules and their component glass. Analysis and testing are performed on LCD Module component glass as well as finished LCD modules. Statistics of mechanical strength of the modules are determined allowing a prediction of module failure probability at a given stress level or for a given probability of failure, the maximum recommended safe loading stress for the module.

- 6 -

LIQUID CRYSTAL DISPLAY DEVICES –

Part 5-3: Environmental, endurance and mechanical test methods – Glass strength and reliability

1 Scope

This part of IEC 61747 applies to commercially available liquid crystal displays (LCDs). This standard applies to all LCD types, including transmissive, reflective or transflective liquid crystal display (LCD) modules using either segment, passive or active matrix and achromatic or colour type LCDs that are equipped with their own integrated source of illumination or without their own source of illumination.

The objective of this standard is to establish uniform requirements for accurate and reliable measurements of the following LCD parameters:

- a) quasistatic strength,
- b) quasistatic fatigue.

The methods described in this standard apply to all sizes, small and large, liquid crystal displays.

NOTE Methods for measuring the fatigue constant are described in this standard and are taken from the referenced literature, see [13]¹ to [20]. The primary results are formulae for estimated allowable stress for the specified lifetime or estimated failure rate for the specified stress level. As an example, limited data for strength and fatigue behaviour of LCD glass are included in an informative Annex A. Similarly, limited data for static strength of LCD modules are also included and compared with that of parent glass.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61747-1, Liquid crystal and solid-state display devices – Part 1: Generic specification

IEC 61747-5:1998, Liquid crystal and solid-state display devices – Part 5: Environmental, endurance and mechanical test methods

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

strength

stress at which a sample fails for a given loading condition

3.2

LCD surface strength

biaxial strength wherein surface flaws with different orientations are subjected to uniform tension during measurement

¹ Figures in square brackets refer to the bibliography.



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation