



NSAI
Standards

Irish Standard
I.S. EN ISO 1133-1:2011

Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 1: Standard method (ISO 1133-1:2011)

I.S. EN ISO 1133-1:2011

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:
EN ISO 1133:2005

<i>This document is based on:</i> EN ISO 1133-1:2011	<i>Published:</i> 20 December, 2011
---	--

This document was published under the authority of the NSAI and comes into effect on:
20 December, 2011

ICS number:
83.080.20

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

Plastics - Determination of the melt mass-flow rate (MFR) and
melt volume-flow rate (MVR) of thermoplastics - Part 1:
Standard method (ISO 1133-1:2011)

Plastiques - Détermination de l'indice de fluidité à chaud
des thermoplastiques, en masse (MFR) et en volume
(MVR) - Partie 1: Méthode normale (ISO 1133-1:2011)

Kunststoffe - Bestimmung der Schmelze-Massefließrate
(MFR) und der Schmelze-Volumenfließrate (MVR) von
Thermoplasten - Teil 1: Allgemeines Prüfverfahren (ISO
1133-1:2011)

This European Standard was approved by CEN on 30 November 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

Foreword

This document (EN ISO 1133-1:2011) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2012, and conflicting national standards shall be withdrawn at the latest by June 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1133:2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 1133-1:2011 has been approved by CEN as a EN ISO 1133-1:2011 without any modification.

This page is intentionally left BLANK.

I.S. EN ISO 1133-1:2011
**INTERNATIONAL
STANDARD**

**ISO
1133-1**

First edition
2011-12-01

**Plastics — Determination of the melt
mass-flow rate (MFR) and melt volume-
flow rate (MVR) of thermoplastics —**

**Part 1:
Standard method**

*Plastiques — Détermination de l'indice de fluidité à chaud des
thermoplastiques, en masse (MFR) et en volume (MVR) —*

Partie 1: Méthode normale



Reference number
ISO 1133-1:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	3
5.1 Extrusion plastometer	3
5.2 Accessory equipment	7
6 Test sample	8
6.1 Sample form	8
6.2 Conditioning	8
7 Temperature verification, cleaning and maintenance of the apparatus	9
7.1 Verification of the temperature control system	9
7.2 Cleaning the apparatus	10
7.3 Vertical alignment of the instrument	10
8 Procedure A: mass-measurement method	10
8.1 Selection of temperature and load	10
8.2 Cleaning	10
8.3 Selection of sample mass and charging the cylinder	10
8.4 Measurements	11
8.5 Expression of results	12
9 Procedure B: displacement-measurement method	13
9.1 Selection of temperature and load	13
9.2 Cleaning	13
9.3 Minimum piston displacement distance	13
9.4 Selection of sample mass and charging the cylinder	13
9.5 Measurements	13
9.6 Expression of results	14
10 Flow rate ratio	15
11 Precision	16
12 Test report	16
Annex A (normative) Test conditions for MFR and MVR determinations	18
Annex B (informative) Conditions specified in International Standards for the determination of the melt flow rate of thermoplastic materials	19
Annex C (informative) Device and procedure for preforming a compacted charge of material by compression	20
Annex D (informative) Precision data for polypropylene obtained from an intercomparison of MFR and MVR testing	23
Bibliography	24

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1133-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This first edition of ISO 1133-1 cancels and replaces ISO 1133:2005. It also incorporates the Technical Corrigendum, ISO 1133:2005/Cor.1:2006.

In this part of ISO 1133, changes have been made to accommodate ISO 1133-2. In addition: Clause 3 includes further definitions relevant to both parts of ISO 1133; 5.1.3 specifies the lower edge of the piston head; 5.1.4 updates temperature tolerances; 5.2.1.7 on a preforming device has been added; 5.2.2.2 includes revised cut-off timing accuracy; 8.3 provides cut-off time intervals that are consistent with other specifications in this part of ISO 1133; 8.5.3 and 9.6.3 have been included on expression of half die results; 9.3 provides minimum piston displacements that are consistent with other specifications in this part of ISO 1133; Annex B has been simplified to avoid inconsistencies between this and the materials specification standards; Annex C, has been added for the preparation of charges of material that is particularly suited to testing flake or other large aspect ratio particles; Annex D has been added to provide precision data from an intercomparison on a high MVR/MFR material.

This part of ISO 1133 applies to melt flow rate testing broadly equivalent to that of ISO 1133:2005. ISO 1133-2 applies to the testing of polymers that are rheologically sensitive to the time-temperature history to which they are subjected during melt flow rate testing.

ISO 1133 consists of the following parts, under the general title *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics*:

- *Part 1: Standard method*
- *Part 2: Method for materials sensitive to time-temperature history and/or moisture*

Introduction

For stable materials that are not rheologically sensitive to the time-temperature history experienced during melt flow rate testing, this part of ISO 1133 is recommended.

For materials whose rheological behaviour is sensitive to the test's time-temperature history, e.g. materials which degrade during the test, ISO 1133-2 is recommended.

NOTE At the time of publication, there is no evidence to suggest that the use of ISO 1133-2 for stable materials results in better precision in comparison with the use of this part of ISO 1133.

Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics —

Part 1: Standard method

WARNING — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This part of ISO 1133 specifies two procedures for the determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastic materials under specified conditions of temperature and load. Procedure A is a mass-measurement method. Procedure B is a displacement-measurement method. Normally, the test conditions for measurement of melt flow rate are specified in the material standard with a reference to this part of ISO 1133. The test conditions normally used for thermoplastics are listed in Annex A.

The MVR is particularly useful when comparing materials of different filler content and when comparing filled with unfilled thermoplastics. The MFR can be determined from MVR measurements, or vice versa, provided the melt density at the test temperature is known.

This part of ISO 1133 is also possibly applicable to thermoplastics for which the rheological behaviour is affected during the measurement by phenomena such as hydrolysis (chain scission), condensation and cross-linking, but only if the effect is limited in extent and only if the repeatability and reproducibility are within an acceptable range. For materials which show significantly affected rheological behaviour during testing, this part of ISO 1133 is not appropriate. In such cases, ISO 1133-2 applies.

NOTE The rates of shear in these methods are much smaller than those used under normal conditions of processing, and therefore it is possible that data obtained by these methods for various thermoplastics will not always correlate with their behaviour during processing. Both methods are used primarily in quality control.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture*

ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-