



NSAI
Standards

Irish Standard
I.S. EN 10245-4:2011

Steel wire and wire products - Organic coatings on steel wire - Part 4: Polyester coated wire

I.S. EN 10245-4:2011

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:
EN 10245-4:2003

This document is based on:
EN 10245-4:2011

Published:
7 November, 2011

This document was published
under the authority of the NSAI
and comes into effect on:
7 November, 2011

ICS number:

25.220.60

77.140.65

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

**Steel wire and wire products - Organic coatings on steel wire -
Part 4: Polyester coated wire**

Fils et produits tréfilés en acier - Revêtements organiques
sur fils d'acier - Partie 4: Fils à revêtement de polyester

Stahldraht und Drahterzeugnisse - Organische
Beschichtungen auf Stahldraht - Teil 4: Polyester
beschichteter Draht

This European Standard was approved by CEN on 17 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Foreword.....	3
Introduction	4
1 Scope	4
2 Normative references	5
3 Terms and definitions	6
4 Methods of application of polyester coatings	6
5 Requirements and testing methods for polyester coating material.....	6
5.1 General.....	6
5.2 Composition and method of application	6
5.3 Consistency.....	6
5.4 Density	7
5.5 Hardness.....	7
5.6 Tensile strength	7
5.7 Elongation	7
6 Requirements and test methods for polyester coating on wire and wire products	7
6.1 General.....	7
6.2 Appearance	7
6.3 Colour	8
6.4 Gloss	8
6.5 Thickness	8
6.6 Elongation	8
6.7 Concentricity	8
6.8 Adherence	8
7 Performance requirements and tests for the polyester coating on the finished wire and wire products	9
7.1 General.....	9
7.2 Colour stability (accelerated weathering)	9
7.3 Kesternich test.....	9
7.4 Boiling water test.....	10
8 Retests	10
9 Inspection and quality assurance	10
Bibliography	11

Foreword

This document (EN 10245-4:2011) has been prepared by Technical Committee ECISS/TC 106 “Wire rod and wires”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2012, and conflicting national standards shall be withdrawn at the latest by April 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10245-4:2003.

This standard is made up of the following parts:

- *Part 1: General Rules;*
- *Part 2: PVC finished wire;*
- *Part 3: PE coated wire;*
- *Part 4: Polyester coated wire;*
- *Part 5: Polyamide coated wire.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This European Standard for organic coatings for steel wire covers the requirements of a general nature and applies also to coatings for which no specific requirements have been established in the subsequent parts of this standard.

The subsequent parts of this standard deal more specifically with clearly defined coatings or groups of coatings. These coatings may have their own particular methods of application and their individual requirements which are specified in these parts of this standard, in other standards or in manufacturers data sheets.

Because the standard specifies requirements and tests not only for the coating but also for the coating material, it has proved not practical to put all the requirements in one clause and all the tests in another one. Following structure has been chosen in order to limit complexity and to facilitate the use.

In writing this series of standards consideration has been given to the nomenclature and transformation of organic coating materials as applied to steel wire products. These organic coating materials may, on application to wire and by their integration into the finished wire product, change their characteristics and properties.

This standard specifies characteristics and tests not only for the organic coating but also for the coating materials both before and after their application to steel wire and wire products. In addition it specifies the requirements for performance levels and testing methods on organic coating material which have become an integral and permanent part of the finished wire product. Therefore it has proven not to be practical to put all requirements in one clause and all the tests in another one.

To aid continuity and in order to limit complexity, the following structure has been chosen for this standard:

- **Clause 5** deals with the characteristics and testing methods of organic coating material as supplied by the manufacturer for the purposes of its application to the wire product.

Tests described in this section are intended to be carried out by the organic coating material manufacturer or the applicator **before** the coating operation.

- **Clause 6** relates to the characteristics and testing methods for the "organic coating" when the organic coating material has been applied to and has become an integral part of the finished wire. Consequently tests are intended to be in the main carried out by the coating "applicators".
- **Clause 7** defines the performance requirements and testing methods on the "organic coating" of the finished wire product, and where this is not possible, tests will be carried out on "coated" panels Scope

1 Scope

Complementary to EN 10245-1, this European Standard specifies the characteristics and requirements for steel wire and wire products coated with polyester.

It covers both thermoplastic and thermosetting polyester.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10021, *General technical delivery conditions for steel products*

EN 10245-1:2001, *Steel wire and wire products — Organic coatings on steel wire — Part 1: General rules*

EN ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets (ISO 527-3:1995)*

EN ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868:2003)*

EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1:2004)*

EN ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2:2004)*

EN ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method (ISO 1183-3:1999)*

EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85° (ISO 2813:1994, including Technical Corrigendum 1:1997)*

EN ISO 2815, *Paints and varnishes — Buchholz indentation test (ISO 2815:2003)*

EN ISO 3231, *Paints and varnishes — Determination of resistance to humid atmospheres containing sulfur dioxide (ISO 3231:1993)*

EN ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints (ISO 3668:1998)*

EN ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance (ISO 4892-1:1999)*

EN ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps (ISO 4892-2:2006)*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 7724-1, *Paints and varnishes — Colorimetry — Part 1: Principles*

ISO 7724-2, *Paints and varnishes — Colorimetry — Part 2: Colour measurement*

ISO 7724-3, *Paints and varnishes — Colorimetry — Part 3: Calculation of colour differences*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10245-1:2001 and the following apply.

3.1

polyester

organic material which is the result of a polycondensation reaction of a polyhydroxy compound with di- or polycarbon acids

NOTE There are two main classes of polyester: the linear polyesters and the crosslinked polyesters. Linear polyesters generally are thermoplastic, whereas crosslinked polyester is thermosetting and is hard.

3.2

polyethyleneglycoltereftalate (PET)

one of the most commonly used linear polyesters

NOTE PET is only the abbreviation of polyethyleneglycoltereftalate. The designation of other types of polyester by PET is not correct and is to be avoided.

4 Methods of application of polyester coatings

The most commonly used method for polyester coating on wire is by extrusion and for coating of wire products is by powder coating. The coating may be applied directly on the surface of the wire or wire product or after applying a primer. Where appropriate other methods may be used.

5 Requirements and testing methods for polyester coating material

5.1 General

Unless otherwise specified the test methods for polyester coating material shall be in accordance with EN 10245-1.

5.2 Composition and method of application

The coating material shall be free of lead (Pb), cadmium (Cd) and benzoin. Other requirements for the composition shall be agreed between manufacturer and applicator and shall take account of this method of application. However, the polyester coating material shall fulfil the requirements of this standard. The processing of the polyester coating material shall be at the manufacturer's discretion.

The requirements for the polyester intended for extrusion are those for PET. For other coating material other requirements may be agreed between the parties.

5.3 Consistency

The manufacturer shall ensure that the organic coating material composition and its characteristics shall remain constant from batch to batch and unchanged from that as agreed at the time of inquiry and ordering.

The manufacturer shall immediately notify the applicator of any subsequent change in the type and quantity of the constituent parts of the composition once this has been agreed between the two parties.

At the request of the supplier or purchaser the presence of certain elements may be limited. In any case, the compound composition shall be cadmium-free.

5.4 Density

Unless otherwise agreed between the applicator and the coating material supplier the density of the coating material, when tested in accordance with EN ISO 1183- 1 to -3, shall be in accordance with Table 1.

Where the apparent density of the supplied powder is specified, requirements and test methods shall be agreed between the parties.

5.5 Hardness

When measured in accordance with EN ISO 868 the Shore hardness D shall be in accordance with Table 1. If so agreed between the parties the Bucholtz hardness, when measured in accordance with EN ISO 2815, shall be in accordance with Table 1.

5.6 Tensile strength

When tested in accordance with EN ISO 527-3 the minimum tensile strength shall be in accordance with Table 1.

5.7 Elongation

When tested in accordance with EN ISO 527-3 the elongation shall be in accordance with Table 1.

Table 1 — Requirements and tests for the coating material

Characteristics	Requirements for		Test method
	Thermoplastics materials	Thermosetting materials	
Density (kg/dm ³)	Neutral, uncoloured: 1,30 – 1,40 ^a	White: 1,50 – 1,70 ± 0,05 ^a Green: 1,45 – 1,65 ± 0,05	EN ISO 1183-1 to -3
Shore hardness D	Min. 76	not applicable	EN ISO 868
Bucholtz hardness	Not applicable	Min. 90	EN ISO 2815
Tensile strength MPa	Min. 55	not applicable	EN ISO 527-3
Elongation %	Min. 300	> 50	EN ISO 527-3
^a For other colours the density shall be by agreement.			

6 Requirements and test methods for polyester coating on wire and wire products

6.1 General

In addition to the general requirements of EN 10245-1, polyester coatings shall satisfy following requirements. The coating requirements are summarized in Table 2.

6.2 Appearance

Following examination by visual inspection with the naked eye, the surface of the polyester coating shall be smooth, shiny, free from irregularities and uniform in colour.

Small dents, not affecting subsequent use and resulting from contact with adjacent turns, shall not constitute a cause for rejection.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-