



**NSAI**  
Standards

Irish Standard  
I.S. EN 14272:2011

# Plywood - Calculation method for some mechanical properties

## I.S. EN 14272:2011

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

*This document replaces:*  
ENV 14272:2002

*This document is based on:* EN 14272:2011  
*Published:* 3 January, 2012

This document was published under the authority of the NSAI and comes into effect on:  
3 January, 2012

**ICS number:**  
79.060.10

**NSAI**  
1 Swift Square,  
Northwood, Santry  
Dublin 9

T +353 1 807 3800  
F +353 1 807 3838  
E standards@nsai.ie  
W NSAI.ie

**Sales:**  
T +353 1 857 6730  
F +353 1 857 6729  
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

## Plywood - Calculation method for some mechanical properties

Contreplaqué - Méthode de calcul pour certaines caractéristiques mécaniques

Sperrholz - Rechenverfahren für einige mechanische Eigenschaften

This European Standard was approved by CEN on 1 October 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

Foreword.....	4
1 Scope .....	5
2 Normative references .....	5
3 Principle .....	5
4 Terms and definitions .....	6
5 Symbols .....	6
5.1 Main symbols .....	6
5.2 Subscripts .....	7
6 Calculation method.....	8
6.1 General.....	8
6.2 Properties relevant to the calculation methods .....	8
6.3 Wood species.....	8
6.4 Factors for plywood composition .....	8
7 Characteristic values for strength and stiffness in bending, tension and compression.....	11
7.1 General.....	11
7.2 Bending.....	11
7.2.1 General.....	11
7.2.2 Modulus of elasticity .....	11
7.2.3 Strength .....	11
7.3 Tension and compression .....	12
7.3.1 Stiffness and capacity of the layers in the cross section .....	12
7.3.2 Stiffness and capacity of the panel.....	13
7.3.3 Property of the panel (as if homogenized).....	13
7.4 Property values for layers.....	13
7.4.1 General.....	13
7.4.2 Modulus of elasticity ( $E_m$ , $E_t$ , $E_c$ ).....	14
7.4.3 Resistance .....	14
8 Shear properties .....	15
8.1 Panel shear .....	15
8.1.1 Panel shear rigidity ( $G_v$ ) .....	15
8.1.2 Panel shear strength ( $f_v$ ) .....	16
8.2 Planar shear .....	16
8.2.1 General.....	16
8.2.2 Planar shear rigidity ( $G_r$ ) .....	16
8.2.3 Planar shear strength ( $f_r$ ) .....	17
9 Ratio of strength upon modulus .....	17
10 Density .....	17
11 Conversion from strength and modulus of elasticity to capacity and stiffness.....	18
Annex A (normative) Derivation for the veneer values (or basic values) .....	19
A.1 Scope .....	19
A.2 Principle .....	19
A.2.1 Option 1: Using plywood test results .....	19
A.2.2 Option 2: Using solid timber properties .....	19
A.3 Procedure for derivation of properties from testing plywood .....	19
A.3.1 General.....	19
A.3.2 Sampling.....	20

<b>A.3.3</b>	<b>Test pieces .....</b>	<b>20</b>
<b>A.3.4</b>	<b>Testing .....</b>	<b>20</b>
<b>A.3.5</b>	<b>Exploitation of the results .....</b>	<b>21</b>
<b>A.4</b>	<b>Derivation of estimated values for veneers .....</b>	<b>25</b>
<b>A.4.1</b>	<b>General .....</b>	<b>25</b>
<b>A.4.2</b>	<b>Values obtained by testing .....</b>	<b>25</b>
<b>A.4.3</b>	<b>Imposed values.....</b>	<b>25</b>
<b>A.5</b>	<b>Report .....</b>	<b>25</b>
<b>Annex B</b>	<b>(normative) Practical spreadsheets to derive the properties.....</b>	<b>27</b>
<b>B.1</b>	<b>General .....</b>	<b>27</b>
<b>B.2</b>	<b>Bending .....</b>	<b>28</b>
<b>B.2.1</b>	<b>General .....</b>	<b>28</b>
<b>B.2.2</b>	<b>Main tables .....</b>	<b>28</b>
<b>B.2.3</b>	<b>Tables for strength values.....</b>	<b>31</b>
<b>B.3</b>	<b>Tension and compression .....</b>	<b>33</b>
<b>B.4</b>	<b>Panel shear .....</b>	<b>39</b>
<b>B.5</b>	<b>Planar shear .....</b>	<b>40</b>
<b>B.5.1</b>	<b>General .....</b>	<b>40</b>
<b>B.5.2</b>	<b>Available veneer values .....</b>	<b>40</b>
<b>B.5.3</b>	<b>Veneer values not available .....</b>	<b>42</b>
<b>Annex C</b>	<b>(informative) Example of bending strength .....</b>	<b>43</b>
<b>C.1</b>	<b>Determination of the stress in the layers.....</b>	<b>43</b>
<b>C.2</b>	<b>Determination of the panel strength.....</b>	<b>45</b>
<b>Bibliography</b>	<b>.....</b>	<b>47</b>

## Foreword

This document (EN 14272:2011) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2012, and conflicting national standards shall be withdrawn at the latest by June 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes ENV 14272:2002.

Annex A and Annex B are normative.

Compared to ENV 14272:2002, the following modifications have been made:

- a) calculation applies to panels of any composition, symmetrical or not;
- b) values resulting for the panels can be used for calculation as characteristics values as required by EN 1995-1-1;
- c) new Annex A (normative) provides the derivation for the veneer values (basic values);
- d) new Annex B (normative) provides practical spreadsheets to derive the properties;
- e) new Annex C (informative) gives an example of bending strength.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This European Standard specifies, for plywood panels of any composition, symmetrical or not, a calculation method to derive some mechanical properties (strength and stiffness in bending, tension, compression, panel and planar shear) as well as density from the wood compounding the layers.

**NOTE** Usually, the lay-up of the panels is symmetrical but, very often, the surface appearance of the face and the surface appearance of the back face differ, hence a difference between the mechanical properties of the respective veneers. Therefore, in this case, the composition is not mechanically symmetrical and a symmetry independent calculation method is needed.

Provided that structural characteristic values are taken for the layers, the resulting values for the panels can be used as characteristic values as required by EN 1995-1-1.

Conversely, Annex A defines the procedures to derive the veneer properties, in bending, tension and compression, either from testing panels according to EN 789 and EN 1058 or from timber testing according to EN 408 or from imposed values defined in EN 338.

Annex B provides practical spreadsheets, which are applications of the equations in the main part of this standard.

Annex C provide an example for the calculation of bending strength, in accordance with Annex B.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 325, *Wood-based panels — Determination of dimensions of test pieces*

EN 338:2009, *Structural timber — Strength classes*

EN 384, *Structural timber — Determination of characteristic values of mechanical properties and density*

EN 408, *Timber structures — Structural timber and glued laminated timber — Determination of some physical and mechanical properties*

EN 789, *Timber structures — Test methods — Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels — Determination of characteristic 5-percentile values and characteristic mean values*

EN 12369-2, *Wood-based panels — Characteristic values for structural design — Part 2 Plywood*

EN 14358, *Timber structures — Calculation of characteristic 5-percentile values and acceptance criteria for a sample*

## 3 Principle

Using the mechanical properties of the wood species, which compound the layers (in this standard referred to as veneer or basic values), it consists in deriving, by calculation, the mechanical properties of a panel.

For bending, tension and compression, each layer property value, along and across the length of the panel, is weighted by a geometrical factor related to its weight in the panel cross section.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-