



NSAI
Standards

Irish Standard
I.S. EN ISO 9455-16:2013

Soft soldering fluxes - Test methods - Part 16: Flux efficacy test, wetting balance method (ISO 9455-16:2013)

I.S. EN ISO 9455-16:2013

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:
EN ISO 9455-16:2001

This document is based on:
EN ISO 9455-16:2013

Published:
26 April, 2013

This document was published under the authority of the NSAI and comes into effect on:
26 April, 2013

ICS number:
25.160.50

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

Soft soldering fluxes - Test methods - Part 16: Flux efficacy test,
wetting balance method (ISO 9455-16:2013)

Flux de brasage tendre - Méthodes d'essai - Partie 16:
Essai d'efficacité du flux, méthode à la balance de
mouillage (ISO 9455-16:2013)

Flussmittel zum Weichlöten - Prüfverfahren - Teil 16:
Bestimmung der Wirksamkeit des Flussmittels, Verfahren
zur Messung der Benetzungskraft (ISO 9455-16:2013)

This European Standard was approved by CEN on 2 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

Foreword

This document (EN ISO 9455-16:2013) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9455-16:2001.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 9455-16:2013 has been approved by CEN as EN ISO 9455-16:2013 without any modification.

This page is intentionally left BLANK.

I.S. EN ISO 9455-16:2013
INTERNATIONAL
STANDARD

ISO
9455-16

Second edition
2013-04-15

Soft soldering fluxes — Test methods —
Part 16:
Flux efficacy test, wetting balance
method

Flux de brasage tendre — Méthodes d'essai —

Partie 16: Essai d'efficacité du flux, méthode à la balance de mouillage



Reference number
ISO 9455-16:2013(E)

© ISO 2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Symbols	1
4 Principle	2
5 Reagents	2
6 Apparatus	2
7 Test pieces	3
8 Procedure	3
8.1 Preparation of the test pieces	3
8.2 Test method	3
9 Reference value using standard flux	4
10 Presentation of results	4
11 Calculation and expression of results	6
12 Test report	7
Annex A (normative) Method for the preparation of standard rosin (colophony) based liquid fluxes having 25 % (by mass) non-volatile content	8
Annex B (normative) Method for the production of test pieces with a controlled-contaminated surface for the wetting balance test (artificial sulfidation method)	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9455-16 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 12, *Soldering materials*.

This second edition cancels and replaces the first edition (ISO 9455-16:1998), which has been technically revised.

ISO 9455 consists of the following parts, under the general title *Soft soldering fluxes — Test methods*:

- *Part 1: Determination of non-volatile matter, gravimetric method*
- *Part 2: Determination of non-volatile matter, ebulliometric method*
- *Part 3: Determination of acid value, potentiometric and visual titration methods*
- *Part 5: Copper mirror test*
- *Part 6: Determination and detection of halide (excluding fluoride) content*
- *Part 8: Determination of zinc content*
- *Part 9: Determination of ammonia content*
- *Part 10: Flux efficacy test, solder spread method*
- *Part 11: Solubility of flux residues*
- *Part 13: Determination of flux spattering*
- *Part 14: Assessment of tackiness of flux residues*
- *Part 15: Copper corrosion test*
- *Part 16: Flux efficacy test, wetting balance method*
- *Part 17: Surface insulation resistance comb test and electrochemical migration test of flux residues*

Requests for official interpretations of any aspect of this part of ISO 9455 should be directed to the Secretariat of ISO/TC 44/SC 12 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Soft soldering fluxes — Test methods —

Part 16:

Flux efficacy test, wetting balance method

1 Scope

This part of ISO 9455 specifies a method for the assessment of the efficacy of a soft soldering flux, known as the wetting balance method. It gives a qualitative assessment of the comparative efficacy of two fluxes (for example, a standard and a test flux), based on their capacity to promote wetting of a metal surface by liquid solder. The method is applicable to all flux types in liquid form classified in ISO 9454-1.

NOTE It is hoped that future developments using improved techniques for obtaining a reproducible range of test surfaces will enable this method for assessing flux efficacy to be quantitative. For this reason, several alternative procedures for preparing the surface of the test piece are included in the present method.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9453, *Soft solder alloys — Chemical compositions and forms*

ISO 9454-1, *Soft soldering fluxes — Classification and requirements — Part 1: Classification, labelling and packaging*

IEC 60068-2-20:2008, *Environmental testing — Part 2-20: Tests — Test T: Test methods for solderability and resistance to soldering heat of devices with leads*

IEC 60068-2-54, *Environmental testing — Part 2-54: Tests — Test Ta: Solderability testing of electronic components by the wetting balance method*

IEC 60068-2-78:2001, *Environmental testing — Part 2-78: Tests; Test Cab: Damp heat, steady state*

3 Symbols

- d depth of immersion, in millimetres, of the test piece below the undisturbed solder level
- A cross sectional area, in square millimetres, of the test piece at the solder line
- ρ density, in grams per millilitre, of the solder under test at the test temperature
- F wetting force, in millinewtons
- t_0 time at which the test piece first makes contact with the surface of the liquid solder in the bath
- t_1 time at which the solder starts to wet the test piece (point A, see [Figure 1](#)), at which point the trace begins to fall
- t_2 time at which the recorded force is equal to the upward force due to buoyancy
- t_3 time at which the trace crosses the reference line

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-