

Irish Standard I.S. EN 61951-2:2011

Secondary cells and batteries containing alkaline or other non-acid electrolytes - Portable sealed rechargeable single cells -- Part 2: Nickel-metal hydride (IEC 61951-2:2011 (EQV))

© NSAI 2011

No copying without NSAI permission except as permitted by copyright law.

| Incorporating amendments/corrigenda issued since publication: |   |  |  |
|---|---|--|--|
|   | Incorporating amendments/corrigenda issued since publication: |  |  |
|   |   |  |  |
|   |   |  |  |
|   |   |  |  |
|   |   |  |  |
|   |   |  |  |
|   |   |  |  |
|   |   |  |  |

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces: EN 61951-2:2003 This document is based on: EN 61951-2:2011

EN 61951-2:2003

Published: 15 July, 2011 9 July, 2003

This document was published

under the authority of the NSAI and comes into effect on:

ICS number: 29.220.30

19 July, 2011

NSAI

T +353 1 807 3800

Sales:

1 Swift Square, Northwood, Santry Dublin 9 F +353 1 807 3838 E standards@nsai.ie T +353 1 857 6730 F +353 1 857 6729

W standards.ie

W/ NSA

W NSAl.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

**EUROPEAN STANDARD** 

EN 61951-2

NORME EUROPÉENNE EUROPÄISCHE NORM

July 2011

ICS 29.220.30

Supersedes EN 61951-2:2003

English version

# Secondary cells and batteries containing alkaline or other non-acid electrolytes -

Portable sealed rechargeable single cells - Part 2: Nickel-metal hydride

(IEC 61951-2:2011)

Accumulateurs alcalins et autres accumulateurs à électrolyte non acide -Accumulateurs individuels portables étanches -Partie 2: Nickel-métal hydrure (CEI 61951-2:2011) Akkumulatoren und Batterien mit alkalischem oder anderen nichtsäurehaltigen Elektrolyten -Tragbare wiederaufladbare gasdichte Einzelzellen -Teil 2: Nickel-Metallhydrid (IEC 61951-2:2011)

This European Standard was approved by CENELEC on 2011-06-29. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

# **CENELEC**

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

EN 61951-2:2011

- 2 -

#### **Foreword**

The text of document 21A/484/FDIS, future edition 3 of IEC 61951-2, prepared by SC 21A, Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC TC 21, Secondary cells and batteries, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 61951-2 on 2011-06-29.

This European Standard supersedes EN 61951-2:2003.

EN 61951-2:2011 includes the following significant technical changes with respect to EN 61951-2:2003:

- Clause 4: addition of 2 parameters;
- Clause 5: addition of cells type "S" and cells type "T";
- Subclause 6.1.2: addition of new cylindrical cells;
- Subclause 7.8: addition of a specific test for "S" cells.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN and CENELEC shall not be held responsible for identifying any or all such patent rights.

The following dates were fixed:

 latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement

(dop) 2012-03-29

 latest date by which the national standards conflicting with the EN have to be withdrawn

(dow) 2014-06-29

Annex ZA has been added by CENELEC.

## **Endorsement notice**

The text of the International Standard IEC 61951-2:2011 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60051 series NOTE Harmonized in EN 60051 series.

IEC 61434 NOTE Harmonized as EN 61434.

EN 61951-2:2011

# Annex ZA (normative)

- 3 -

# Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

| <u>Publication</u> | <u>Year</u> | <u>Title</u>   | EN/HD                    | <u>Year</u> |
|--------------------|-------------|--|--------------------------|-------------|
| IEC 60050-482      | -           | International Electrotechnical Vocabulary -<br>Part 482: Primary and secondary cells and<br>batteries  | -                        | -           |
| IEC 60086          | Series      | Primary batteries  | EN 60086                 | Series      |
| IEC 60086-1        | 2006        | Primary batteries -<br>Part 1: General   | EN 60086-1 <sup>1)</sup> | 2007        |
| IEC 60086-2        | 2006        | Primary batteries -<br>Part 2: Physical and electrical specifications  | EN 60086-2 <sup>2)</sup> | 2007        |
| IEC 60410          | -           | Sampling plans and procedures for inspection by attributes   | -                        | -           |
| IEC 61959          | -           | Secondary cells and batteries containing alkaline or other non-acid electrolytes - Mechanical tests for sealed portable secondary cells and batteries  | EN 61959                 | -           |
| IEC 62133          | -           | Secondary cells and batteries containing alkaline or other non-acid electrolytes - Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications | EN 62133                 | -           |

\_

<sup>&</sup>lt;sup>1)</sup> EN 60086-1 is superseded by EN 60086-1:2011, which is based on IEC 60086-1:2011.

 $<sup>^{2)}</sup>$  EN 60086-2 is superseded by EN 60086-2:2011, which is based on IEC 60086-2:2011.

This is a free page sample. Access the full version online.

I.S. EN 61951-2:2011

This page is intentionally left BLANK.

- 2 -

# 61951-2 © IEC:2011

# **CONTENTS**

| FOI | REWC  | )RD                         |   | 4  |  |
|-----|-------|-----------------------------|---|----|--|
| 1   | Scope |                             |   |    |  |
| 2   | Norm  | rmative references          |   |    |  |
| 3   | Term  | s and d                     | efinitions  | 6  |  |
| 4   | Parar | meter m                     | easurement tolerances   | 7  |  |
| 5   | Cell  | designat                    | ion and marking   | 8  |  |
|     | 5.1   | _                           | signation   |    |  |
|     |       | 5.1.1                       | Small prismatic cells and cylindrical cells                         |    |  |
|     |       | 5.1.2                       | Button cells  |    |  |
|     | 5.2   | 5.2 Cell termination        |   |    |  |
|     | 5.3   | Marking                     |   |    |  |
|     |       | 5.3.1                       | Small prismatic cells and cylindrical cells                         | 9  |  |
|     |       | 5.3.2                       | Button cells  |    |  |
| 6   | Dime  | nsions .                    |   | 10 |  |
|     | 6.1   | Small p                     | orismatic cells and cylindrical cells                               | 10 |  |
|     |       | 6.1.1                       | General   |    |  |
|     |       | 6.1.2                       | Small prismatic cells   |    |  |
|     |       | 6.1.3                       | Cylindrical cells   |    |  |
|     | 6.2   |                             | cells   |    |  |
| 7   | Elect |                             | ts  |    |  |
|     | 7.1   |                             | ıl  |    |  |
|     | 7.2   | _                           | ng procedure for test purposes                                      |    |  |
|     | 7.3   |                             | rge performance   |    |  |
|     |       | 7.3.1                       | General   |    |  |
|     |       | 7.3.2                       | Discharge performance at 20 °C                                      |    |  |
|     |       | 7.3.3                       | Discharge performance at 0 °C                                       |    |  |
|     | 7.4   | 7.3.4                       | Discharge performance for rapid charge cells (R cells)              |    |  |
|     | 7.4   | Charge (capacity) retention |   |    |  |
|     | 7.5   |                             | Endurance in evelop   |    |  |
|     |       | 7.5.1<br>7.5.2              | Permanent charge endurance  |    |  |
|     | 7.6   |                             | e acceptance at constant voltage                                    |    |  |
|     | 7.7   | •                           | rarge   |    |  |
|     | 1.1   | 7.7.1                       | Small prismatic, L, M, H, X, LS or MS cylindrical, and button cells |    |  |
|     |       | 7.7.2                       | LT/LU, MT/MU or HT/HU cylindrical cells                             |    |  |
|     |       | 7.7.3                       | R cylindrical cells   |    |  |
|     | 7.8   | Safety                      | device operation  |    |  |
|     | 7.9   | ·                           |   |    |  |
|     | 7.10  |                             | e   |    |  |
|     | 7.11  | Charge                      | acceptance at +55 °C for LT, MT or HT cylindrical cells             | 25 |  |
|     | 7.12  | Interna                     | I resistance  | 26 |  |
|     |       | 7.12.1                      | General   | 26 |  |
|     |       | 7.12.2                      | Measurement of the internal a.c. resistance                         | 26 |  |
|     |       | 7.12.3                      | Measurement of the internal d.c. resistance                         | 27 |  |
| 8   | Mech  | anical t                    | ests  | 27 |  |

61951-2 © IEC:2011

- 3 -

| 9        | Safet   | ty requirements  | 27 |
|----------|---------|--|----|
| 10       | Туре    | approval and batch acceptance  | 27 |
|          | 10.1    | Type approval  | 27 |
|          |         | 10.1.1 Type approval for small prismatic cells and button cells  | 27 |
|          |         | 10.1.2 Type approval for cylindrical cells   |    |
| <b>-</b> |         | Batch acceptance   |    |
| Bib      | liogra  | phy  | 31 |
| Fig      | ure 1   | – Jacketed cylindrical cells   | 11 |
| Fig      | ure 2   | Jacketed small prismatic cells   | 11 |
| Fig      | ure 3   | Jacketed cells dimensionally interchangeable with primary cells  | 12 |
| Fig      | ure 4   | – Button cells   | 14 |
| Tab      | ole 1 – | - Dimensions of jacketed small prismatic cells   | 11 |
|          |         | - Jacketed cylindrical cells dimensionally interchangeable with primary cells  |    |
|          |         | - Jacketed cylindrical cells not dimensionally interchangeable with primary  |    |
|          |         |  | 13 |
| Tab      | le 4 -  | - Dimensions of button cells   | 14 |
| Tab      | le 5 -  | - Discharge performance at 20 °C for small prismatic cells and cylindrical cells                                     | 15 |
| Tab      | le 6 -  | - Discharge performance at 20 °C for button cells  | 15 |
|          |         | - Discharge performance at 0 °C for small prismatic cells and cylindrical cells                                      |    |
| Tab      | le 8 -  | - Discharge performance at 0 °C for button cells   | 16 |
|          |         | - Endurance in cycles for small prismatic, button and cylindrical cells not nally interchangeable with primary cells | 17 |
| Tab      | le 10   | - Endurance in cycles for H or X cells   | 18 |
| Tab      | le 11   | - Endurance in cycles for X cells  | 18 |
| Tab      | le 12   | - Endurance in cycles for HR or XR cells   | 19 |
| Tab      | le 13   | - Permanent charge endurance for L, M, H or X cells  | 19 |
| Tab      | le 14   | - Permanent charge endurance for LT, MT or HT cells  | 21 |
| Tab      | le 15   | - Permanent charge endurance for LU, MU or HU cells  | 22 |
| Tab      | le 16   | - Overcharge at 0 °C   | 23 |
| Tab      | le 17   | - Charge and discharge at +55 °C   | 26 |
| Tab      | le 18   | - Constant discharge currents used for measurement of d.c. resistance  | 27 |
| Tab      | le 19   | - Sequence of tests for type approval for small prismatic and for button cells                                       | 28 |
| Tab      | le 20   | - Sequence of tests for type approval for cylindrical cells  | 29 |
| Tab      | le 21   | - Recommended test sequence for batch acceptance   | 30 |

**-4** -

61951-2 © IEC:2011

### INTERNATIONAL ELECTROTECHNICAL COMMISSION

# SECONDARY CELLS AND BATTERIES CONTAINING ALKALINE OR OTHER NON-ACID ELECTROLYTES – PORTABLE SEALED RECHARGEABLE SINGLE CELLS –

Part 2: Nickel-metal hydride

#### **FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61951-2 has been prepared by subcommittee 21A: Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC technical committee 21: Secondary cells and batteries.

This third edition cancels and replaces the second edition published in 2003 of which it constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- clause 4: addition of 2 parameters;
- clause 5: addition of cells type "S" and cells type "T";
- subclause 6.1.2: addition of new cylindrical cells;
- subclause 7.8: addition of a specific test for "S" cells.

61951-2 © IEC:2011

- 5 -

The text of this standard is based on the following documents:

| FDIS         | Report on voting |
|--------------|------------------|
| 21A/484/FDIS | 21A/487/RVD      |

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61951 series can be found, under the general title Secondary cells and batteries containing alkaline or other non-acid electrolytes – Portable sealed rechargeable single cells, on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- · replaced by a revised edition, or
- amended.



| This is a free preview | <ul> <li>Purchase the entire</li> </ul> | e publication at the link below: |
|------------------------|---|----------------------------------|
|------------------------|---|----------------------------------|

**Product Page** 

- Dooking for additional Standards? Visit Intertek Inform Infostore
- Dearn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation