



**NSAI**  
Standards

Irish Standard  
I.S. EN 1156:2013

# Wood-based panels - Determination of duration of load and creep factors

## I.S. EN 1156:2013

*Incorporating amendments/corrigenda/National Annexes issued since publication:*

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

*This document replaces:*  
ENV 1156:1998

*This document is based on:* EN 1156:2013  
*Published:* 26 April, 2013

This document was published under the authority of the NSAI and comes into effect on:  
26 April, 2013

**ICS number:**  
79.060.01

**NSAI**  
1 Swift Square,  
Northwood, Santry  
Dublin 9

T +353 1 807 3800  
F +353 1 807 3838  
E standards@nsai.ie  
W NSAI.ie

**Sales:**  
T +353 1 857 6730  
F +353 1 857 6729  
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

## Wood-based panels - Determination of duration of load and creep factors

Panneaux à base de bois - Détermination des facteurs de durée de charge et de fluage

Holzwerkstoffe - Bestimmung von Zeitstandfestigkeit und Kriechzahl

This European Standard was approved by CEN on 1 March 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Page

Foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Principle.....	4
4 Apparatus .....	4
5 Sampling of panels and preparation of test pieces .....	7
5.1 Sampling and cutting.....	7
5.2 Dimensions of test pieces .....	7
5.3 Conditioning.....	7
6 Procedure .....	8
6.1 Measurement of dimensions .....	8
6.2 Setting up the test rigs with test pieces.....	8
6.3 Determination of short-term bending strength .....	8
6.4 Determination of the duration of load and creep factors .....	8
6.4.1 General testing required .....	8
6.4.2 Testing for duration of load .....	9
6.4.3 Testing for creep .....	9
7 Expression of results .....	10
7.1 Duration of load factor .....	10
7.2 Creep factor.....	11
8 Test report .....	13
Annex A (informative) Provisional test method for medium-size test pieces.....	14
A.1 General .....	14
A.2 Principle.....	14
A.3 Apparatus .....	14
A.4 Sampling of panels and the preparation of test pieces.....	15
A.5 Procedure .....	15
A.6 Expression of results .....	15
A.7 Test report .....	15
Bibliography.....	16

## **Foreword**

This document (EN 1156:2013) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2013, and conflicting national standards shall be withdrawn at the latest by October 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes ENV 1156:1998.

Compared to ENV 1156:1998, the following significant technical modifications have been made:

- a) status changed from ENV to EN;
- b) accuracy of the deflection measurement changed from 0,001 mm to 0,01 mm.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This European Standard specifies a method of determining in a constant climate both a duration of load factor and a creep factor for wood-based panels stressed in flatwise bending with and without a shear component. Details of an alternative but provisional method employing medium sized test pieces are given in Annex A; this method can also be used for test pieces loaded under varying climates.

**NOTE** The duration of load factor is necessary to modify the characteristic strength values obtained in short-term structural tests in order to derive long-term values. The creep factor obtained in the test is used to predict a long-term deflection from the initial elastic deflection.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 310, *Wood-based panels — Determination of modulus of elasticity in bending and of bending strength*

EN 325, *Wood-based panels — Determination of dimensions of test pieces*

EN 326-1, *Wood-based panels — Sampling, cutting and inspection — Part 1: Sampling and cutting of test pieces and expression of test results*

EN 1058, *Wood-based panels — Determination of characteristic 5-percentile values and characteristic mean values*

EN 1995-1-1, *Eurocode 5: Design of timber structures — Part 1-1: General — Common rules and rules for buildings*

## 3 Principle

Determination in a constant climate of the load duration factor (loss in strength with time under load) and the creep factor (ratio of increase in deflection with time to the initial elastic deflection) in bending by applying and sustaining a constant moment over the central region of a test piece; both the time to failure, and the increase in deflection with time are measured.

## 4 Apparatus

**4.1 Measuring instruments** as specified in EN 325.

**4.2 A number of test rigs** (see Figure 1), that have essentially the following components:

**4.2.1 Two parallel cylindrical supports** of a length exceeding the width of the test piece and of diameter  $d = (15 \pm 0,5)$  mm.

The distance between the supports shall be adjustable, and each support shall be capable of rotating in its frame.

Two cylindrical loading rollers of the same length and diameter as the supports. These shall lie parallel to the supports, be capable of rotating, and be linked together with cross-arms of fixed length.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

- 
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
  - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-