

Irish Standard I.S. EN 1367-7:2014

Tests for thermal and weathering properties of aggregates - Part 7: Determination of resistance to freezing and thawing of Lightweight aggregates

© CEN 2014 No copying without NSAI permission except as permitted by copyright law.

#### I.S. EN 1367-7:2014

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

*NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.* 

*This document is based on:* EN 1367-7:2014 *Published:* 2014-04-02

This document was published		ICS number:
and comes into effect on:		91.100.15
2014-04-12		
		NOTE: If blank see CEN/CENELEC cover page
		·
NSAI	T +353 1	L 807 3800 Sales:
1 Swift Square,	F +353 1	L 807 3838 T +353 1 857 6730
Northwood, Santry	E standa	ards@nsai.ie F +353 1 857 6729
Dublin 9	W NSAI.i	ie W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

# EUROPEAN STANDARD

# EN 1367-7

# NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2014

ICS 91.100.15

**English Version** 

## Tests for thermal and weathering properties of aggregates - Part 7: Determination of resistance to freezing and thawing of Lightweight aggregates

Essais pour déterminer les propriétés thermiques et l'altérabilité des granulats - Partie 7: Détermination de la résistance au gel-dégel des granulats légers Prüfverfahren für thermische Eigenschaften und Verwitterungsbeständigkeit von Gesteinskörnungen - Teil 7: Bestimmung des Widerstandes von leichten Gesteinskörnungen gegen Frost-Tau-Wechsel

This European Standard was approved by CEN on 16 February 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. EN 1367-7:2014 E

This is a free page sample. Access the full version online. I.S. EN 1367-7:2014

EN 1367-7:2014 (E)

# Contents

Forewo	ord	.3
1	Scope	.4
2	Normative references	.4
3	Terms and definitions	.4
4	Principle	.4
5	Apparatus and materials	.5
6	Sampling	.5
7	Test specimens	.5
7.1	General	.5
7.2	Size of test specimens	.5
7.3	Preparation of test specimens	.6
8	Procedure	.6
8.1	Soaking	.6
8.2	Freezing in air and thawing in water	.6
9	Calculation and expression of results	.6
10	Test report	.7
10.1	Mandatory data	.7
10.2	Optional data	.7
Bibliog	· Iraphy	.8

# Foreword

This document (EN 1367-7:2014) has been prepared by Technical Committee CEN/TC 154 "Aggregates", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2014, and conflicting national standards shall be withdrawn at the latest by October 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

EN 1367 "Tests for thermal and weathering properties of aggregates" consists of the following parts:

- Part 1: Determination of resistance to freezing and thawing
- Part 2: Magnesium sulfate test
- Part 3: Boiling test for "Sonnenbrand Basalt"
- Part 4: Determination of drying shrinkage
- Part 5: Determination of resistance to thermal shock
- Part 6: Determination of resistance to freezing and thawing in the presence of salt (NaCl)
- Part 7: Determination of resistance to freezing and thawing of Lightweight Aggregates (the present document)
- Part 8: Determination of resistance to disintegration of Lightweight Aggregates

Test methods for other properties of aggregates are covered by parts of the following European Standards:

- EN 932, Tests for general properties of aggregates
- EN 933, Tests for geometrical properties of aggregates
- EN 1097, Tests for mechanical and physical properties of aggregates
- EN 1744, Tests for chemical properties of aggregates
- EN 13179, Tests for filler aggregate used in bituminous mixtures

NOTE This document supersedes the test methods described in EN 13055–1:2002, Annex C and EN 13055-2:2004, Annex B.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

### 1 Scope

This European Standard specifies the reference test method used for type testing, and in case of dispute, for determining the resistance to freezing and thawing of lightweight aggregates (LWA) in accordance with EN 13055. For other purposes, in particular for factory production control, other methods may be used provided that an appropriate working relationship with the reference method has been established. The test is applicable to LWA with particle size not less than 4 mm and up to a maximum size of 32 mm.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 932-1, Tests for general properties of aggregates - Part 1: Methods for sampling

EN 932-2, Tests for general properties of aggregates - Part 2: Methods for reducing laboratory samples

EN 932-5, Tests for general properties of aggregates - Part 5: Common equipment and calibration

EN 933-2, Tests for geometrical properties of aggregates - Part 2: Determination of particle size distribution - Test sieves, nominal size of apertures

EN 13055-1, Lightweight aggregates - Part 1: Lightweight aggregates for concrete, mortar and grout

EN 13055-2, Lightweight aggregates - Part 2: Lightweight aggregates for bituminous mixtures and surface treatments and for unbound and bound applications

### 3 Terms and definitions

For the purpose of this document, the terms and definitions given in EN 13055-1, EN 13055-2 and the following apply.

### 3.1

#### test specimen

sample used as in single determination when a test method requires more than one determination of a property

### 3.2

#### constant mass

mass determined by successive weighings performed 1 h apart and not differing by more than 0,1 %

Note 1 to entry: In many cases constant mass can be achieved after a test portion has been dried for a predetermined period in a specified oven at  $(110 \pm 5)$  °C. Test laboratories can determine the time required to achieve constant mass for specific types and sizes of sample dependent upon the drying capacity of the oven used.

## 4 Principle

Three test specimens of lightweight aggregates, having been soaked in water at atmospheric pressure, are subjected to 20 freeze-thaw cycles. This involves cooling down to -17,5 °C in air and then thawing in a water bath at about 20 °C. After completion of the freeze-thaw cycles, the loss of mass of the lightweight aggregates is recorded.



This is a free preview. Purchase the entire publication at the link below:

**Product Page** 

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation