This is a free page sample. Access the full version online.



Standard Recommendation S.R. CEN ISO/TS 16181:2011

Footwear - Critical substances potentially present in footwear and footwear components - Determination of phthalates in footwear materials (ISO/TS 16181:2011)

© NSAI 2011 No copying without NSAI permission except as permitted by copyright law.

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

٦

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

<i>This document replaces:</i>			
<i>This document is based or</i> CEN ISO/TS 16181:2011	n: Published: 27 July, 2011		
This document was published under the authority of the NSAI and comes into effect on: 27 July, 2011			<u>ICS number:</u> 61.060
NSAI 1 Swift Square, Northwood, Santry Dublin 9	T +353 1 807 3800 F +353 1 807 3838 E standards@nsai.ie W NSAI.ie	Sales: T +353 1 857 6730 F +353 1 857 6729 W standards.ie	
Údarás um Chaighdeáin Náisiúnta na hÉireann			

TECHNICAL SPECIFICATION SPÉCIFICATION TECHNIQUE TECHNISCHE SPEZIFIKATION

CEN ISO/TS 16181

July 2011

ICS 61.060

English Version

Footwear - Critical substances potentially present in footwear and footwear components - Determination of phthalates in footwear materials (ISO/TS 16181:2011)

Chaussures - Substances critiques potentiellement présentes dans les chaussures et les composants des chaussures - Détermination des phtalates dans les matériaux des chaussures (ISO/TS 16181:2011) Schuhe - Möglicherweise in Schuhen und Schuhbestandteilen vorhandene kritische Substanzen -Bestimmung von Phthalaten in Schuhwerkstoffen (ISO/TS 16181:2011)

This Technical Specification (CEN/TS) was approved by CEN on 21 May 2011 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2011 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. CEN ISO/TS 16181:2011: E

CEN ISO/TS 16181:2011 (E)

Foreword

This document (CEN ISO/TS 16181:2011) has been prepared by Technical Committee CEN/TC 309 "Footwear", the secretariat of which is held by AENOR, in collaboration with Technical Committee ISO/TC 216 "Footwear".

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

This page is intentionally left BLANK.

S.R. CEN ISO/TS 16181:2011 TECHNICAL SPECIFICATION

ISO/TS 16181

First edition 2011-07-15

Footwear — Critical substances potentially present in footwear and footwear components — Determination of phthalates in footwear materials

Chaussures — Substances critiques potentiellement présentes dans les chaussures et les composants des chaussures — Détermination des phtalates dans les matériaux des chaussures



Reference number ISO/TS 16181:2011(E)

ISO/TS 16181:2011(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 16181 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in collaboration with Technical Committee ISO/TC 216, *Footwear*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Introduction

Phthalates are commonly used as plasticizers in polymers. Toxicological concern has arisen due to their potential effect as endocrine disruptors and some of the listed phthalates are toxic in reproduction. The level of media publicity will ensure that their use continues to be of concern to consumers.

Phthalates are controversial because high doses of many phthalates have shown hormonal activity in rodent studies. Studies on rodents involving large amounts of phthalates have shown damage to the liver, the kidneys, the lungs, and the developing testes.

This Technical Specification calls for the use of substances and/or procedures that can be injurious to health if appropriate precautions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

Footwear — Critical substances potentially present in footwear and footwear components — Determination of phthalates in footwear materials

SAFETY PRECAUTIONS — Persons using this Technical Specification should be familiar with normal laboratory practice. This Technical Specification does not claim to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

IMPORTANT — It is absolutely essential that tests conducted according to this Technical Specification be carried out by suitably trained staff.

1 Scope

This Technical Specification specifies a test method to determine the presence of phthalate compounds. This test method is applicable to all types of footwear materials.

NOTE 1 This test method can also be used to determine plasticizers other than those listed in 3.2, subject to validation.

NOTE 2 ISO/TR 16178 defines which materials are concerned by this determination.

2 Principle

The aim of the method is to extract phthalates in footwear materials such as leather, textile, polymer, coated materials or others. This method uses extraction apparatus with *n*-hexane/acetone as solvent.

The total *n*-hexane/acetone extractable phthalate plasticizer content is calculated by weight with gas chromatography-mass spectrometry (GC-MS) detection to identify and quantify individual phthalates.

3 Apparatus and reagents

3.1 Apparatus

- **3.1.1 Scales**, resolution of 1 mg.
- 3.1.2 Flask, 50 ml.
- 3.1.3 Water-cooled condenser.
- 3.1.4 Spark-proof heating mantle/water bath.
- 3.1.5 Ultrasonic bath.
- 3.1.6 Microwave extractor.
- 3.1.7 Steam bath or rotary evaporator.



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation