



NSAI
Standards

Irish Standard
I.S. EN 2648:2013

Aerospace series - Washers, concave, in alloy steel, cadmium plated

I.S. EN 2648:2013

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 2648:2013

Published:

2013-12-18

This document was published under the authority of the NSAI and comes into effect on:

2013-12-28

ICS number:

49.030.50

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 2648

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2013

ICS 49.030.50

Supersedes EN 2648:1995

English Version

Aerospace series - Washers, concave, in alloy steel, cadmium plated

Série aérospatiale - Rondelles concaves, en acier allié, cadmiées

Luft- und Raumfahrt - Scheiben, für Neigungsausgleich, aus legiertem Stahl, verkadmet

This European Standard was approved by CEN on 28 September 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	3
1 Scope	4
2 Normative references	4
3 Required characteristics	4
4 Designation	6
5 Marking	6
6 Qualification	6

Foreword

This document (EN 2648:2013) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2014, and conflicting national standards shall be withdrawn at the latest by June 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 2648:1995.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 2648:2013 (E)

1 Scope

This standard specifies the characteristics of concave washers, in alloy steel, cadmium plated, maximum operating temperature 235 °C.

They are intended to be used with nuts to EN 2647.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2133, *Aerospace series — Cadmium plating of steels with specified tensile strength $\leq 1\,450$ MPa, copper, copper alloys and nickel alloys*

EN 2424, *Aerospace series — Marking of aerospace products*

EN 2448, *Aerospace series — Steel FE-PL1503 (35CrMo4) — $900\text{ MPa} \leq R_m \leq 1\,100\text{ MPa}$ — Bars — $D_e \leq 40\text{ mm}$*

EN 2542, *Aerospace series — Steel FE-PL1502 (25CrMo4) — Annealed — Bar and wire — $D_e \leq 40\text{ mm}$ — for prevailing torque nuts*

EN 2647, *Aerospace series — Nuts, hexagonal, self-locking, ball seat, in alloy steel, cadmium plated, MoS₂ lubricated — Classification: 900 MPa (at ambient temperature) / 235 °C*

EN 3330, *Aerospace series — Steel FE-PL1503 (35CrMo4) — Annealed — Bar and wire — $D_e \leq 40\text{ mm}$ — for prevailing torque nuts*

3 Required characteristics

3.1 Configuration – Dimensions – Masses

See Figure 1 and Table 1. Dimensions and tolerances are expressed in millimetres and apply after surface treatment.

3.2 Materials

Steel FE-PL1502 (25CrMo4), chemical composition in conformity with EN 2542, characteristics after manufacture: $1\,250\text{ MPa} \leq R_m \leq 1\,400\text{ MPa}$, $40 \leq \text{HRC} \leq 43$.

Or steel FE-PL1503 (35CrMo4), chemical composition in conformity with EN 3330 or EN 2448 or equivalent, characteristics after manufacture: $1\,250\text{ MPa} \leq R_m \leq 1\,400\text{ MPa}$, $40 \leq \text{HRC} \leq 43$.

3.3 Surface treatment

EN 2133, 8 μm to 14 μm .

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-