



NSAI
Standards

Irish Standard
I.S. EN 12390-13:2013

Testing hardened concrete - Part 13: Determination of secant modulus of elasticity in compression

I.S. EN 12390-13:2013

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:

This document is based on:
EN 12390-13:2013

Published:
5 November, 2013

This document was published under the authority of the NSAI and comes into effect on:
5 November, 2013

ICS number:

91.100.30

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

ICS 91.100.30

English Version

Testing hardened concrete - Part 13: Determination of secant modulus of elasticity in compression

Essais pour béton durci - Partie 13: Détermination du module sécant d'élasticité en compression

Prüfung von Festbeton - Teil 13: Bestimmung des Elastizitätsmoduls unter Druckbelastung (Sekantenmodul)

This European Standard was approved by CEN on 21 September 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions, symbols and scripts	4
4	Principle.....	6
5	Apparatus	6
6	Test specimens	7
7	Method	7
8	Calculation of secant modulus of elasticity.....	12
9	Test report	13
10	Precision.....	13
Bibliography		14

Foreword

This document (EN 12390-13:2013) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

It is based on an extensive investigation and comparison of existing National Standards: ASTM, BS, DIN, ISO, NORD TEST and UNI followed by the analysis of a test programme involving five laboratories carried out by UNI.

This standard is one of a series concerned with testing concrete.

The series EN 12390, *Testing hardened concrete*, consists of the following parts:

- *Part 1: Shape, dimensions and other requirements of specimens and moulds*
- *Part 2: Making and curing specimens for strength tests*
- *Part 3: Compressive strength of test specimens*
- *Part 4: Compressive strength - Specification for testing machines*
- *Part 5: Flexural strength of test specimens*
- *Part 6: Tensile splitting strength of test specimens*
- *Part 7: Density of hardened concrete*
- *Part 8: Depth of penetration of water under pressure*
- *Part 13: Determination of secant modulus of elasticity in compression*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the method for the determination of the secant modulus of elasticity in compression of hardened concrete on test specimens which may be cast or taken from a structure.

The test method allows the determination of two secant moduli of elasticity: the *initial modulus*, $E_{C,0}$ measured at first loading and the *stabilized modulus*, $E_{C,S}$ measured after three loading cycles.

Two different test methods are given. The first (method A) is for determination of both initial and stabilized moduli, the second (method B) is for determination of stabilized modulus only.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12390-1, *Testing hardened concrete — Part 1: Shape, dimensions and other requirements of specimens and moulds*

EN 12390-2, *Testing hardened concrete — Part 2: Making and curing specimens for strength tests*

EN 12390-3, *Testing hardened concrete — Part 3: Compressive strength of test specimens*

EN 12390-4, *Testing hardened concrete — Part 4: Compressive strength – Specification for testing machines*

EN 12504-1:2009, *Testing concrete in structures — Part 1: Cored specimens – Taking, examining and testing in compression*

EN ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing (ISO 9513)*

3 Terms and definitions, symbols and scripts

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

initial secant modulus of elasticity

$E_{C,0}$

secant slope of the stress strain curve at first loading

3.1.2

stabilized secant modulus of elasticity

$E_{C,S}$

secant slope of the stress strain curve after three loading cycles

3.1.3

base or gauge length

length used as reference base for strain measurement

3.1.4

measuring line

straight line laying on the lateral surface of the specimen and parallel to the vertical axis (see Figure 1)

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-