



NSAI
Standards

Irish Standard
I.S. EN 16653:2015

Rubber or plastics-coated fabrics -
Determination of stitch tear resistance (using
a needle) - Test method

I.S. EN 16653:2015

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 16653:2015

Published:

2015-03-25

This document was published under the authority of the NSAI and comes into effect on:

2015-04-11

ICS number:

59.080.40

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 16653

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2015

ICS 59.080.40

English Version

Rubber or plastics-coated fabrics - Determination of stitch tear resistance (using a needle) - Test method

Supports textiles revêtus de caoutchouc ou de plastique -
Détermination de la résistance au déchirement au point de
couture (à l'aide d'une aiguille) - Méthode d'essai

Mit Kautschuk oder Kunststoff beschichtete Textilien -
Bestimmung des Stichausreißwiderstands (unter
Verwendung einer Nadel) - Prüfverfahren

This European Standard was approved by CEN on 7 February 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
	Foreword	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Test apparatus and materials	4
5	Sampling and conditioning	6
6	Test method	7
7	Expression of results	8
8	Test report	8

Foreword

This document (EN 16653:2015) has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2015 and conflicting national standards shall be withdrawn at the latest by September 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 16653:2015 (E)

1 Scope

This European Standard specifies a method for the determination of the resistance of the seams of rubber or plastic-coated fabrics against tearing out a needle perpendicular to the stitching direction. This resistance is characterized by determining the stitch tear force.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 2231, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing (ISO 2231)*

EN ISO 2286-3, *Rubber- or plastics-coated fabrics — Determination of roll characteristics — Part 3: Method for determination of thickness (ISO 2286-3)*

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1)*

EN ISO 10012, *Measurement management systems — Requirements for measurement processes and measuring equipment (ISO 10012)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

stitch tear resistance

resistance to pull a needle from a sample perpendicular to the stitching direction

3.2

stitch tear force

stitch tear resistance, recorded as the maximum tearing force

3.3

stitch tear strength

stitch tear force divided by the thickness

4 Test apparatus and materials

The following test apparatus and materials shall be used:

4.1 CRE machine.

Metrological confirmation system of the tensile-testing machine shall be in accordance with EN ISO 10012.

The constant-rate-of-extension (CRE) machine shall have the general characteristics given in 4.1.1 to 4.1.4.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-