



NSAI
Standards

Irish Standard
I.S. EN 16594:2014

Packaging - Rigid plastic containers - PET finish 26/22 (12,0)

I.S. EN 16594:2014

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 16594:2014

Published:

2014-10-29

This document was published under the authority of the NSAI and comes into effect on:

2014-11-26

ICS number:

55.100

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 16594

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2014

ICS 55.100

English Version

Packaging - Rigid plastic containers - PET finish 26/22 (12,0)

Emballage - Récipients en plastique rigide - Bague PET
26/22 (12,0)

Verpackung - Formstabile Kunststoffbehälter - PET-
Verschlussmundstück 26/22 (12,0)

This European Standard was approved by CEN on 6 September 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword		3
Introduction		4
1 Scope		5
2 Dimensions		5
3 Requirements		5
Bibliography		8

Foreword

This document (EN 16594:2014) has been prepared by Technical Committee CEN/TC 261 “Packaging”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2015, and conflicting national standards shall be withdrawn at the latest by April 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 16594:2014 (E)

Introduction

This European Standard is based on CE.T.I.E. (International Technical Centre for Bottling and Packaging) data sheet GME 30.28 (2011) [1].

Efficient packaging is of great importance for the distribution and the protection of goods. Insufficient or inappropriate packaging can lead to damage or wastage of the contents of the pack.

1 Scope

This European Standard specifies the design and dimensions of the 26 mm screw finish with three thread starts for flat waters and non-carbonated beverages.

This finish can be used for aseptic filling and filling with nitrogen charge (internal overpressure inferior to 1 bar max).

The dimension (12,0) is the height in millimetres from the top of finish to the bottom of the support ledge.

This finish is designed to accept a tamper evident plastic closure only. During first opening, the tamper evident band will separate from the closure shell and remain on a one way bottle neck or like bottles in the returnable market the tamper evident band will tear but will remain connected to the closure shell.

2 Dimensions

2.1 The design and dimensions of the finish shall be as shown in Figure 1. Dimensions are those of the preform.

2.2 Dimensions of the 3 thread starts 120° apart:

— 180° of full thread per lead:

— R 6,25 mm thread run-in;

— R 6,25 mm thread run-out.

Lead: 6,5 mm (travel per turn).

2.3 General tolerance for others radii: $\pm 0,13$ mm.

2.4 Weight on height 12,0 mm: 1,95 g (density = $1,335 \text{ g/cm}^3$).

3 Requirements

The finish is a top, side and inside seal finish.

This finish shall be smooth and free of any defects that will contribute to liquid leaks or pressure loss. Flash not to exceed 0,13 mm per side, and not to be continuous.

The diameter under the support ledge shown at 24,25 mm refers to the preform and should not exceed 24,75 maximum on the blown bottle.

On the blown bottle, the control diameter C shall be free of any defects to a depth of 4 mm in the internal bore and across the sealing surface of the finish.

Requirements for good closure application on finish:

— 0,13 mm max out-of-parallel sealing surface with neck support ledge is allowed.

— an offset or vertical mismatch of thread is not to exceed 0,10 mm at the mould seam.

Variations in $\varnothing E$ are to follow uniformly those of $\varnothing T$.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-