



NSAI
Standards

Irish Standard
I.S. EN 1426:2015

Bitumen and bituminous binders - Determination of needle penetration

I.S. EN 1426:2015

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 1426:2015

Published:

2015-07-01

*This document was published
under the authority of the NSAI
and comes into effect on:*

2015-07-18

ICS number:

75.140

91.100.50

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN 1426

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2015

ICS 75.140; 91.100.50

Supersedes EN 1426:2007

English Version

Bitumen and bituminous binders - Determination of needle penetration

Bitumes et liants bitumineux - Détermination de la pénétrabilité à l'aiguille

Bitumen und bitumenhaltige Bindemittel - Bestimmung der Nadelpenetration

This European Standard was approved by CEN on 27 May 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN 1426:2015 (E)

Contents	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	4
5 Apparatus	5
6 Sampling	7
7 Procedure	8
8 Expression of results	9
9 Precision	10
10 Test report	10
Annex A (informative) Characteristics of thermometers	13
Bibliography	14

Foreword

This document (EN 1426:2015) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

This document supersedes EN 1426:2007.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2016, and conflicting national standards shall be withdrawn at the latest by January 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

The major changes to the standard at this revision have been:

- the normative reference to mercury thermometers has been deleted (see 5.7 and Annex A) and
- Table 1 and the description of 6.4 have been clarified and improved.

Apart from this various smaller adjustments have been made.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 1426:2015 (E)

1 Scope

This European Standard specifies a method for determining the consistency of bitumen and bituminous binders. Normal procedure is described for penetrations up to $(330 \times 0,1)$ mm, but for penetrations above this value, up to $(500 \times 0,1)$ mm, different operating parameters are necessary.

WARNING — Use of this European Standard may involve hazardous materials, operations and equipment. This European Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this European Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders - Sampling bituminous binders*

EN 1425, *Bitumen and bituminous binders - Characterization of perceptible properties*

EN 1427, *Bitumen and bituminous binders - Determination of the softening point - Ring and Ball method*

EN 10088-3, *Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes*

EN 12594, *Bitumen and bituminous binders - Preparation of test samples*

EN 12597, *Bitumen and bituminous binders - Terminology*

EN ISO 6508-1, *Metallic materials - Rockwell hardness test - Part 1: Test method (ISO 6508-1)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12597 and the following applies.

3.1

penetration

consistency, expressed as the distance in tenths of a millimetre that a standard needle will penetrate vertically into a sample of the material under specified conditions of temperature, load and loading duration

4 Principle

The penetration of a standard needle into a conditioned test sample shall be measured. For penetrations up to approximately $(330 \times 0,1)$ mm the operating parameters shall be a test temperature of 25 °C, an applied load of 100 g, and a loading duration of 5 s. For penetrations expected above approximately $(330 \times 0,1)$ mm, the test temperature shall be reduced to 15 °C but the operating parameters of the applied load and the loading duration remain unchanged. Other conditions can be applied; also to reflect different purposes – e.g. 200 g, 60 s and 5 °C may be used as indicative for low temperature performance.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-