



NSAI
Standards

Irish Standard
I.S. EN ISO 9453:2014

Soft solder alloys - Chemical compositions and forms (ISO 9453:2014)

I.S. EN ISO 9453:2014

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN ISO 9453:2014

Published:

2014-08-06

*This document was published
under the authority of the NSAI
and comes into effect on:*

2014-09-02

ICS number:

25.160.50

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN ISO 9453

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 2014

ICS 25.160.50

Supersedes EN ISO 9453:2006

English Version

Soft solder alloys - Chemical compositions and forms (ISO 9453:2014)

Alliages de brasage tendre - Compositions chimiques et formes (ISO 9453:2014)

Weichlote - Chemische Zusammensetzung und Lieferformen (ISO 9453:2014)

This European Standard was approved by CEN on 10 July 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN ISO 9453:2014 (E)

Contents	Page
Foreword.....	3

Foreword

This document (EN ISO 9453:2014) has been prepared by Technical Committee ISO/TC 44 “Welding and allied processes” in collaboration with Technical Committee CEN/TC 121 “Welding” the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2015, and conflicting national standards shall be withdrawn at the latest by February 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9453:2006.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 9453:2014 has been approved by CEN as EN ISO 9453:2014 without any modification.

This page is intentionally left blank

INTERNATIONAL STANDARD

**ISO
9453**

Third edition
2014-08-01

Soft solder alloys — Chemical compositions and forms

Alliages de brasage tendre — Compositions chimiques et formes



Reference number
ISO 9453:2014(E)

© ISO 2014

ISO 9453:2014(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Chemical composition	1
5 Forms of delivery	1
5.1 General.....	1
5.2 Unit of product.....	2
6 Sampling and analysis	2
7 Marking, labelling and packaging	2
Annex A (informative) Comparison between alloy numbers in ISO 9453 and short names and chemical compositions according to IEC 61190-1-3	12
Annex B (informative) Patented alloys and patent holder list	15
Bibliography	16

ISO 9453:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 44, *Welding*, Subcommittee SC 12, *Soldering materials*.

This third edition cancels and replaces the second edition (ISO 9453:2006), which has been technically revised.

Request for an official interpretation of technical aspects of this International Standard should be directed to the relevant secretariat of ISO/TC 44/SC 12 "Soldering materials" via the user's national standardization body; a listing of these bodies can be found at: <http://www.iso.org>.

Introduction

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of patents concerning soft solder alloy compositions given in [Table 3](#).

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has ensured the ISO that he/she is willing to negotiate licences either free of charge or under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from [Annex B](#).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any or all such patent rights.

ISO (www.iso.org/patents) maintains online databases of patents relevant to their standards. Users are encouraged to consult the databases for the most up to date information concerning patents.

Soft solder alloys — Chemical compositions and forms

1 Scope

WARNING — National or regional regulations may limit the employment of certain alloys.

This International Standard specifies the requirements for chemical composition for soft solder alloys containing two or more of tin, lead, antimony, copper, silver, bismuth, zinc, indium and/or cadmium.

An indication of the forms generally available is also included.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3677, *Filler metal for soft soldering, brazing and braze welding — Designation*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

soft solder

metallic filler material which is used to join metallic parts and which has a melting temperature (liquidus) lower than that of the parts to be joined and, usually, lower than 450 °C and which wets the parent metals

3.2

batch

collection of one or more units of product, made in a single production operation

4 Chemical composition

The chemical composition of the soft solder, sampled and analysed in accordance with [Clause 6](#), shall be as given for the appropriate material in [Table 1](#) or [Table 2](#).

5 Forms of delivery

5.1 General

Soft solders conforming to this International Standard shall be supplied in one of the following forms: ingot, slab, stick, bar, rod, wire, pellets, preforms, rings, spheres, ribbons, powder or soldering pastes. Solder shall be uniform in quality and free from detrimental conditions such as contamination or surface oxide that prevent melting and flow in a manner suitable for the intended application.

NOTE 1 Solders supplied in the form of rod, wire, or preforms can be supplied with or without an integral flux, subject to agreement between the supplier and the purchaser.

NOTE 2 Not all the solder compositions given in the tables are necessarily available in all the product forms listed.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-