

Irish Standard I.S. EN ISO 6506-3:2014

Metallic materials - Brinell hardness test - Part 3: Calibration of reference blocks (ISO 6506-3:2014)

 $\ \odot$ CEN 2014 No copying without NSAI permission except as permitted by copyright law.

I.S. EN ISO 6506-3:2014

2014-10-11

Incorporating amendments/corrigenda/National Annexes issued since publication

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R.~xxx: Standard~Recommendation-recommendation~based~on~the~consensus~of~an~expert~panel~and~subject~to~public~consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on: Published:

EN ISO 6506-3:2014 2014-09-24

This document was published ICS number:

under the authority of the NSAI
and comes into effect on: 77.040.10

NOTE: If blank see CEN/CENELEC cover page

NSAI T +353 1 807 3800 Sales:

 1 Swift Square,
 F +353 1 807 3838
 T +353 1 857 6730

 Northwood, Santry
 E standards@nsai.ie
 F +353 1 857 6729

 Dublin 9
 W NSAI.ie
 W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

EUROPEAN STANDARD

EN ISO 6506-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2014

ICS 77.040.10

Supersedes EN ISO 6506-3:2005

English Version

Metallic materials - Brinell hardness test - Part 3: Calibration of reference blocks (ISO 6506-3:2014)

Matériaux métalliques - Essai de dureté Brinell - Partie 3: Étalonnage des blocs de référence (ISO 6506-3:2014) Metallische Werkstoffe - Härteprüfung nach Brinell - Teil 3: Kalibrierung von Härtevergleichsplatten (ISO 6506-3:2014)

This European Standard was approved by CEN on 30 August 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN ISO 6506-3:2014 (E)

^ -	- 4 -	- 4 -
1:0	nte	nte
\mathbf{v}	IILE	IILO

	Page
Foreword	3

EN ISO 6506-3:2014 (E)

Foreword

This document (EN ISO 6506-3:2014) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee ECISS/TC 101 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2015, and conflicting national standards shall be withdrawn at the latest by March 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6506-3:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6506-3:2014 has been approved by CEN as EN ISO 6506-3:2014 without any modification.

This is a free page sample. Access the full version online.

This page is intentionally left blank

This is a free page sample. Access the full version online. I.S. EN ISO 6506-3:2014

INTERNATIONAL STANDARD

ISO 6506-3

Third edition 2014-10-01

Metallic materials — Brinell hardness test —

Part 3: Calibration of reference blocks

Matériaux métalliques — Essai de dureté Brinell — Partie 3: Étalonnage des blocs de référence



ISO 6506-3:2014(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

ISO 6506-3:2014(E)

Co	ntents	Page
Fore	eword	iv
1	Scope	1
2	Normative references	
3	Manufacture of reference blocks	1
4	Calibration machine	2
5	Calibration procedure	3
6	Number of indentations	3
7	Non-uniformity of reference block	4
8	Marking	4
9	Validity	5
Ann	nex A (informative) Uncertainty of the mean hardness value of reference blocks	6
Bibl	liography	10

ISO 6506-3:2014(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

This third edition cancels and replaces the second edition (ISO 6506-3:2005), which has been technically revised.

ISO 6506 consists of the following parts, under the general title *Metallic materials* — *Brinell hardness test*:

- Part 1: Test method
- Part 2: Verification and calibration of testing machines
- Part 3: Calibration of reference blocks
- Part 4: Tables of hardness values

Metallic materials — Brinell hardness test —

Part 3:

Calibration of reference blocks

1 Scope

This part of ISO 6506 specifies a method for the calibration of reference blocks to be used in the indirect verification of Brinell hardness testing machines as described in ISO 6506-2.

The procedures necessary to ensure metrological traceability of the calibration machine are also specified.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 376, Metallic materials — Calibration of force-proving instruments used for the verification of uniaxial testing machines

ISO 6506-1:2014, Metallic materials — Brinell hardness test — Part 1: Test method

ISO 6506-2:2014, Metallic materials — Brinell hardness test — Part 2: Verification and calibration of testing machines

3 Manufacture of reference blocks

3.1 The block shall be specially manufactured for use as a reference block.

NOTE Attention is drawn to the need to use a manufacturing process which will give the necessary homogeneity, stability of structure, and uniformity of surface hardness.

- **3.2** Each metal block to be calibrated shall be of a thickness not less than
- 16 mm for 10 mm balls,
- 12 mm for 5 mm balls, or
- 6 mm for smaller balls.

NOTE 12 mm for 10 mm balls can be used only if the hardness of the reference block is greater than 150 HBW.

- **3.3** The reference blocks shall be free of magnetism. It is recommended that the manufacturer shall ensure that the blocks, if of steel, have been demagnetized at the end of the manufacturing process.
- **3.4** The flatness of the two surfaces and the parallelism of the reference block shall be in accordance with $\underline{\text{Table 1}}$.



This is a free preview	 Purchase the entire 	e publication at the link below:
------------------------	---	----------------------------------

Product Page

- Dooking for additional Standards? Visit Intertek Inform Infostore
- Dearn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation