



NSAI
Standards

Irish Standard
I.S. EN 16128:2015

Ophthalmic optics - Reference method for the testing of spectacle frames and sunglasses for nickel release

I.S. EN 16128:2015

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 16128:2015

Published:

2015-11-04

This document was published under the authority of the NSAI and comes into effect on:

2015-11-22

ICS number:

11.040.70

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 16128:2015 is the adopted Irish version of the European Document EN 16128:2015, Ophthalmic optics - Reference method for the testing of spectacle frames and sunglasses for nickel release

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

EUROPEAN STANDARD

EN 16128

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2015

ICS 11.040.70

Supersedes CEN/TS 16677:2014, EN 16128:2011

English Version

Ophthalmic optics - Reference method for the testing of spectacle frames and sunglasses for nickel release

Optique ophtalmique - Méthode d'essai de référence
relative à la libération du nickel par les montures de
lunettes et les lunettes de soleil

Augenoptik - Referenzverfahren für die Bestimmung
der Nickellässigkeit von Brillenfassungen und
Sonnenbrillen

This European Standard was approved by CEN on 19 September 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
European foreword.....	4
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	7
4 Principle	8
5 Selection of test samples	8
6 Simulation of wear and corrosion.....	9
6.1 Preparation of test samples	9
6.2 Procedure.....	10
7 Coating test.....	10
7.1 General.....	10
7.2 Apparatus and consumables.....	10
7.3 Preparation of test samples for the coating test.....	11
7.3.1 Parts to be tested.....	11
7.3.2 Dismantling and/or cutting and/or masking	11
7.3.3 Determination of test area.....	13
7.3.4 Preparation of electrical contact area	13
7.4 Preparation of saline solution.....	13
7.5 Procedure.....	13
7.5.1 Preparation of the electro-chemical cell	13
7.5.2 Insertion and connection of the test part in the electro-chemical cell.....	14
7.5.3 Determination of open circuit potential and measurement of electrochemical impedance of test samples.....	14
7.5.4 Calibration and verification of the equipment.....	15
7.6 Calculation of results	15
7.6.1 General.....	15
7.6.2 Criteria for pass or fail of the test sample	15
7.7 Test report.....	15
8 Release of nickel and its quantitative analytical detection (migration test)	16
8.1 General.....	16
8.2 Apparatus and consumables.....	16
8.3 Preparation of test samples for the migration test.....	18
8.3.1 Parts to be tested.....	18
8.3.2 Guidance on selection of test areas on the parts to be tested	18
8.3.3 Dismantling and degreasing	19
8.4 Procedure.....	19
8.4.1 Preparation of test paper including determination of its area	19
8.4.2 Preparation of artificial sweat solution	20
8.4.3 Applying artificial sweat solution to the test paper and attaching it to the test sample....	21
8.4.4 Blank sample	22
8.4.5 Incubation of test sample with test paper attached (release of nickel into paper)	22
8.4.6 Retrieval of the test paper from the test samples	22

8.4.7	Analysis of the test papers for nickel	22
8.5	Calculation of migration test results	24
8.6	Interpretation of migration test results	25
8.6.1	General	25
8.6.2	Assessment of compliance.....	25
8.7	Test report	25
Annex A	(informative) Cutting and masking of test samples (Coating test).....	27
A.1	Fronts.....	27
A.2	Sides (temples)	28
Annex B	(normative) Selection of test areas and application of the test paper (Migration	
	test)	29
B.1	General	29
B.2	Rims	29
B.3	Bridge.....	30
B.4	Brace bar.....	31
B.5	Sides.....	32
B.6	Trims	34
	Bibliography	35

EN 16128:2015 (E)**European foreword**

This document (EN 16128:2015) has been prepared by Technical Committee CEN/TC 170 "Ophthalmic optics", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2016, and conflicting national standards shall be withdrawn at the latest by November 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 16128:2011 and CEN/TS 16677:2014.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports the harmonising effect of a restriction adopted under Regulation (EC) No 1907/2006 (REACH) of the European Parliament and the Council.

Compared to EN 16128:2011 and CEN/TS 16677:2014, the following changes have been made:

- a) Compared to EN 16128:2011, the reference test method has been substantially revised:

In the method according to EN 16128:2011 the parts to be tested for nickel release are placed in an artificial sweat test solution for one week. The concentration of dissolved nickel in the solution is determined by atomic absorption spectrometry, inductively-coupled plasma spectrometry or other appropriate analytical method.

The present standard provides, for parts with an organic coating, a coating test based on Electrochemical Impedance Spectroscopy (EIS). The coating test aims at demonstrating that the coating is of sufficient quality to prevent the release of nickel, thereby ensuring that the test sample's nickel release does not exceed the regulatory limit.

For parts without an organic coating, the present standard specifies a migration test. The migration test makes provision for quantitative testing for the amount of nickel released, to determine whether or not the model's nickel release exceeds the regulatory limit. The migration test comprises two steps: Release of nickel by artificial sweat solution into a test paper and the subsequent quantitative analytical detection of the nickel released into the paper.

See also the principle described in Clause 4.

- b) Compared to CEN/TS 16677:2014 the revisions and refinements made are relatively minor, as follows:

For the coating test, see Clause 7:

Amendment of the calculation and presentation of the test result including amendment of the threshold value (see 7.6);

The dummy or test lenses used in the simulation of wear and corrosion are to be kept in the frame.

For the migration test, see Clause 8:

Inclusion of the requirement to prepare and analyze a blank sample with every batch of test samples, along with the relevant specifications of sample preparation and procedure (see 8.4.4);

Specification that the incubation shall be made using a climate chamber; the previously permissible alternative to use an oven with a container for insertion of the test samples has been deleted (see 8.4.5);

Inclusion of more detailed specifications as to the permissible and non-permissible combination of the test papers from the various test areas for the analysis;

Inclusion of directions on how to proceed in the case that the design of a model does not allow the application of the test paper at (one of) the specified location(s);

Amendment of the procedure for the application and sealing of the test paper onto the test area using the sealing film; as an alternative to wrapping with the sealing film it is now also permissible to use a folding technique; see the revised Annex B;

Recommendation that the time between the retrieval of the test papers from the test samples and their extraction and analysis does not exceed 3 d (see 8.4.6).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 16128:2015 (E)

Introduction

This document has been prepared under Mandate M/448 issued by the European Commission in the framework of Regulation (EC) No 1907/2006, REACH, in particular Commission Regulation (EC) No 552/2009 of 22 June 2009 amending regulation (EC) No 1907/2006 of the European Parliament and of the Council on the Registration, Evaluation, Authorization and restriction of Chemicals (REACH) as regards Annex XVII RESTRICTIONS ON THE MANUFACTURE, PLACING ON THE MARKET AND USE OF CERTAIN DANGEROUS SUBSTANCES, PREPARATIONS AND ARTICLES.

The aim of the mandate is the revision of the method of analysis to detect the release of nickel from spectacle frames and sunglasses.

The availability of the new reference method for the determination of the release of nickel will provide the reliable framework to enforce the limit value for nickel release of 0,5 µg/cm²/week set forth by European Regulation. It will ensure a uniform application and control of the European legislation in all member states.

Harmonizing the test method for nickel release in all member states is vital with a view to protecting effectively the health of the end consumer, that is, the spectacle wearer. Nickel allergy is still the most frequent contact allergy in Europe and a significant health issue.

1 Scope

This European Standard specifies the reference method for the testing of spectacle frames, ready-to-wear spectacles, sunglasses and other items for eye and face protection for nickel release.

The reference method supports the demonstration of conformity with the limit value for nickel release of 0,5 µg/cm²/week set forth by European Regulation.

The reference method involves the procedural steps shown in Figure 1 and described in Clause 4.

This document applies to those parts of metal spectacle frames and those metal parts of combination spectacle frames that are intended to come into direct and prolonged contact with the skin of the wearer. This document also applies to those relevant metal parts of ready-to-wear spectacles, sunglasses and other items for eye and face protection.

NOTE The reference method for articles apart from spectacle frames, ready-to-wear spectacles, sunglasses and other items for eye and face protection is specified in EN 1811.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12472, *Method for the simulation of wear and corrosion for the detection of nickel release from coated items*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

EN ISO 11380, *Optics and optical instruments — Ophthalmic optics — Formers (ISO 11380)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

model

spectacle frame, ready-to-wear spectacles, sunglass or other item used for eye and face protection produced to a common design, using the same materials and surface treatment, and to which the scope of this document applies

3.2

test sample

spectacle frame, ready-to-wear spectacles, sunglass or other item used for eye and face protection submitted for testing

Note 1 to entry: Fronts or sides may be submitted separately for testing.

3.3

test part

part of a test sample that is intended to come into direct and prolonged contact with the skin and is due to be tested

Note 1 to entry: These parts are defined in 7.3.1 (for the coating test) and in 8.3.1 (for the migration test).

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-