



NSAI
Standards

Irish Standard
I.S. EN 336:2013

Structural timber - Sizes, permitted deviations

© CEN 2013

No copying without NSAI permission except as permitted by copyright law.

I.S. EN 336:2013

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard – national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation - recommendation based on the consensus of an expert panel and subject to public consultation.

SWIFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces:
EN 336:2003

This document is based on:
EN 336:2013
EN 336:2003

Published:
11 October, 2013
5 September, 2003

This document was published
under the authority of the NSAI
and comes into effect on:
11 October, 2013

ICS number:
79.040

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

English Version

Structural timber - Sizes, permitted deviations

Bois de structure - Dimensions, écarts admissibles

Bauholz für tragende Zwecke - Maße, zulässige
Abweichungen

This European Standard was approved by CEN on 24 August 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Sizes for structural timber	5
4.1 General	5
4.2 Changes in size due to changes in moisture content	6
4.3 Permitted cross-sectional deviations.....	6
4.4 Permitted length deviations.....	6
5 Moisture content measurement.....	6
Bibliography.....	7

Foreword

This document (EN 336:2013) has been prepared by Technical Committee CEN/TC 124 “Timber structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2014, and conflicting national standards shall be withdrawn at the latest by April 2014.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document will supersede EN 336:2003.

Compared to EN 336:2003, the following modifications have been made:

- a) in the scope, the limit to 300 mm is deleted so the standard is available for large cross section;
- b) minimum size changed from 22 mm to 6 mm;
- c) in subclause 4.2, the changes in size due to changes in moisture content are given for hardwoods;
- d) in subclause 4.3, the permitted cross sectional deviations are given for thicknesses and widths above 300 mm;
- e) in Clause 5, moisture content measurement in accordance with the three parts of EN 13183.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Target size is the basis for the standard.

A method of calculating sizes at other moisture levels is provided.

The standard also stipulates a method for the measurement of moisture content.

1 Scope

This European Standard specifies two classes of permitted deviations from target sizes for structural timber of softwood and hardwood species.

It also specifies the moisture content to be used as a reference point for the measurement of sizes, and gives average values for changes in size due to changes in moisture content.

It is applicable to sawn and prepared square-edged structural timber with parallel edges having sawn thicknesses or widths greater than 6 mm.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1309-1, *Round and sawn timber — Method of measurement of dimensions — Part 1: Sawn timber*

EN 13183-1, *Moisture content of a piece of sawn timber — Part 1: Determination by oven dry method*

EN 13183-2, *Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method*

EN 13183-3, *Moisture content of a piece of sawn timber — Part 3: Estimation by capacitance method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

target size

size specified (at the reference moisture content), and to which the deviations, which would ideally be zero, are to be related

3.2

deviation

difference between actual size and the corresponding target size, making allowance for the difference in size due to difference in moisture content (see Clause 5)

3.3

moisture content

amount of water present in timber, expressed as a percentage of the oven-dry mass

4 Sizes for structural timber

4.1 General

Sizes shall be measured in accordance with EN 1309-1.

For the purposes of this European Standard, the reference moisture content is 20 %.

NOTE The reference moisture content is the moisture content at which sizes are given. It is different from target moisture contents which are defined in EN 14298.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- Looking for additional Standards? Visit Intertek Inform Infostore
 - Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation
-