



NSAI
Standards

Irish Standard
I.S. EN 438-3:2016

High-pressure decorative laminates (HPL) -
Sheets based on thermosetting resins
(usually called laminates) - Part 3:
Classification and specifications for
laminates less than 2 mm thick intended for
bonding to supporting substrates

I.S. EN 438-3:2016

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN 438-3:2016

Published:

2016-02-17

This document was published under the authority of the NSAI and comes into effect on:

2016-03-06

ICS number:

83.140.20

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN 438-3:2016 is the adopted Irish version of the European Document EN 438-3:2016, High-pressure decorative laminates (HPL) - Sheets based on thermosetting resins (usually called laminates) - Part 3: Classification and specifications for laminates less than 2 mm thick intended for bonding to supporting substrates

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This page is intentionally left blank

EUROPEAN STANDARD

EN 438-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2016

ICS 83.140.20

Supersedes EN 438-3:2005

English Version

High-pressure decorative laminates (HPL) - Sheets based on thermosetting resins (usually called laminates) - Part 3: Classification and specifications for laminates less than 2 mm thick intended for bonding to supporting substrates

Stratifiés décoratifs haute pression (HPL) - Plaques à base de résines thermodurcissables (communément appelées stratifiés) - Partie 3: Classification et spécifications des stratifiés d'épaisseur inférieure à 2 mm destinés à être collés sur des supports

Dekorative Hochdruck-Schichtpressstoffplatten (HPL) - Platten auf Basis härtpbarer Harze (Schichtpressstoffe) - Teil 3: Klassifizierung und Spezifikationen für Platten mit einer Dicke kleiner als 2 mm, vorgesehen zum Verkleben auf ein Trägermaterial

This European Standard was approved by CEN on 13 December 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN 438-3:2016 (E)

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions, symbols and abbreviations	4
3.1 Terms and definitions.....	4
3.2 Symbols.....	5
4 Material types	5
5 Requirements	5
5.1 General.....	5
5.2 Numerical classification system.....	5
5.3 Alphabetical classification system.....	6
5.4 Nomenclature.....	7
6 Requirements	8
6.1 Compliance.....	8
6.2 Inspection requirements	8
6.2.1 General	8
6.2.2 Colour and pattern	8
6.2.3 Surface finish	8
6.2.4 Reverse side	8
6.2.5 Visual inspection	8
6.3 Dimensional tolerance requirements.....	9
6.4 Test requirements.....	10
6.4.1 General requirements	10
6.4.2 Additional requirements for Type P laminates	12
6.4.3 Requirements for reaction to fire	12
6.5 Supplemental properties.....	12
Annex A (informative) Addendum to sub-clause 6.4.3, relating to fire performance	14
Bibliography	16

European foreword

This document (EN 438-3:2016) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2016, and conflicting national standards shall be withdrawn at the latest by August 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 438-3:2005.

EN 438, *High-pressure decorative laminates (HPL) — Sheets based on thermosetting resins (usually called laminates)*, consists of the following parts:

- *Part 1: Introduction and general information*
- *Part 2: Determination of properties*
- *Part 3: Classification and specifications for laminates less than 2 mm thick intended for bonding to supporting substrates*
- *Part 4: Classification and specifications for Compact laminates of thickness 2 mm and greater*
- *Part 5: Classification and specifications for flooring grade laminates less than 2 mm thick intended for bonding to supporting substrates*
- *Part 6: Classification and specifications for Exterior-grade Compact laminates of thickness 2 mm and greater*
- *Part 7: Compact laminate and HPL composite panels for internal and external wall and ceiling finishes*
- *Part 8: Classification and specifications for design laminates*
- *Part 9: Classification and specifications for alternative core laminates*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 438-3:2016 (E)

1 Scope

This European Standard applies to laminates less than 2 mm thick produced by using an high pressure process, normally intended for bonding to supporting substrates to produce HPL composite panels and establishes a classification system for high-pressure decorative laminates according to their performance and main recommended fields of application, including materials with special characteristics, for example formability or defined reaction to fire. This European Standard also specifies requirements for the properties of the various types of laminates covered by this classification system.

High-pressure decorative laminates are characterised by their qualities, durability and functional performance. HPL sheets are available in a wide variety of colours, patterns and surface finishes; they are resistant to wear, scratching, impact, moisture, heat and staining; and possess good hygienic and anti-static properties, being easy to clean and maintain.

EN 438-2 specifies the methods of test relevant to this European Standard. EN 438-4, EN 438-5, EN 438-6, EN 438-7, EN 438-8 and EN 438-9 are reserved for special types of HPL materials.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 438-2:2016, *High-pressure decorative laminates (HPL) — Sheets based on thermosetting resins (usually called laminates) — Part 2: Determination of properties*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13722, *Furniture — Assessment of the surface gloss*

EN 61340-4-1, *Electrostatics — Part 4-1: Standard test methods for specific applications — Electrical resistance of floor coverings and installed floors (IEC 61340-4-1)*

EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1)*

EN ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants (ISO 11664-2)*

3 Terms and definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

high-pressure decorative laminate(s)

HPL

sheet(s) consisting of decorative surface layer(s) and core layers bonded together by an high pressure process

Note 1 to entry: Typical values for the high pressure process are a temperature of ≥ 120 °C and a pressure of ≥ 5 MPa.

This is a free preview. Purchase the entire publication at the link below:

[Product Page](#)

-
- [Looking for additional Standards? Visit Intertek Inform Infostore](#)
 - [Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation](#)
-